Hrastovec 22, 1236 Trzin, Slovenija, tel.: 00 386 (0)1 56 21 843, mob.: 00 386 (0)40 855 805
maximo3@siol.net, www.maximo-tekstil.com

TECHNICAL DATA SHEET

art. PANAMA 260

Stretch 20%

Workwear fabric · Work trousers, jackets and uniforms · Stretch twill

64% PES / 34% CO / 2% EA	260 g/m²	Twill 2/1	145 cm
COMPOSITION	WEIGHT ±5%	WEAVE	FINISHED WIDTH

01 BASIC CHARACTERISTICS

PARAMETER	TEST METHOD	VALUE
Composition		64% polyester / 34% cotton / 2% elastane
Colour		navy, piece dyed (disperse / vat)
Weight	EN ISO 3801	260 g/m² (±5%)
Weight per linear metre	calculated	approx. 377 g/m
Weave	EN ISO 8020	twill 2/1 S
Finished width	EN ISO 3932	145 cm (±1.3 cm)
Finish		regular comfort, stretch

02 PHYSICAL PERFORMANCE

PARAMETER	TEST METHOD	RESULT
Dimensional stability, washing	ISO 6330 6N	WARP −3% WEFT −3%
Tensile strength	ISO 13934-1	WARP 1500 N WEFT 600 N
Tear strength	ISO 13937-1	WARP 55 N WEFT 50 N
Stretch, elasticity / recovery / growth	ISO 14704-1	20% / 97% / 3%
Abrasion resistance, 12 kPa, 20,000 cycles	ISO 12947-2	no thread break
Pilling resistance, 5000 cycles	ISO 12945-2	Grade 2–3

03 COLOUR FASTNESS

PARAMETER	TEST METHOD	GRADE
Washing	ISO 105-C06 E2S	CHANGE 4 STAINING 4
Perspiration, acidic	ISO 105-E04	CHANGE 4 STAINING 4
Perspiration, alkaline	ISO 105-E04	CHANGE 4 STAINING 4
Rubbing	ISO 105-X12	DRY 3 WET 2–3
Bleaching, hypochlorite, colour change	ISO 105-N01	4

04 CARE INSTRUCTIONS



Washing
max 60 °C



Bleaching
Chlorine allowed



Tumble dry
Low heat



Ironing
Medium, 150 °C

Values are typical guide values. *Colour performance may vary depending on the shade; dark shades can show lower wet rubbing fastness. A build up of softeners can lead to pilling and should be avoided. Characteristics may vary within commercial tolerances. Please consult us for specific values. The data is based on specific materials and tested by sources believed to be reliable; no guarantee is expressed or implied as to use, handling or possession of the product.*

More workwear fabrics
maximo-tekstil.com