Hrastovec 22, 1236 Trzin, Slovenija, tel.: 00 386 (0)1 56 21 843, mob.: 00 386 (0)40 855 805
maximo3@siol.net, www.maximo-tekstil.com

TECHNICAL DATA SHEET

art. DRACO 215

Water repellent

Workwear fabric · Chef trousers, kitchen and service wear · Yarn-dyed check

85% CO / 13% PES / 2% XLA	215 g/m²	Twill 2/2	152 cm
COMPOSITION	WEIGHT ±5%	WEAVE	FINISHED WIDTH

01 BASIC CHARACTERISTICS

PARAMETER	TEST METHOD	VALUE
Composition		85% cotton / 13% polyester / 2% XLA
Colour		yarn-dyed black / white check (vat)
Weight	EN ISO 3801	215 g/m² (±5%)
Weight per linear metre	calculated	approx. 325 g/m
Weave	EN ISO 8020	twill 2/2 S
Finished width	EN ISO 3932	152 cm
Finish		water repellent, comfort stretch (XLA)

02 PHYSICAL PERFORMANCE

PARAMETER	TEST METHOD	RESULT
Dimensional stability, washing	ISO 6330 6N	WARP −3% WEFT −3%
Tensile strength	ISO 13934-1	WARP 500 N WEFT 500 N
Tear strength	ISO 13937-1	WARP 35 N WEFT 40 N
Stretch, elasticity / recovery / growth	ISO 14704-1	15% / 96% / 4%
Pilling resistance, 1000 cycles	ISO 12945-2	Grade 3
Water repellency, spray test	ISO 4920	100
pH value	ISO 3071	4.5 – 7.5

03 COLOUR FASTNESS

PARAMETER	TEST METHOD	GRADE
Washing	ISO 105-C03	CHANGE 4 STAINING 4
Perspiration, acidic	ISO 105-E04	CHANGE 4 STAINING 4
Perspiration, alkaline	ISO 105-E04	CHANGE 4 STAINING 4
Rubbing	ISO 105-X12	DRY 4 WET 3

04 CARE INSTRUCTIONS



Washing
max 60 °C



Bleaching
Do not bleach



Tumble dry
Low heat



Ironing
Medium, 150 °C

Values are typical guide values. *Colour performance may vary depending on the shade; dark shades can show lower wet rubbing fastness. A build up of softeners can lead to pilling and should be avoided. Characteristics may vary within commercial tolerances. Please consult us for specific values. The data is based on specific materials and tested by sources believed to be reliable; no guarantee is expressed or implied as to use, handling or possession of the product.*

More workwear fabrics
maximo-tekstil.com