Hrastovec 22, 1236 Trzin, Slovenija, tel.: 00 386 (0)1 56 21 843, mob.: 00 386 (0)40 855 805
maximo3@siol.net, www.maximo-tekstil.com

TECHNICAL DATA SHEET

art. BRAVO 210

On stock

Workwear fabric · Medical, chef and workwear · 60/40 cotton-rich polycotton twill

60% CO / 40% PES	210 g/m²	Twill 2/1	150 cm
COMPOSITION	WEIGHT ±3%	WEAVE	FINISHED WIDTH

01 BASIC CHARACTERISTICS

PARAMETER	TEST METHOD	VALUE
Composition		60% cotton / 40% polyester
Colours on stock		27 colours, see maximo-tekstil.com
Weight	EN ISO 3801	210 g/m² (±3%)
Weight per linear metre	calculated	approx. 315 g/m
Weave	EN ISO 8020	twill 2/1
Finished width	EN ISO 3932	150 cm
End use		workwear, medical and chef wear

02 PHYSICAL PERFORMANCE

PARAMETER	TEST METHOD	RESULT
Dimensional stability, washing 60 °C	ISO 6330	WARP −2% WEFT −2%
Tensile strength	ISO 13934-1	WARP 700 N WEFT 600 N
Pilling resistance, 2000 cycles	ISO 12945-2	Grade 3–4

03 COLOUR FASTNESS

PARAMETER	TEST METHOD	GRADE
Washing	ISO 105-C03	CHANGE 4 STAINING 4
Perspiration, acidic	ISO 105-E04	CHANGE 4 STAINING 4
Perspiration, alkaline	ISO 105-E04	CHANGE 4 STAINING 4
Water	ISO 105-E05	CHANGE 4 STAINING 4
Rubbing	ISO 105-X12	DRY 4 WET 4
Light	ISO 105-B02	4

04 CARE INSTRUCTIONS



Washing
max 60 °C



Bleaching
Do not bleach



Tumble dry
Low heat



Ironing
Medium, 150 °C



Dry cleaning
Professional, P

Values are typical guide values. *Colour performance may vary depending on the shade; dark shades can show lower wet rubbing fastness. A build up of softeners can lead to pilling and should be avoided. Characteristics may vary within commercial tolerances. Please consult us for specific values. The data is based on specific materials and tested by sources believed to be reliable; no guarantee is expressed or implied as to use, handling or possession of the product.*

More workwear fabrics
maximo-tekstil.com