Multinorm & FR Proban fabrics

Flame retardant workwear fabrics with durable FR Proban finish · Collection 2026

MAXIMO TEKSTIL

www.maximo-tekstil.com

6 STRETCH FABRICS

#	ARTICLE	COMPOSITION	WEAVE	G/M²	WIDTH CM	FEATURES	FR	ANTI-STATIC	NEGA-STAT	HI-VIS	CHEM. PROTECT.
1	**Extract**	78% CO / 19% PES / 3% XLA	Twill 2/1	**210**	140–142 (55/56")	DRD	✓	–	–	–	–
2	**Remy Naga Stretch**	85% CO / 13% PES / 2% spandex / 1% Nega	Satin 4/1	**230**	150 (59")	Antistatic grid 6×6 mm	✓	✓	✓	–	–
3	**Atish**	78% CO / 19% PES / 3% XLA	Twill 3/1	**235**	140–142 (55/56")	DRD	✓	–	–	–	–
4	**Touch Stone Stretch Nega**	97% CO / 2% spandex / 1% Nega	Twill 3/1	**270**	150 (59")	Antistatic grid 6×6 mm	✓	✓	✓	–	–
5	**Zhob**	98% CO / 2% spandex	Broken twill 3/1	**280**	140–142 (55/56")	Teflon finish · VAT	✓	–	–	–	–
6	**Chaghi**	98% CO / 2% spandex	Twill 3/1 Z	**315**	140–142 (55/56")	VAT	✓	–	–	–	–

8 NON-STRETCH FABRICS

#	ARTICLE	COMPOSITION	WEAVE	G/M²	WIDTH CM	FEATURES	FR	ANTI-STATIC	NEGA-STAT	HI-VIS	CHEM. PROTECT.
7	**Multi Pro / Kaghan**	75% CO / 24% PES / 1% Nega	Twill 3/1	**260**	150 (59")	Chemical protection	✓	✓	✓	–	✓
8	**Murree**	88% CO / 11% PA / 1% antistatic	Twill 3/1 S	**260**	147 (58")	VAT	✓	✓	–	–	–
9	**Biyas**	80% CO / 20% PA	Twill 3/1 S	**280**	147 (58")	VAT	✓	–	–	–	–
10	**Turbat**	80% CO / 20% PA	Twill 3/1 S	**320**	147 (58")	VAT	✓	–	–	–	–
11	**K2**	100% CO	Twill 3/1	**330**	150 (59")		✓	–	–	–	–
12	**Proban 330 / MAZ**	75% CO / 25% PES (CVC) · HV yellow	Satin 4/1 Z	**330**	150 (59")	Hi-Vis	✓	–	–	✓	–
13	**Makran**	75% CO / 24% PES / 1% Negastat	Twill 3/1	**360**	150 (59")	Chemical protection	✓	✓	✓	–	✓
14	**Hunza**	85% CO / 14% PES / 1% Nega	Twill 3/1	**380**	150 (59")	Chemical protection	✓	✓	✓	–	✓

FR Proban®
Durable flame retardant finish, chemically bonded to the cotton fibre. Lasts the life of the garment, including industrial laundering.

Teflon™ finish
Fabric protector that repels water, oil and dirt. Garments stay clean longer and are easier to wash.

Multinorm
One fabric that meets several protective standards at once, e.g. flame, welding, chemical splash and antistatic protection.

VAT dyed
Dyeing with vat dyes, the highest colour fastness to washing and light. Ideal for industrial laundering.

Antistatic / Negastat®
Conductive fibre woven into the fabric (here in a 6×6 mm grid) that dissipates static electricity. Typically used in antistatic garments (EN 1149).

DRD
Disperse / reactive dyed. Each fibre in a cotton / polyester blend is dyed with its own dye class for an even, durable shade.

Chemical protection
Water based finish that repels liquid chemicals such as acids and alkalis and limits penetration. Typically used in EN 13034 garments.

Stretch
Elastic fibre (spandex or XLA elastolefin) for freedom of movement and comfort.

Hi-Vis
Fluorescent high visibility colour for warning clothing according to EN ISO 20471.

Abbreviations
CO cotton · PES polyester · PA polyamide (nylon) · XLA elastolefin · ✓ yes

Makran tested to EN ISO 11611 (class 1, A1+A2) and EN 13034 · Technical data sheets on request

MAXIMO TEKSTIL d.o.o. · maximo3@siol.net · www.maximo-tekstil.com