MAXIMO TEKSTIL

TECHNICAL DATA SHEET
MS 125
MADE TO ORDER · REV. 11/2026

POLYESTER-RICH POLYCOTTON · WORKWEAR AND UNIFORMS

MS 125

Yarn-dyed mini check · mechanical stretch

COMPOSITION	WEIGHT	WEAVE	WIDTH
65% PES / 35% CO	125 g/m²	Plain 1/1	152 cm



1 Fabric specification

ARTICLE	MS 125
COMPOSITION	65% Polyester / 35% Cotton
WEIGHT	125 g/m² (±5%)
WIDTH	152 cm (60")
WEAVE	Plain 1/1
DYEING	Yarn dyed (disperse / vat)
FINISH	Mechanical stretch, crease resistant, soil release
PATTERN	Mini check
AVAILABILITY	Made to order

2 Colour fastness

TEST	METHOD	COLOUR CHANGE	STAINING, COTTON
Washing	ISO 105-C06 C2S	4	4
Industrial laundering, 50 cycles	ISO 15797	4	4
Perspiration, acid	ISO 105-E04	4	4
Perspiration, alkaline	ISO 105-E04	4	4
Rubbing	ISO 105-X12	DRY 4	WET 3
Hypochlorite bleaching	ISO 105-N01	4	–

Grades 1 to 5, 5 is best.

3 Physical properties

TEST	METHOD	WARP	WEFT
Tensile strength	ISO 13934-1	400 N	250 N
Tear strength	ISO 13937-1	20 N	15 N
Dimensional stability, 10 cycles	ISO 15797	−3%	−3%

4 Stretch and performance

TEST	METHOD	RESULT
Elasticity	ISO 14704-1	10%
Recovery	ISO 14704-1	96%
Growth	ISO 14704-1	4%
Air permeability	EN ISO 9237	400 mm/s
Pilling	ISO 12945-2	4
Smoothness appearance	AATCC 124	4
Soil release	AATCC 130	3
Formaldehyde	EN ISO 14184-1	< 75 ppm

5 Care instructions

- Wash at 70 °C
- Chlorine bleach allowed
- Tumble dry, normal
- Iron, medium

Note. Colour performance may vary slightly with the shade. Values are typical results from laboratory testing of production lots. Please request a sample before ordering.

Maximo Tekstil d.o.o. · Hrastovec 22, 1236 Trzin, Slovenia
narocila@maximo-tekstil.com · +386 1 562 1843 · www.maximo-tekstil.com