MAXIMO TEKSTIL

Hrastovec 22, 1236 Trzin, Slovenija, tel.: 00 386 (0)1 56 21 843, mob.: 00 386 (0)40 855 805
maximo3@siol.net, www.maximo-tekstil.com

TECHNICAL DATA SHEET

art. ADIDAS 200

On stock

Workwear fabric · Medical, chef and light workwear · 100% cotton twill

100% CO	200 g/m²	Twill 2/1	150 cm
COMPOSITION	WEIGHT ±3%	WEAVE	FINISHED WIDTH

01 BASIC CHARACTERISTICS

PARAMETER	TEST METHOD	VALUE
Composition		100% cotton
Colours on stock		Bianco 0001, Aqua Green 344C, Black 9001
Weight	EN ISO 3801	200 g/m² (±3%)
Weight per linear metre	calculated	approx. 300 g/m
Weave	EN ISO 8020	twill 2/1
Finished width	EN ISO 3932	150 cm
End use		workwear, medical and chef wear

02 PHYSICAL PERFORMANCE

PARAMETER	TEST METHOD	RESULT
Dimensional stability, washing 60 °C	ISO 6330	WARP −2% WEFT −2%
Tensile strength	ISO 13934-1	WARP 500 N WEFT 300 N
Tear strength	ISO 13937-1	WARP 20 N WEFT 15 N
Abrasion resistance, 20,000 cycles	ISO 12947-2	no thread break
Pilling resistance, 2000 cycles	ISO 12945-2	Grade 3–4

03 COLOUR FASTNESS

PARAMETER	TEST METHOD	GRADE
Washing	ISO 105-C03	CHANGE 4 STAINING 4
Perspiration, acidic	ISO 105-E04	CHANGE 4 STAINING 4
Perspiration, alkaline	ISO 105-E04	CHANGE 4 STAINING 4
Water	ISO 105-E05	CHANGE 4 STAINING 4
Rubbing	ISO 105-X12	DRY 4 WET 3
Light	ISO 105-B02	4

04 CARE INSTRUCTIONS

Washing	Bleaching	Tumble dry	Ironing	Dry cleaning
max 60 °C	Do not bleach	Low heat	Medium, 150 °C	Professional, P

Values are typical guide values. *Colour performance may vary depending on the shade; dark shades can show lower wet rubbing fastness. A build up of softeners can lead to pilling and should be avoided. Characteristics may vary within commercial tolerances. Please consult us for specific values. The data is based on specific materials and tested by sources believed to be reliable; no guarantee is expressed or implied as to use, handling or possession of the product.*

More workwear fabrics
maximo-tekstil.com