

**PASS**

**SUBMITTER**

Noble House Home Furnishings LLC  
 21325 Superior Street, Chatsworth, CA 91311, United States of America.



**STYLE  
NUMBER**

/

**PRODUCT  
DESCRIPTION**

MDF

**EXECUTIVE  
SUMMARY**

The sample(s) MEET all the tested requirement(s).

**REMARKS**

As per client requested, only Formaldehyde Content ASTM D6007-14 CARB/ TSCA Title VI / 40 CFR 770 test was conducted.

**TECHNICAL  
QUESTIONS**

Muhammad Akmalhakim  
 (607) 510 2086  
 akmalhakim.mohd-fauzi@bureauveritas.com

**SIGNATURES BUREAU VERITAS CPS SDN BHD**

**GENERAL  
INFORMATION**

Noor Najwa Laili  
 (607) 510 2086  
 noor.najwa@bureauveritas.com



**MUHAMMAD SYAHIN FIRDAUS BIN AZIZ  
 ZAMBRI  
 M/5690/9201/21  
 AUTHORIZED REPORT APPROVER –  
 ANALYTICAL**



BUREAU  
VERITAS

# Test Report: (1222)238-0011 NOBLE HOUSE HOME FURNISHINGS LLC

Received Date: August 26, 2022  
Report Date: September 07, 2022

VENDOR NAME	NOBLE HOUSE HOME FURNISHINGS LLC
AGENT NAME	/
FACTORY NAME	ID : 1306
NUMBER OF CARTONS/SAMPLES	3 PIECES
ITEM NUMBER	/
MODEL NUMBER	/
PURCHASE ORDER NUMBER	/
COUNTRY OF ORIGIN	MALAYSIA
CLIENT REFERENCE NUMBER	/
UPC CODE	/
COLOR	/
ASSORTMENT NUMBER	/
SKU/SKN NUMBER	/
PRODUCT END USE	/
LOT NUMBER	/
COUNTRY OF DESTINATION	UNITED STATES
BUYER NAME	/
TEST REQUESTED	FORMALDEHYDE CONTENT ASTM D6007-14 CARB/ TSCA Title VI / 40 CFR 770
PROTOCOL STAR LEVEL	/
FAIL RETEST	NO
PREVIOUS REPORT NUMBER	/
RETEST SAMPLE NUMBER	/
REPORT EXPIRATION DATE	September 07, 2023
REPORT REVISION DATE	/
REVISION(S)	/
REPORT REVISION REASON	/
TESTING DATE	August 26, 2022 –September 06, 2022



BUREAU  
VERITAS

# Test Report: (1222)238-0011 NOBLE HOUSE HOME FURNISHINGS LLC

Received Date: August 26, 2022  
Report Date: September 07, 2022

## TEST RESULTS FOR MDF

### TEST RESULT(S):

#### Formaldehyde Content in Air from Wood Products Using a Small-Scale Chamber

**Test Method** : ASTM International Standard ASTM D6007-14.

Test Item(s)	Sample description/ Location	Material	Style(s)
I001	MDF	MDF	-

Test Item(s)	I001		
Type	-		
Parameter	Unit	Limit	Result
Number of specimens in charge	-	-	3
Number of surfaces exposed	-	-	6
Calculated Q/A ratio	cu. m/hr/sq. m	-	1.92
Air-sampling rate	L/min	-	1.00
Air-sampling time	min	-	60
HCHO in sample	ppm	Table 1	< 0.03
<b>Conclusion</b>	PASS		

Note / Key :

"<" = Less than

">" = Greater than

deg. C = degree Celsius

ppm = part(s) of formaldehyde per million parts of air

L/min = Liter(s) per minute

cu. m/hr/sq. m = cubic meter(s) of air per hour per square meter test area

s = second(s)

Q/A ratio = Ratio of air flow through the chamber (Q) to sample surface area (A), cu. m/h/sq. m

#### Requirement: Table 1

Formaldehyde Emission Standards for Composite Wood Products (TSCA Title VI / 40 CFR 770)					
Plywood (HWPW), Particleboard (PB), and Medium Density Fiberboard (MDF)					
Compliance Date	HWPW-VC	HWPW-CC	PB	MDF	Thin MDF
22-12-2017	0.05	0.05	0.09	0.11	0.13

END OF REPORT