



CONSUMER PRODUCTS SERVICES DIVISION

<SHANDONG SINOMAX HOUSEHOLD PRODUCTS TECHNOLOGY LIMITED>

Technical Report: (9024)187-0130  
Date Received: JUL. 05, 2024  
Revision Date: /

JUL. 11, 2024  
Page 1 of 4

ERIC GAI  
SHANDONG SINOMAX HOUSEHOLD PRODUCTS  
TECHNOLOGY LIMITED  
DAGUANG ZHUANG VILLAGE, LIZHUANG  
STREET, TANCHENG COUNTY, LINYI CITY SHANDONG  
PROVINCE

Sample Description:	WHITE SPONGE C28130		
Manufacturer:	SHANDONG SINOMAX HOUSEHOLD PRODUCTS TECHNOLOGY LIMITED	PO No.:	/
Buyer:	/	Style:	/
Country of Origin:	CHINA	Country of Destination:	/
Color:	/	SKU No.:	/
Protocol No.:	/	UPC Code:	/
Retest:	No	Lot No:	/
Previous Report No.:	/		

SUMMARY OF THE TEST RESULTS

TEST REQUESTED	CONCLUSION
RESULT FOR FOAM TECHNICAL BULLETIN 117 -2013 SECTION III	PASS

Remark:

1. The client specified test method and requirement.
2. With the client's prior consent, Result for foam Technical bulletin 117 -2013 Section III were subcontracted test item.

C/N QD/LIU/AZ

Bureau Veritas Consumer Products Service  
(Shanghai) Co., Ltd. Qingdao Branch,  
Floor 3, No. 3 Building, GNDC Tech Base,  
No.192 Zhuzhou Road, Lao Shan District,  
Qingdao  
Code: 266101  
Tel: 86-0532-58827999,  
Fax: 86-0532-88706839  
Email: bvcpinfo.qd@cn.bureauveritas.com  
Website: www.bureauveritas.com/cps

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at <http://www.bureauveritas.com/home/about-us/our-business/cps/about-us/terms-conditions/> and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our prior written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all of the tests requested by you and the results thereof based upon the information that you provided to us. Measurement uncertainty is only provided upon request for accredited tests. Statements of conformity are based on simple acceptance criteria without taking measurement uncertainty into account, unless otherwise requested in writing. You have 60 days from date of issuance of this report to notify us of any material error or omission caused by our negligence or if you require measurement uncertainty; provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.



Vendor name: SHANDONG SINOMAX HOUSEHOLD PRODUCTS TEC  
HNOLOGY LIMITED  
Technician Report: (9024)187-0130  
JUL. 11, 2024  
Page 2 of 4

**BVCPS (SHANGHAI)-QINGDAO BRANCH CONTACT INFORMATION FOR THIS REPORT**

**Technical enquiry:**

Anderson zhang 86-532-58827985 anderson.zhang@bureauveritas.com

**General enquiry and invoicing:**

Mandy Zhang 86-532-58827932 mandy.zhang@bureauveritas.com

Bella Wang 86-532-58827931 bella.wang@bureauveritas.com

**BUREAU VERITAS  
CONSUMER PRODUCTS SERVICE DIVISION (SHANGHAI)-QINGDAO  
BRANCH**

ANDERSON ZHANG  
QINGDAO HARDLINE REPORTING MANAGER



### **TEST RESULT**


Result for foam Technical bulletin 117 -2013 Section III (Resilient Filling Material Datasheet)

Specimen No.	Smoldering time (>45min or Not)	Char Length / in	Requirement	Rating
1	Not	0.3	Maximum char length of any specimen shall not exceed 1.5 inches in any direction from cigarette.	Pass
2	Not	0.3		Pass
3	Not	0.3		Pass

**Remark:**

1. If the specimen continues to smolder after the 45 minute test duration, the resilient filling material fails the test.
2. If more than one specimen fails, the resilient filling material fails the test.
3. If any one of the three initial specimens fails, repeat the test on additional three specimens. Record the additional test specimens result in new datasheet and provide the Final Overall Rating.
4. If all three additional specimens pass the test, the resilient filling material passes the test. If any one of the additional three specimens fails, the resilient filling material fails the test.

**Original Sample**



**END OF REPORT**