



中国认可
国际互认
检测
TESTING
CNAS L4743

Test Report

Report No.: AJFS2312012521FF

Date: JAN.10, 2024

Page 1 of 3

ZHEJIANG WANG JIA FENG FAN FOAM MANUFACTURING CO. LTD

NO .50 HUITONG ROAD HUIMIN STREET, JIASHAN COUNTY, ZHEJIANG

Sample Description: C3013W FOAM

Color: WHITE

Density: 30kg/m³

Style/Item No.: /

Supplier: JIANGSU WANGJIA Demeanour NEW MATERIAL TECHNOLOGY CO., LTD

Manufacturer: ZHEJIANG WANG JIA FENG FAN FOAM MANUFACTURING CO. LTD

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Test Requested:

State of California, Department of Consumer Affairs, Bureau Household Goods and Services, Technical Bulletin 117-2013(R2019), Requirement, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture, Section 3 Resilient Filling Material Test.

Test Results: -- See attached sheet --

Conclusion: The tested sample **meets** the Requirements of Section 3 for Resilient Filling Material Test of California Technical Bulletin 117-2013(R2019).

Test Period:

Sample Receiving Date : DEC.26, 2023

Test Performing Date : DEC.26, 2023 TO JAN.02, 2024

Signed for and on behalf of

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch

Echo

Echo Li

Approved Signatory

Scan to see the report



AJFS2312012521FF
Verification:
check.sgsonline.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 sgs.china@sgs.com

Test Report

Report No.: AJFS2312012521FF

Date: JAN.10, 2024

Page 2 of 3

Test Conducted

The test was conducted in accordance with California Technical Bulletin 117-2013(R2019) Testing the Smolder Resistance of Materials Used in Upholstered Furniture, Section 3: Resilient Filling Material Test.

Test Specimen

Description	Foam
Color	White
Density	29.9 kg/m ³
Size of specimen	203 mm × 127 mm × 51mm & 203 mm × 203 mm × 51 mm

Conditioning:

Prior to testing, the specimens were conditioned for a minimum of 24 hours, at 70 ± 5°F (21°C ± 3°C) and less than 55% relative humidity.

Test Result

Specimen No.	Duration of smoldering (min:sec)	Open flaming (Yes/No)	Vertical char length (mm)	Comment
1	31min40s	No	15	Pass
2	32min29s	No	16	Pass
3	31min44s	No	15	Pass

Pass / Fail Criteria:

- 1) A single mock-up test specimen fails the requirements of this test procedure if any of the following criteria occurs:
 - a) The mock-up test specimen continues to smolder after the 45 minute test duration;
 - b) A vertical char length (measured as described in step 17.9 of ASTM E1353-08a ^{§1}) of more than 1.5inches (38 mm) develops on the cover fabric.
 - c) The mock-up test specimen transitions to open flaming.
- 2) The resilient filling material passes the test if three mock-up specimens pass the test.
- 3) If more than one specimen fails, the resilient filling material fails the test.
- 4) If any one of the three initial specimens fails, repeat the test on additional three specimens.
- 5) If all three additional specimens pass the test, the resilient filling material passes the test. If any one of the additional three specimens fails, the resilient filling material fails the test.

Statement: This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.



Test Report

Report No.: AJFS2312012521FF

Date: JAN.10, 2024

Page 3 of 3

Photo Appendix:



SGS authenticate the photo on original report only

End of Report