

Test Report

Number: SZHH01781813

Applicant: NOBLE HOUSE HOME FURNISHINGS LLC
BAIMEI NO.7 BUILDING, FENGHUA/YONGFENG
INDUSTRIAL ZONE, JINGXI TOWN, MINHOU COUNTY,
FUZHOU, FUJIAN, CHINA

Date: Mar 21, 2023

Attn: Keller Zheng

Sample Description:

Six (6) submitted samples said to be **chair leg&zipper head**.

Reference No. : SP2023020115.

Manufacturer : ID: 696.

Country of Origin : China.

Country of Destination : USA.

Date Sample Received : Mar 16, 2023.

Testing Period : Mar 16, 2023 – Mar 20, 2023.



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.



Page 1 of 5



Test Report

Number: SZHH01781813

Conclusion:

Tested Sample
Submitted Samples

Standard
Adhesive Tape Test
- With reference to ASTM D3359-22 method A

Result
See Test Conducted

Tested components of
submitted samples

U.S. CFR Title 16 Part 1303 total Lead content

Pass

Authorized by:
For Intertek Testing Services Shenzhen Ltd
Xiamen Branch



Rachel L. Guo
General Manager



Page 2 of 5

Intertek Testing Services Shenzhen Ltd. Xiamen Branch
深圳天祥质量技术服务有限公司厦门分公司

Unit 1E, 1st floor, Unit 2C, 2nd floor, Unit 4C
、4D、4L、4O, 4th floor, Xinglian
Building, No.2, Chuangxin RD, Huoju Hi-
tech District, Xiamen, Fujian, P.R.C
福建省厦门市湖里区火炬高新区创新路2
号兴联电子大厦一楼1E区, 二楼2C和四楼
4C、4D、4L、4O

Tel: +86592 8063339
Fax: +86592 8060054
www.intertek.com
www.intertek.com.cn



Test Report

Number: SZHH01781813

Tests Conducted

1 Adhesive Tape Test

With reference to ASTM D3359-22– standard test methods for rating adhesion by tape test, test method A – X cut tape test.

No. of sample tested : Two (2) pieces.






Result :

Coating	Rating
A	5A
B	5A

Client Requirement : Not Specified

Rating : See test data

Remark :

Classification		Surface of "X" - Cut from which flaking/peeling has occurred
5A	No peeling or removal	None
4A	Trace peeling or removal along incisions or at their intersection	
3A	Jagged removal along incisions up to 1/16" on either side	
2A	Jagged removal along most of incisions up to 1/8" on either side	
1A	Removal from most of the area of the X under the tape	
0A	Removal beyond the area of the X	

Pressure sensitive tape applied: Intertape 51596.



Page 3 of 5




Test Report

Number: SZHH01781813

Tests Conducted

Photo for Reference:



2 Total Lead (Pb) Content (U.S. 16 CFR Part 1303)

As per Standard Operating Procedure for Determining Lead (Pb) in paint and other similar surface coatings, test method CPSC-CH-E1003-09.1 was used and total Lead content was determined by Inductively Coupled Argon Plasma Spectrometry.

Element	Result (%)		Reporting Limit (%)	Limit (%)
	Tested Component			
	(1+2+3)	(4+5)		
Lead (Pb)	0.001	0.001	0.001	0.009

The above limit was quoted according to U.S. CFR Title 16 Part 1303 for Ban of Lead-containing Paint and Certain Consumer Products Bearing Lead-containing Paint.

ND = Not detected (less than reporting limit)

Tested Components:

- (1) Black coating on metal (chair leg)
- (2) Pewter color with black base coating on metal (chair leg)
- (3) Gray coating on metal (big & small zipper head)
- (4) Khaki coating on metal (big zipper head)
- (5) Dark khaki coating on metal (small zipper head)

End of report



Page 4 of 5



Test Report

Number: SZHH01781813

Tests Conducted

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band $w = U$) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) received and tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek.



Page 5 of 5

