Print-ready files

Generated by `python cad/tools/export_print.py` from `cad/parts/*.py` (every part builds **PASS** through the 3dprint-contract checks: watertight, walls, overhangs/bridges, bed fit, clearances, part claims). Geometry is already in print orientation: **do not auto-orient**. Units mm. Printer: Bambu Lab X2D, 0.4 mm nozzle, textured PEI. See `docs/handoffs/03-printing.md` (coupons first, then parts; Matt starts every print).

Part	Qty	Material	Process	Supports	Slicer overrides	Size (mm)	Verdict	Check wa
`moon_shell`	1	pla-basic-white	0.12-fine	none	wall_loops=6, sparse_infill_density=100%, top_shell_layers=0, bottom_shell_layers=3, seam_position=back, brim_type=outer_only, brim_width=3	50.0 x 50.0 x 46.7	PASS	wall_min:0.
`moon_base`	1	petg-basic	0.16-fine	none	-	38.7 x 38.7 x 14.1	PASS	-
`moon_ring`	1	petg-basic	0.20-standard	none	-	33.2 x 33.2 x 0.6	PASS	wall_min:0.
`pack_front`	1	petg-basic	0.20-standard	none	-	39.3 x 76.9 x 18.6	PASS	wall_min:0.
`pack_back`	1	petg-basic	0.20-standard	none	-	35.3 x 73.8 x 3.8	PASS	wall_min:0.
`pack_clip`	1	petg-basic	0.20-standard	none	-	34.0 x 61.3 x 3.7	PASS	-
`button_caps`	1 plate (3 caps)	petg-basic	0.12-fine	none	-	33.0 x 9.0 x 4.3	PASS	wall_min:0. first_layer_
`jig_led_board`	1	petg-basic	0.20-standard	none	-	40.0 x 40.0 x 4.0	PASS	wall_min:0.
`coupon_fit`	1	petg-basic	0.20-standard	none	-	70.0 x 36.0 x 8.5	PASS	wall_min:0.
`coupon_bayonet`	1	petg-basic	0.16-fine	none	-	80.0 x 38.7 x 5.8	PASS	wall_min:0.
`coupon_litho_wedge`	1	pla-basic-white	0.12-fine	none	-	86.0 x 14.0 x 3.2	PASS	wall_min:0.

Process names map to Bambu Studio presets: `0.12-fine` = 0.12 mm Fine, `0.16-fine` = 0.16 mm Optimal, `0.20-standard` = 0.20 mm Standard. Materials: Bambu PLA Basic (white) for the moon and step wedge, Bambu PETG Basic for everything else (it sits next to warm electronics).

Moon: 100 % infill + 6 walls makes the lithophane solid; outer brim 3 mm (the skirt ring is the only bed contact). The inner dome closes over the top as a short bridge - expected; nothing can be supported inside.