

This is to certify that, in accordance with TS00 General Requirements for Certification of Fire Protection Products
The undermentioned products of

JOTUN A/S

PO Box 2021, Sandefjord, N-3202, Norway Tel: +47 334570000

Have been assessed against the requirements of the Technical Schedule(s) denoted below and are approved for use subject to the conditions appended hereto:

CERTIFIED PRODUCT SteelMaster 600WF

TECHNICAL SCHEDULE
TS15 INTUMESCENT
COATINGS FOR STEELWORK

Signed and sealed for and on behalf of Warringtonfire Testing and Certification Limited

Paul Duggan

Certification Manager



Issued: Revised Date: Valid to: 29th March 2018 24th March 2020 28th March 2023



Page 1 of 20



SteelMaster 600WF

- This certification is provided to the client for their own purposes and we cannot opine on whether it will be accepted by Building Control authorities or any other third parties for any purpose.
- This approval relates to the use of SteelMaster 600WF for the fire protection of I-section beams and columns. The precise scope is given in Tables 1 to 18 which show the total dry film thickness of SteelMaster 600WF (excluding primer and top sealer) required to provide fire resistance periods in accordance with BS476: Part 21: 1987 of 15 minutes up to 105 minutes for I/H section beams, up to 90 minutes I/H section columns, up to 60minutes for Rectangular Hollow Section (RHS) columns and up to 75 minutes for Circular Hollow Section (CHS) columns differing section factors.
- 3. The products are approved on the basis of:
 - i) Initial type testing.
 - ii) A design appraisal against TS15.
 - iii) Certification of quality management system to ISO 9001.
 - iv) Inspection and surveillance of factory production control
 - v) Audit testing
- 4. The data referring to three-sided fire exposure of beams relate to beams supporting concrete floor slabs. Separate consideration is required where this is not the case.
- 5. The data shown is applicable to steel sections blast cleaned to ISO 8501-1 SA2.5 or equivalent and primed with a suitable and compatible primer. Specifications of surface preparations, primers and top sealers is available from Jotun A/S whose responsibility is to ensure that SteelMaster 600WF is compatible for use in respect of both ambient and fire conditions. The total dry film thickness of primer and top sealer together should not exceed that tested.
- 6. The data shown is applicable to SteelMaster 600WF applied by spray to horizontal, vertical, flexural and compression members supporting loads up to the maximum design loads specified in BS449: Part 2 as indicated in Tables 1 and 2.
- 7. The approval relates to ongoing production. Product and/or its immediate packaging is identified with the manufacturers' name, the product name or number, the CERTIFIRE name or name and mark, together with the CERTIFIRE certificate number and application where appropriate.
- 8. The data shown in the tables is based on assessments which comply with the criteria for acceptability now incorporated within the CERTIFIRE scheme.

Page 2 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pel Rag-



SteelMaster600WF

			Т	able1: I/H-Se	ction Beam	: Fire resist	ance period	l: 15 Minute	s			
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatu	re of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
35	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
40 45	0.154	0.154 0.154	0.154									
50	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
55	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
60	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
65	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
70	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
75	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
80	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
85	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
90 95	0.154	0.154 0.154										
100	0.157	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
105	0.163	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
110	0.170	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
115	0.176	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
120	0.183	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
125	0.189	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
130	0.195	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
135	0.202	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
140	0.208	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
145 150	0.215	0.154 0.154										
150	0.221	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
160	0.234	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
165	0.240	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
170	0.247	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
175	0.253	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
180	0.260	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
185	0.266	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
190	0.273	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
195	0.279	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
200 205	0.286	0.154 0.154	0.154									
210	0.298	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
215	0.305	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
220	0.311	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
225	0.318	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
230	0.324	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
235	0.331	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
240	0.337	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
245	0.343	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
250 255	0.350	0.154 0.154										
260	0.363	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
265	0.369	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
270	0.376	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
275	0.382	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
280	0.388	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
285	0.395	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
290	0.401	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
295	0.408	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
300	0.414	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
305 310	0.421	0.154 0.154	0.154									
310	0.427	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
320	0.444	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
325	0.453	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
330	0.462	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
335	0.472	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 3 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol Agg-



SteelMaster 600WF

-				asiez. I/F36	otion beam	: Fire resist	ance period	. Jo minute	•			
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatur	e of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
35	0.170	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
40	0.211	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
45	0.252	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
50	0.293	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
55	0.334	0.161	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
60	0.374	0.172	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
65	0.415	0.183	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
70	0.489	0.195	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
75	0.582	0.206	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
80 85	0.624	0.217	0.154 0.154	0.154								
90	0.659 0.695	0.229	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
95		0.240	0.154	0.154		0.154	0.154	0.154	0.154	0.154	0.154	0.154
100	0.731 0.766	0.263	0.154	0.154	0.154 0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
105	0.802	0.263	0.160	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
110	0.837	0.274	0.166	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
115	0.873	0.297	0.172	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
120	0.909	0.308	0.172	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
125	0.944	0.319	0.170	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
130	0.980	0.331	0.189	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
135	1.016	0.342	0.195	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
140	1.051	0.354	0.201	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
145	1.087	0.365	0.207	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
150	1.122	0.376	0.213	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
155	1.158	0.388	0.219	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
160	1.194	0.399	0.225	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
165	-	0.410	0.230	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
170	-	0.422	0.236	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
175	-	0.432	0.242	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
180	-	0.438	0.248	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
185	-	0.444	0.254	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
190	-	0.449	0.260	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
195	-	0.455	0.266	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
200	-	0.461	0.272	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
205	-	0.467	0.277	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
210	-	0.473	0.283	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
215		0.479	0.289	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
220	-	0.485	0.295	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
225	-	0.491	0.301	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
230		0.497	0.307	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
235		0.502	0.313	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
240		0.508	0.319	0.161	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
245 250	-	0.514	0.324	0.168	0.154 0.154							
255		0.520	0.330	0.176	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
260	- :	0.532	0.342	0.191	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
265	- :	0.532	0.342	0.191	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
270	- :	0.544	0.354	0.199	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
275	-	0.549	0.360	0.214	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
280	-	0.555	0.366	0.221	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
285	-	0.561	0.371	0.229	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
290	-	0.567	0.377	0.237	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
295	-	0.573	0.383	0.244	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
300	-	0.579	0.389	0.252	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
305	-	0.585	0.395	0.259	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
310	-	0.591	0.401	0.267	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
315	-	0.626	0.407	0.275	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
320	-	0.670	0.413	0.282	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
325	-	0.713	0.418	0.290	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
330	-	0.757	0.424	0.297	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
335		0.800	0.430	0.305	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 4 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol Agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

			T	able3: I/H-Se	ection Beam	: Fire resist	ance period	1: 45 Minute	S			
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatu	re of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	0.345	0.187	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
35	0.423	0.225	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
40	0.616	0.263	0.167	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
45 50	0.709 0.801	0.301	0.181 0.194	0.154 0.154								
55	0.893	0.376	0.208	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
60	0.986	0.414	0.221	0.161	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
65	1.078	0.450	0.235	0.169	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
70	1.170	0.484	0.248	0.177	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
75	-	0.518	0.262	0.184	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
80 85	-	0.551 0.585	0.275 0.289	0.192	0.154 0.154							
90	-	0.627	0.302	0.208	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
95	-	0.671	0.316	0.216	0.160	0.154	0.154	0.154	0.154	0.154	0.154	0.154
100	-	0.714	0.330	0.224	0.166	0.154	0.154	0.154	0.154	0.154	0.154	0.154
105	-	0.758	0.343	0.232	0.172	0.154	0.154	0.154	0.154	0.154	0.154	0.154
110	-	0.802	0.357	0.240	0.178	0.154	0.154	0.154	0.154	0.154	0.154	0.154
115 120	-	0.845 0.889	0.370 0.384	0.248 0.256	0.184 0.190	0.154 0.154						
125	_	0.933	0.397	0.263	0.196	0.154	0.154	0.154	0.154	0.154	0.154	0.154
130	-	0.976	0.411	0.271	0.202	0.154	0.154	0.154	0.154	0.154	0.154	0.154
135	-	1.020	0.424	0.279	0.208	0.155	0.154	0.154	0.154	0.154	0.154	0.154
140	-	1.063	0.436	0.287	0.213	0.161	0.154	0.154	0.154	0.154	0.154	0.154
145	-	1.107	0.446	0.295	0.219	0.166	0.154	0.154	0.154	0.154	0.154	0.154
150 155	-	1.151 1.194	0.457 0.467	0.303	0.225 0.231	0.172 0.178	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154
160	-	1.194	0.467	0.311	0.237	0.178	0.154	0.154	0.154	0.154	0.154	0.154
165	-	-	0.488	0.327	0.243	0.189	0.154	0.154	0.154	0.154	0.154	0.154
170	-	-	0.498	0.335	0.249	0.194	0.154	0.154	0.154	0.154	0.154	0.154
175	-	-	0.508	0.342	0.255	0.200	0.154	0.154	0.154	0.154	0.154	0.154
180	-	-	0.519	0.350	0.261	0.206	0.154	0.154	0.154	0.154	0.154	0.154
185	-	-	0.529	0.358	0.267	0.211	0.154	0.154	0.154	0.154	0.154	0.154
190 195	-	-	0.539 0.550	0.366 0.374	0.273 0.279	0.217 0.223	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154
200	-	-	0.560	0.374	0.279	0.228	0.154	0.154	0.154	0.154	0.154	0.154
205	-	-	0.570	0.390	0.291	0.234	0.154	0.154	0.154	0.154	0.154	0.154
210	-	-	0.581	0.398	0.296	0.240	0.154	0.154	0.154	0.154	0.154	0.154
215	-	-	0.591	0.406	0.302	0.245	0.154	0.154	0.154	0.154	0.154	0.154
220	-	-	0.612	0.413	0.308	0.251	0.154	0.154	0.154	0.154	0.154	0.154
225	-	-	0.635 0.657	0.421	0.314	0.257 0.262	0.154 0.154	0.154 0.154	0.154	0.154	0.154 0.154	0.154 0.154
235	-	-	0.679	0.429	0.320 0.326	0.262	0.154	0.154	0.154 0.154	0.154 0.154	0.154	0.154
240	-	-	0.702	0.445	0.332	0.274	0.154	0.154	0.154	0.154	0.154	0.154
245	-	-	0.724	0.453	0.338	0.279	0.154	0.154	0.154	0.154	0.154	0.154
250	-	-	0.747	0.461	0.344	0.285	0.154	0.154	0.154	0.154	0.154	0.154
255	-	-	0.769	0.469	0.350	0.291	0.154	0.154	0.154	0.154	0.154	0.154
260	-	-	0.792	0.477	0.356	0.296	0.154	0.154	0.154	0.154	0.154	0.154
265 270	-	-	0.814 0.836	0.485 0.493	0.362 0.368	0.302 0.307	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154
275	-	-	0.859	0.493	0.374	0.307	0.154	0.154	0.154	0.154	0.154	0.154
280	-	-	0.881	0.509	0.379	0.319	0.154	0.154	0.154	0.154	0.154	0.154
285	-	-	0.904	0.517	0.385	0.324	0.154	0.154	0.154	0.154	0.154	0.154
290	-	-	0.926	0.525	0.391	0.330	0.154	0.154	0.154	0.154	0.154	0.154
295	-	-	0.948	0.533	0.397	0.336	0.154	0.154	0.154	0.154	0.154	0.154
300	-	-	0.971	0.541	0.403	0.341	0.154	0.154	0.154	0.154	0.154	0.154
305 310	-	-	0.993 1.016	0.549 0.557	0.409 0.415	0.347 0.353	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154
315	-	-	1.016	0.565	0.415	0.358	0.165	0.154	0.154	0.154	0.154	0.154
320	-	-	1.061	0.573	0.427	0.364	0.176	0.154	0.154	0.154	0.154	0.154
325	-	-	1.083	0.581	0.435	0.370	0.186	0.154	0.154	0.154	0.154	0.154
330	-	-	1.105	0.589	0.448	0.375	0.197	0.154	0.154	0.154	0.154	0.154
335	l -		1.128	0.617	0.460	0.381	0.207	0.164	0.154	0.154	0.154	0.154

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 5 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

				a	JULION DE ANI	: Fire resist	per 100	Jo minute				
Section Factor up to m ⁻¹				Thic	kness (m m	ı) Required f	or a Design	Temperatu	re of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	-	0.344	0.230	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
35		0.405	0.265	0.180	0.154	0.154	0.154	0.154	0.154	0.154	0.154	0.154
40	-	0.515	0.299	0.198	0.162	0.154	0.154	0.154	0.154	0.154	0.154	0.154
45	-	0.635	0.334	0.215	0.172	0.154	0.154	0.154	0.154	0.154	0.154	0.154
50	-	0.727	0.368	0.232	0.181	0.154	0.154	0.154	0.154	0.154	0.154	0.154
55	-	0.819	0.403	0.249	0.191	0.154	0.154	0.154	0.154	0.154	0.154	0.154
60	-	0.911	0.435	0.267	0.201	0.158	0.154	0.154	0.154	0.154	0.154	0.154
65	-	1.003	0.459	0.284	0.210	0.166	0.154	0.154	0.154	0.154	0.154	0.154
70	-	1.095	0.483	0.301	0.220	0.173	0.154	0.154	0.154	0.154	0.154	0.154
75 80	-	1.187	0.507 0.532	0.319 0.336	0.229	0.181 0.188	0.154 0.154	0.154 0.154	0.154 0.154	0.154	0.154 0.154	0.154 0.154
85	-		0.556	0.353	0.239	0.188	0.154	0.154	0.154	0.154	0.154	0.154
90	-		0.580	0.353	0.258	0.196	0.160	0.154	0.154	0.154	0.154	0.154
95	-		0.608	0.371	0.268	0.203	0.166	0.154	0.154	0.154	0.154	0.154
100	-	-	0.608	0.388	0.268	0.211	0.166	0.154	0.154	0.154	0.154	0.154
105	-	-	0.674	0.403	0.217	0.219	0.172	0.165	0.154	0.154	0.154	0.154
110	-		0.707	0.422	0.296	0.234	0.178	0.103	0.154	0.154	0.154	0.154
115	-		0.740	0.450	0.296	0.234	0.189	0.177	0.157	0.154	0.154	0.154
120	-	-	0.773	0.462	0.315	0.249	0.195	0.183	0.163	0.154	0.154	0.154
125	-	-	0.806	0.475	0.325	0.256	0.201	0.188	0.168	0.154	0.154	0.154
130	-	-	0.839	0.487	0.335	0.264	0.207	0.194	0.174	0.154	0.154	0.154
135	-	-	0.872	0.500	0.344	0.271	0.213	0.200	0.179	0.154	0.154	0.154
140	-	-	0.905	0.512	0.354	0.279	0.219	0.205	0.185	0.154	0.154	0.154
145	-	-	0.938	0.525	0.363	0.286	0.225	0.211	0.190	0.154	0.154	0.154
150	-	-	0.971	0.537	0.373	0.294	0.231	0.217	0.196	0.154	0.154	0.154
155	-	-	1.004	0.550	0.382	0.302	0.237	0.223	0.201	0.154	0.154	0.154
160		-	1.037	0.563	0.392	0.309	0.243	0.228	0.207	0.154	0.154	0.154
165	-	-	1.070	0.575	0.402	0.317	0.249	0.234	0.212	0.154	0.154	0.154
170	-	-	1.103	0.588	0.411	0.324	0.255	0.240	0.217	0.154	0.154	0.154
175	-	-	1.135	0.608	0.421	0.332	0.260	0.246	0.223	0.154	0.154	0.154
180	=	-	1.168	0.632	0.430	0.339	0.266	0.251	0.228	0.154	0.154	0.154
185	=	-	1.201	0.656	0.442	0.347	0.272	0.257	0.234	0.154	0.154	0.154
190	,	1	-	0.680	0.453	0.354	0.278	0.263	0.239	0.154	0.154	0.154
195	-	-	-	0.704	0.465	0.362	0.284	0.269	0.245	0.154	0.154	0.154
200	-	-	-	0.728	0.477	0.369	0.290	0.274	0.250	0.154	0.154	0.154
205	-	-	-	0.752	0.488	0.377	0.296	0.280	0.256	0.154	0.154	0.154
210	-	-	-	0.776	0.500	0.384	0.302	0.286	0.261	0.154	0.154	0.154
215	-	-	-	0.801	0.511	0.392	0.308	0.291	0.266	0.154	0.154	0.154
220	-	-	-	0.825	0.523	0.400	0.314	0.297	0.272	0.154	0.154	0.154
225	-	-	-	0.849	0.534	0.407	0.320	0.303	0.277	0.154	0.154	0.154
230	-	-	-	0.873	0.546	0.415	0.326	0.309	0.283	0.154	0.154	0.154
235	-	-	-	0.897	0.558	0.422	0.332	0.314	0.288	0.154	0.154	0.154
240	-	-	-	0.921	0.569	0.430	0.337	0.320	0.294	0.154	0.154	0.154
245	-	-	-	0.945	0.581	0.439	0.343	0.326	0.299	0.154	0.154	0.154
250	-	-	-	0.969	0.593	0.448	0.349	0.332	0.305	0.154	0.154	0.154
255	-	-	-	0.993	0.620	0.458	0.355	0.337	0.310	0.154	0.154	0.154
260	-	-	-	1.017	0.646	0.467	0.361	0.343	0.316	0.154	0.154	0.154
265	-	-	-	1.041	0.673	0.476	0.367	0.349	0.321	0.154	0.154	0.154
270	-	-	-	1.066	0.700	0.486	0.373	0.355	0.326	0.154	0.154	0.154
275 280	-	-	- -	1.090	0.726 0.753	0.495 0.504	0.379	0.360 0.366	0.332	0.154 0.154	0.154 0.154	0.154
280	-	-	- -	1.114	0.753	0.504	0.385	0.366	0.337	0.154	0.154	0.154
285	-	-	- -	1.138	0.779	0.514	0.391	0.372	0.343	0.154	0.154	0.154
290	-	-	-	1.162	0.806	0.523	0.397	0.378	0.348	0.154	0.154	0.154
300	-	-	-	1.186	0.833	0.532	0.403	0.383	0.354	0.154	0.154	0.154
305	-	-	-	1.210	0.859	0.542	0.408	0.389	0.359	0.154	0.154	0.154
310	-		-	-	0.886	0.560	0.414	0.395	0.365	0.158	0.154	0.154
315	-		-	-	0.939	0.570	0.426	0.406	0.376	0.170	0.154	0.154
320	-		-	-	0.966	0.579	0.426	0.406	0.376	0.102	0.154	0.154
325					0.992	0.579	0.455	0.412	0.386	0.194	0.154	0.154
330	-		_	-	1.019	0.616	0.467	0.413	0.392	0.219	0.154	0.154
335	-		-	-	1.046	0.654	0.484	0.429		0.213	0.154	0.154
335	-				1.046	U.004	0.484	0.429	0.397	0.231	0.154	0.1

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 6 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol Agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

				ables: I/H-Se	ection Beam	: Fire resist	ance period	1: 75 Minute	·S			
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatu	re of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	-	-	0.348	0.263	0.186	0.154	0.154	0.154	0.154	0.154	0.154	0.154
35	-	-	0.402	0.298	0.208	0.173	0.154	0.154	0.154	0.154	0.154	0.154
40	-	-	0.468	0.332	0.231	0.184	0.157	0.154	0.154	0.154	0.154	0.154
45 50	-	-	0.546 0.622	0.366	0.253 0.276	0.195 0.206	0.167 0.176	0.154 0.161	0.154 0.154	0.154 0.154	0.154 0.154	0.154 0.154
55	-		0.622	0.400	0.276	0.206	0.176	0.169	0.154	0.154	0.154	0.154
60			0.764	0.456	0.230	0.217	0.194	0.109	0.154	0.154	0.154	0.154
65	-	-	0.836	0.479	0.344	0.239	0.203	0.186	0.154	0.154	0.154	0.154
70	-	-	0.907	0.502	0.366	0.251	0.212	0.195	0.157	0.154	0.154	0.154
75	-	-	0.979	0.526	0.389	0.262	0.222	0.203	0.165	0.154	0.154	0.154
80	-	-	1.050	0.549	0.411	0.273	0.231	0.212	0.173	0.154	0.154	0.154
85	-	-	1.122	0.572	0.433	0.284	0.240	0.220	0.181	0.154	0.154	0.154
90	-	-	1.193	0.596	0.447	0.295	0.249	0.229	0.189	0.156	0.154	0.154
95	-	-	-	0.630	0.461	0.306	0.258	0.238	0.196	0.162	0.154	0.154
100 105	-		-	0.665	0.475 0.489	0.318	0.267	0.246 0.255	0.204	0.168 0.174	0.154 0.154	0.154 0.154
105	-		-	0.699	0.489	0.329	0.277	0.255	0.212	0.174	0.154	0.154
115	-		-	0.767	0.503	0.340	0.295	0.263	0.228	0.186	0.154	0.154
120		-		0.801	0.517	0.362	0.304	0.272	0.235	0.192	0.165	0.154
125	-	-	-	0.835	0.545	0.373	0.313	0.289	0.243	0.198	0.170	0.154
130	-	-	-	0.869	0.559	0.384	0.323	0.297	0.251	0.204	0.176	0.154
135	-	-	-	0.904	0.573	0.396	0.332	0.306	0.259	0.210	0.181	0.154
140	-	-	-	0.938	0.587	0.407	0.341	0.314	0.267	0.216	0.187	0.154
145	-	-	-	0.972	0.613	0.418	0.350	0.323	0.274	0.222	0.192	0.154
150	-	-	-	1.006	0.644	0.429	0.359	0.332	0.282	0.228	0.198	0.154
155	-	-	-	1.040	0.675	0.447	0.368	0.340	0.290	0.234	0.203	0.154
160	-	-	-	1.074	0.706	0.467	0.378	0.349	0.298	0.240 0.246	0.209	0.154 0.154
165 170			-	1.108 1.142	0.737 0.768	0.487 0.507	0.387	0.357 0.366	0.306 0.314	0.246	0.214 0.220	0.154
175	-			1.177	0.799	0.526	0.405	0.374	0.321	0.258	0.225	0.154
180	-	-	-	1.211	0.830	0.546	0.414	0.383	0.329	0.264	0.231	0.154
185	-	-	-	-	0.861	0.566	0.423	0.391	0.337	0.270	0.236	0.154
190	-	-	-	-	0.892	0.585	0.433	0.400	0.345	0.276	0.242	0.154
195	-	-	-	-	0.923	0.606	0.446	0.409	0.353	0.282	0.247	0.154
200	-	-	-	-	0.954	0.628	0.459	0.417	0.360	0.288	0.252	0.154
205	-	-	-	-	0.985	0.649	0.472	0.426	0.368	0.294	0.258	0.154
210	-	-	-	-	1.016	0.671	0.485	0.435	0.376	0.300	0.263	0.154
215 220	-		-	-	1.047	0.692 0.713	0.498	0.446 0.457	0.384	0.306 0.312	0.269 0.274	0.154 0.154
225			-	-	1.109	0.713	0.523	0.457	0.392	0.312	0.274	0.154
230					1.140	0.756	0.536	0.479	0.399	0.314	0.285	0.154
235	-	-	-	-	1.171	0.778	0.549	0.490	0.415	0.330	0.291	0.154
240		-			1.202	0.799	0.562	0.501	0.423	0.336	0.296	0.154
245	-	-	-	-	-	0.821	0.575	0.511	0.431	0.342	0.302	0.154
250	-	-	-	-	-	0.842	0.588	0.522	0.442	0.348	0.307	0.154
255	-	-	-	-	-	0.863	0.610	0.533	0.453	0.354	0.313	0.154
260	-	-	-	-	-	0.885	0.637	0.544	0.464	0.360	0.318	0.154
265	-		-	-	-	0.906	0.665	0.555	0.475	0.366	0.324	0.154
270 275			-	-	-	0.928	0.692	0.566	0.486	0.372	0.329	0.154 0.154
280			-	-	-	0.949	0.719	0.577	0.497	0.376	0.335	0.154
285	-	-	-	-	-	0.992	0.773	0.613	0.519	0.390	0.346	0.154
290	-	-	-	-	-	1.013	0.800	0.646	0.530	0.396	0.351	0.154
295	-	-	-	-	-	1.035	0.827	0.680	0.541	0.402	0.357	0.154
300	-	-	-	-	-	1.056	0.854	0.713	0.552	0.408	0.362	0.154
305	-	-	-	-	-	1.078	0.882	0.746	0.563	0.414	0.368	0.166
310	-	-	-	-	-	1.099	0.909	0.780	0.574	0.420	0.373	0.179
315	-	-	-	-	-	1.121	0.936	0.813	0.585	0.426	0.379	0.192
320	-	-	-	-	-	1.142	0.963	0.846	0.608	0.437	0.384	0.205
325	-	-	-	-	-	1.164 1.185	0.990 1.017	0.880	0.651 0.695	0.465 0.492	0.390 0.395	0.217
330												

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 7 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

Continu			-	Table6: I/H-Se	ection Beam	: Fire resist	ance period	a: 90 Winute	s			
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatu	re of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	-	-	-	0.365	0.294	0.237	0.178	0.168	0.154	0.154	0.154	0.154
35		,	-	0.415	0.330	0.262	0.195	0.182	0.167	0.154	0.154	0.154
40	-	-	-	0.478	0.366	0.287	0.213	0.197	0.178	0.154	0.154	0.154
45		-		0.545	0.402	0.312	0.231	0.211	0.189	0.154	0.154	0.154
50	-	-	-	0.615	0.436	0.338	0.249	0.226	0.200	0.157	0.154	0.15
55	-	-	-	0.689	0.464	0.363	0.267	0.240	0.210	0.167	0.154	0.15
60	-	-	-	0.763	0.492	0.388	0.284	0.254	0.221	0.177	0.154	0.15
65	-	-	-	0.837	0.519	0.413	0.302	0.269	0.232	0.187	0.154	0.15
70	-	-	-	0.911	0.547	0.437	0.320	0.283	0.243	0.196	0.154	0.15
75	-	-	-	0.985	0.575	0.459	0.338	0.298	0.254	0.206	0.154	0.15
80	-	-	-	1.059	0.608	0.480	0.355	0.312	0.265	0.216	0.155	0.15
85	-	-	-	1.133	0.648	0.501	0.373	0.326	0.276	0.226	0.164	0.15
90		-	-	1.207	0.689	0.523	0.391	0.341	0.287	0.235	0.172	0.154
95		-	-	-	0.730	0.544	0.409	0.355	0.298	0.245	0.180	0.15
100 105		-	- -	-	0.771 0.812	0.566 0.587	0.427	0.370 0.384	0.309	0.255 0.264	0.188 0.197	0.16
110	-	-	-		0.853	0.567	0.442	0.398	0.330	0.204	0.197	0.17
115	-	-	-	-	0.894	0.649	0.457	0.396	0.330	0.274	0.203	0.17
120	-	-	-	-	0.935	0.681	0.486	0.427	0.352	0.294	0.222	0.18
125	-	-	-	-	0.976	0.713	0.501	0.444	0.363	0.303	0.230	0.19
130	-	-	-	-	1.017	0.745	0.516	0.463	0.374	0.313	0.238	0.20
135	-	-	-	-	1.058	0.777	0.531	0.481	0.385	0.323	0.247	0.20
140	-	-	-	-	1.099	0.809	0.545	0.499	0.396	0.333	0.255	0.21
145	-	-	-	-	1.140	0.841	0.560	0.517	0.407	0.342	0.263	0.21
150	-	-	-	-	1.181	0.873	0.575	0.535	0.418	0.352	0.271	0.22
155	-	-	-	-	-	0.905	0.590	0.553	0.429	0.362	0.280	0.23
160	-	-	-	-	-	0.937	0.620	0.571	0.454	0.372	0.288	0.238
165	-	-	-	-	-	0.969	0.653	0.589	0.482	0.381	0.296	0.24
170	-	-	-	-	-	1.001	0.686	0.615	0.510	0.391	0.305	0.25
175		,	-	-	-	1.033	0.719	0.643	0.539	0.401	0.313	0.25
180	-	-	-	-	-	1.065	0.752	0.670	0.567	0.411	0.321	0.26
185	-	-	-	-	-	1.097	0.785	0.697	0.595	0.420	0.329	0.26
190	-	-	-	-	-	1.129	0.818	0.725	0.616	0.430	0.338	0.27
195	-	-	-	-	-	1.162	0.851	0.752	0.638	0.452	0.346	0.28
200	-	-	-	-	-	1.194	0.884	0.780	0.659	0.475	0.354	0.28
205	-	-	-	-	-	-	0.917	0.807	0.680	0.498	0.363	0.29
210	-	-	-	-	-	-	0.950	0.835	0.702	0.520	0.371	0.299
215	-	-	-	-	-	-	0.983	0.862	0.723	0.543	0.379	0.30
220	-	-	-	-	-	-	1.016	0.890	0.745	0.566	0.388	0.31
225	-	-	-	-	-	-	1.049	0.917	0.766	0.589	0.396	0.31
230	-	-	-	-	-	-	1.081	0.944	0.788	0.613	0.404	0.32
235	-	-	-	-	-	-	1.114	0.972	0.809	0.636	0.412	0.330
240	-	-	-	-	-	-	1.147	0.999	0.831	0.660	0.421	0.336
245 250	-	-	-	-	-	-	1.180 1.213	1.027 1.054	0.852 0.873	0.684 0.708	0.429 0.447	0.34
255		-		-	-	-	1.213	1.054	0.873	0.708	0.447	0.34
260	-	-	-		-	-	-	1.082	0.895	0.732	0.488	0.35
265	-	-	-	-	-	-	-	1.137	0.916	0.780	0.508	0.36
270								1.164	0.959	0.804	0.528	0.37
275		-	_	_		-	-	1.191	0.981	0.828	0.549	0.37
280	-	-	-	-	-	-	-	-	1.002	0.852	0.569	0.38
285	-	-	-	-	-	-	-	-	1.024	0.875	0.589	0.39
290	-	-	-	-	-	-	-	-	1.045	0.899	0.621	0.39
295	-	-	-	-	-	-	-	-	1.066	0.923	0.655	0.40
300	-	-	-	-	-	-	-	-	1.088	0.947	0.689	0.40
305	-	-	-	-	-	-	-	-	1.109	0.971	0.723	0.41
310	-	-	-	-	-	-	-	-	1.131	0.995	0.757	0.42
315	-	-	-	-	-	-	-	-	1.152	1.019	0.790	0.42
320	-	0	-	-	-	-	-	-	1.174	1.043	0.824	0.49
325	-	-	-	-	-	-	-		1.195	1.067	0.858	0.60
330	-	-	-	-	-	-	-	-	0.154	1.091	0.892	0.639
335	-	-	-	-	-	-	-	-	0.154	1.114	0.926	0.67

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 8 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

Section						: Fire resist						
Factor up				Thic	kness (mm) Required f	or a Design	Temperatu	re of			
10111	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30		-	400 C	430 C	0.384	0.319	0.264	0.244	0.214	0.167	0.154	0.154
35	-	-	-	-	0.439	0.358	0.294	0.270	0.236	0.184	0.154	0.154
40	-	-	-	-	0.523	0.397	0.323	0.296	0.259	0.200	0.155	0.154
45	-	-	-	-	0.609	0.437	0.353	0.323	0.281	0.217	0.167	0.154
50		-	-	-	0.699	0.484	0.382	0.349	0.303	0.233	0.180	0.154
55	-	-	-	-	0.789	0.531	0.412	0.375	0.325	0.250	0.193	0.154
60	-	-	-	-	0.879	0.578	0.443	0.402	0.347	0.266	0.206	0.154
65	-	-	-	-	0.969	0.635	0.477	0.428	0.369	0.282	0.219	0.154
70 75	-	-		-	1.059 1.149	0.697 0.759	0.511 0.546	0.461	0.392 0.414	0.299 0.315	0.232 0.245	0.163
80		-		-	1.149	0.759	0.580	0.527	0.414	0.332	0.245	0.176
85		-		-	-	0.883	0.617	0.560	0.471	0.348	0.271	0.202
90	-	-		_	-	0.946	0.656	0.593	0.504	0.364	0.283	0.215
95	-	-	-	-	-	1.008	0.695	0.628	0.537	0.381	0.296	0.228
100	-	-	-	-	-	1.070	0.735	0.664	0.570	0.397	0.309	0.241
105	-	-	-	-	-	1.132	0.774	0.699	0.603	0.414	0.322	0.254
110	-	-	-	-	-	1.194	0.813	0.735	0.636	0.430	0.335	0.267
115	-	-	-	-	-	-	0.853	0.770	0.669	0.463	0.348	0.280
120	-	-	-	-	-	-	0.892	0.806	0.702	0.497	0.361	0.293
125	-	-	-	-	-	-	0.931	0.841	0.735	0.530	0.374	0.306
130	-	-	-	-	-	-	0.970	0.877	0.768	0.564	0.386	0.319
135 140	-	-	-	-	-	-	1.010	0.912	0.801 0.834	0.597 0.626	0.399 0.412	0.332
145					-	-	1.049	0.983	0.867	0.655	0.425	0.358
150			-	_		-	1.127	1.019	0.900	0.684	0.462	0.371
155	-	-	-	-	-	-	1.167	1.054	0.933	0.713	0.518	0.384
160	-	-	-	-	-	-	1.206	1.090	0.966	0.742	0.574	0.397
165	-	-	-	-	-	-	-	1.125	0.999	0.771	0.607	0.410
170	-	-		-	-	-		1.161	1.032	0.800	0.628	0.423
175		-	-	-	-	=	-	1.196	1.065	0.829	0.650	0.455
180	-	-	-	-	-	-	-	-	1.098	0.858	0.671	0.514
185	-	-	-	-	-	-	-	-	1.131	0.887	0.693	0.573
190	-	-	-	-	-	-	-	-	1.164	0.916	0.715	0.605
195 200	-	-	-	-	-	-	-	-	1.197	0.945 0.974	0.736 0.758	0.624
205	-	-		-	-	-			-	1.003	0.758	0.663
210	-	-	-	-	-	-	-	-	-	1.032	0.801	0.682
215	-	-		-	-	-	-		-	1.061	0.823	0.701
220	-	-	-	-	-	-			-	1.090	0.844	0.720
225	-	-	-	-	-	-			-	1.119	0.866	0.740
230	-	-		-	-	-			-	1.148	0.887	0.759
235	-	-	-	-	-	-	-	-	-	1.177	0.909	0.778
240	-	-	-	-	-	-	-	-	-	1.206	0.931	0.797
245	-	-	-	-	-	-	-	-	-	-	0.952	0.817
250	-	-	-	-	-	-	-	-	-	-	0.974	0.836
255 260	-	-		-	-	-	-	-	-	-	0.995	0.855
260 265	-	-		-	-	-	-		-	-	1.017	0.874
270	-	-					-	-		-	1.039	0.894
275	-	-	-		-	-	-	-	-	-	1.082	0.932
280	-	-	-	-	-	-	-	-	-	-	1.103	0.952
285	-	-	-	-	-	-	-	-	-	-	1.125	0.971
290	-	-	-	-	-	-			-	-	1.146	0.990
295	-	-	-	-	-	-	-	-	-	-	1.168	1.009
300	-	-	-	-	-	-	-	-	-	-	1.190	1.029
305	-	-	-	-	-	-	-	-	-	-	1.211	1.048
310	-	-		-	-	-		-	-	-	-	1.067
315	-	-	-	-	-	-	-	-	-	-	-	1.086
320	-	-	-	-	-	-	-	-	-	-	-	1.106
325	-	-	-	-	-	-	-	-	-	-	-	1.125
330 335	-	-	-	-	-	-		-	-		-	1.144

Thickness is intumescent only. Results apply to I/H-section beams with concrete slabs with 3 sided fire exposure.

Page 9 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

				Та	ble8: I/H-Co	olumn Section	ns 15 Minut	es				
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatur	e of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30 35	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
35 40	0.141 0.141	0.141										
45	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
50	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
55	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
60 65	0.141 0.141	0.141										
70	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
75	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
80	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
85	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
90 95	0.141 0.141											
100	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
105	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
110	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
115	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
120 125	0.141 0.141	0.141										
130	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
135	0.150	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
140	0.156	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
145	0.162	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
150 155	0.168 0.174	0.141 0.141										
160	0.180	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
165	0.185	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
170	0.191	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
175 180	0.197 0.203	0.141 0.141	0.141									
185	0.203	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
190	0.215	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
195	0.221	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
200	0.226	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
205 210	0.232 0.238	0.141 0.141	0.141									
215	0.244	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
220	0.250	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
225	0.256	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
230 235	0.261	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
240	0.267 0.273	0.141 0.141	0.141									
245	0.279	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
250	0.285	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
255	0.291	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
260	0.297	0.141	0.141	0.141 0.141	0.141	0.141	0.141	0.141 0.141	0.141	0.141	0.141	0.141
265 270	0.302	0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
275	0.314	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
280	0.320	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
285	0.326	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
290 295	0.332 0.338	0.141 0.141										
300	0.343	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
305	0.349	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
310	0.355	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
315	0.361	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
320 325	0.367 0.373	0.141 0.141										
325	0.373	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
335	0.384	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
340	0.390	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
345	0.396	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
350 355	0.402	0.141	0.141 0.141	0.141								
360	0.408	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
365	0.419	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
370	0.440	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 10 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

				ıa	ble9: 1/ n-C0	olumn Sectio	iis 30 Miliut	C3				
Section Factor up to m ⁻¹				Thic	kness (mm) Required fo	or a Design	Temperatui	e of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
35	0.150	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
40 45	0.195 0.241	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
50	0.241	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
55	0.332	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
60	0.378	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
65	0.423	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
70	0.436	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
75	0.449	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
80	0.462	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
85 90	0.476 0.489	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141
95	0.502	0.142	0.141	0.141	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141	0.141	0.141
100	0.515	0.169	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
105	0.528	0.183	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
110	0.541	0.197	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
115	0.554	0.210	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
120	0.567	0.224	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
125	0.580	0.237	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
130 135	0.593 0.606	0.251 0.264	0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
135 140	0.606	0.264	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
145	0.633	0.278	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
150	0.646	0.305	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
155	0.659	0.319	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
160	0.672	0.332	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
165	0.685	0.346	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
170	0.698	0.360	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
175	-	0.373	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
180	-	0.387	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
185 190		0.400 0.414	0.148	0.141	0.141 0.141	0.141 0.141	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141
195	-	0.414	0.162	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
200	-	0.437	0.170	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
205	-	0.447	0.177	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
210	-	0.458	0.184	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
215	-	0.468	0.192	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
220	-	0.479	0.199	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
225	-	0.489	0.206	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
230	-	0.499	0.214	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
235 240	-	0.510 0.520	0.221	0.141 0.141	0.141							
245	-	0.520	0.236	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
250	-	0.541	0.243	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
255	-	0.551	0.250	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
260	-	0.562	0.257	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
265	-	0.572	0.265	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
270	-	0.583	0.272	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
275	-	0.593	0.279	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
280 285		0.604	0.287 0.294	0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141	0.141	0.141 0.141	0.141
285	-	0.614 0.624	0.294	0.141	0.141 0.141	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141	0.141
295	-	0.635	0.301	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
300	-	0.645	0.316	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
305		0.656	0.323	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
310	-	0.666	0.331	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
315		0.677	0.338	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
320	-	0.687	0.345	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
325	-	0.697	0.353	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
330 335	-	-	0.360	0.141	0.141 0.141	0.141						
335 340	-	-	0.367	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
345	-	-	0.373	0.151	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
350	-	-	0.389	0.166	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
355	-	-	0.397	0.180	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
360	-	-	0.404	0.195	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
365	-	-	0.411	0.210	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
370	-	-	0.419	0.224	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 11 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

Section Factor up					-	olumn Section			e of			
to m ⁻¹	20000	25000	40000	45000	E000C	FFOOC	connc	62006	CEOOC	70000	75000	00000
30	300°C 0.333	350°C 0.192	400°C 0.141	450°C 0.141	500°C 0.141	550°C 0.141	600°C 0.141	620°C 0.141	650°C 0.141	700°C 0.141	750°C 0.141	800°C 0.141
35	0.367	0.132	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
40	0.483	0.264	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
45	0.552	0.299	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
50	0.620	0.335	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
55	0.689	0.370	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
60	-	0.406	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
65	-	0.429	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
70 75		0.439 0.450	0.141	0.141 0.141	0.141	0.141 0.141	0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141
80		0.461	0.156	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
85	-	0.472	0.179	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
90	-	0.483	0.201	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
95	-	0.494	0.223	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
100	-	0.505	0.246	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
105	-	0.516	0.268	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
110	-	0.526	0.290	0.143	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
115	-	0.537	0.313	0.153	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
120	-	0.548	0.335	0.163	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
125 130		0.559 0.570	0.358	0.173 0.183	0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
135				0.183			0.141			0.141		
140		0.581	0.402 0.424	0.193	0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141	0.141 0.141	0.141
145		0.603	0.435	0.203	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
150	-	0.613	0.445	0.222	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
155	-	0.624	0,456	0.232	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
160	-	0.635	0.467	0.242	0.142	0.141	0.141	0.141	0.141	0.141	0.141	0.141
165	-	0.646	0.478	0.252	0.151	0.141	0.141	0.141	0.141	0.141	0.141	0.141
170	-	0.657	0.488	0.262	0.160	0.141	0.141	0.141	0.141	0.141	0.141	0.141
175	-	0.668	0.499	0.272	0.169	0.141	0.141	0.141	0.141	0.141	0.141	0.141
180	-	0.679	0.510	0.282	0.177	0.141	0.141	0.141	0.141	0.141	0.141	0.141
185	-	0.690	0.521	0.292	0.186	0.141	0.141	0.141	0.141	0.141	0.141	0.141
190	-	0.700	0.531	0.302	0.195	0.141	0.141	0.141	0.141	0.141	0.141	0.141
195 200	-	-	0.542 0.553	0.311	0.204	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
205			0.564	0.321	0.213	0.141	0.141	0.141	0.141	0.141	0.141	0.141
210			0.574	0.331	0.230	0.141	0.141	0.141	0.141	0.141	0.141	0.141
215	-	-	0.585	0.351	0.239	0.141	0.141	0.141	0.141	0.141	0.141	0.141
220	-	-	0.596	0.361	0.248	0.141	0.141	0.141	0.141	0.141	0.141	0.141
225	-	-	0.607	0.371	0.257	0.141	0.141	0.141	0.141	0.141	0.141	0.141
230	-	-	0.617	0.381	0.266	0.141	0.141	0.141	0.141	0.141	0.141	0.141
235	-		0.628	0.391	0.274	0.141	0.141	0.141	0.141	0.141	0.141	0.141
240	-	-	0.639	0.400	0.283	0.141	0.141	0.141	0.141	0.141	0.141	0.141
245	-	-	0.650	0.410	0.292	0.146	0.141	0.141	0.141	0.141	0.141	0.141
250	-	-	0.660	0.420	0.301	0.157	0.141	0.141	0.141	0.141	0.141	0.141
255		-	0.671	0.438 0.459	0.310	0.168	0.141	0.141	0.141	0.141	0.141	0.141
260 265	-	-	0.682	0.479	0.319	0.179	0.141	0.141	0.141	0.141 0.141	0.141 0.141	0.141
270	-	-	0.703	0.500	0.327	0.202	0.141	0.141	0.141	0.141	0.141	0.141
275	-	-	-	0.521	0.345	0.213	0.141	0.141	0.141	0.141	0.141	0.141
280	-			0.542	0.354	0.224	0.141	0.141	0.141	0.141	0.141	0.141
285	_	-	-	0.563	0.363	0.235	0.141	0.141	0.141	0.141	0.141	0.141
290			-	0.583	0.372	0.246	0.141	0.141	0.141	0.141	0.141	0.141
295	-	-	-	0.604	0.380	0.258	0.141	0.141	0.141	0.141	0.141	0.141
300	-	-	-	0.625	0.389	0.269	0.141	0.141	0.141	0.141	0.141	0.141
305	-	-	-	0.646	0.398	0.280	0.141	0.141	0.141	0.141	0.141	0.141
310 315		-	-	0.666 0.687	0.407 0.416	0.291 0.302	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
320			-	0.687	0.416	0.302	0.141	0.141	0.141	0.141	0.141	0.141
325		-	-	0.706	0.560	0.313	0.141	0.141	0.141	0.141	0.141	0.141
330	-	-	-	-	0.677	0.325	0.141	0.141	0.141	0.141	0.141	0.141
335	-	-	-	-		0.347	0.141	0.141	0.141	0.141	0.141	0.141
340	-	-	-	-	-	0.358	0.141	0.141	0.141	0.141	0.141	0.141
345	-	-	-	-	-	0.369	0.141	0.141	0.141	0.141	0.141	0.141
350		-	-	-		0.381	0.141	0.141	0.141	0.141	0.141	0.141
355	-	-	-	-	-	0.423	0.154	0.141	0.141	0.141	0.141	0.141
360	-	-	-	-	-	0.445	0.175	0.141	0.141	0.141	0.141	0.141
365	-	-	-	-	-	0.471	0.196	0.141	0.141	0.141	0.141	0.141
370	-	-	-	-	-	0.498	0.217	0.141	0.141	0.141	0.141	0.141

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 12 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

				Tal	ole11: I/H-C	olumn Secti	ons 60 Minu	tes				
Section Factor up to m ⁻¹				Thic	kness (mm) Required f	or a Design	Temperatur	e of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	-	0.277	0.230	0.152	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
35		0.361	0.264	0.171	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
40	-	0.445	0.298	0.190	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
45	-	0.486	0.332	0.209	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
50	-	0.526	0.366	0.228	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
55	-	0.567	0.400	0.247	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
60 65	-	0.607 0.648	0.427 0.438	0.265 0.284	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141 0.141	0.141
70	-	0.688	0.448	0.303	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
75	-	-	0.459	0.322	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
80	-	-	0.470	0.341	0.141	0.141	0.141	0.141	0.141	0.141	0.141	0.141
85	-	-	0.481	0.360	0.144	0.144	0.141	0.141	0.141	0.141	0.141	0.141
90	-	-	0.492	0.378	0.154	0.153	0.141	0.141	0.141	0.141	0.141	0.141
95	-	-	0.503	0.397	0.166	0.161	0.141	0.141	0.141	0.141	0.141	0.141
100	-	-	0.513	0.416	0.178	0.170	0.141	0.141	0.141	0.141	0.141	0.141
105			0.524	0.430	0.189	0.178	0.141	0.141	0.141	0.141	0.141	0.141
110	-		0.535	0.440	0.201	0.187	0.141	0.141	0.141	0.141	0.141	0.141
115			0.546	0.450	0.212	0.195	0.141	0.141	0.141	0.141	0.141	0.141
120		-	0.557	0.460	0.224	0.203	0.141	0.141	0.141	0.141	0.141	0.141
125	-	-	0.568	0.471	0.235	0.212	0.141	0.141	0.141	0.141	0.141	0.141
130	-	-	0.579	0.481	0.247	0.220	0.150	0.141	0.141	0.141	0.141	0.141
135	-	-	0.589	0.491	0.258	0.229	0.158	0.141	0.141	0.141	0.141	0.141
140	-	-	0.600	0.501	0.270	0.237	0.166	0.141	0.141	0.141	0.141	0.141
145	-	-	0.611	0.512	0.281	0.246	0.175	0.141	0.141	0.141	0.141	0.141
150 155	-		0.622 0.633	0.522 0.532	0.293 0.305	0.254 0.263	0.183 0.192	0.144 0.153	0.141 0.141	0.141 0.141	0.141 0.141	0.141
160	-		0.633	0.532	0.305	0.263	0.192	0.153	0.141	0.141	0.141	0.141
165	-		0.654	0.553	0.316	0.271	0.208	0.170	0.141	0.141	0.141	0.141
170	-	-	0.665	0.563	0.339	0.288	0.217	0.178	0.141	0.141	0.141	0.141
175	-	-	0.676	0.573	0.351	0.296	0.225	0.187	0.141	0.141	0.141	0.141
180	-	-	0.687	0.583	0.362	0.305	0.233	0.196	0.141	0.141	0.141	0.141
185	-	-	0.698	0.594	0.374	0.313	0.242	0.204	0.141	0.141	0.141	0.141
190	-	-	0.709	0.604	0.385	0.322	0.250	0.213	0.141	0.141	0.141	0.141
195	-	-	-	0.614	0.397	0.330	0.258	0.221	0.149	0.141	0.141	0.141
200	-		-	0.624	0.409	0.339	0.267	0.230	0.158	0.141	0.141	0.141
205	-	-	-	0.635	0.420	0.347	0.275	0.239	0.167	0.141	0.141	0.141
210	-	-	-	0.645	0.443	0.356	0.283	0.247	0.177	0.141	0.141	0.141
215	-	-	-	0.655	0.470	0.364	0.292	0.256	0.186	0.141	0.141	0.141
220	-	-	-	0.665	0.497	0.373	0.300	0.265	0.195	0.141	0.141	0.141
225	-	-	-	0.676	0.523	0.381	0.308	0.273	0.205	0.141	0.141	0.141
230	-	-	-	0.686	0.550	0.389	0.317	0.282	0.214	0.141	0.141	0.141
235	-	-	-	-	0.577	0.398	0.325	0.290	0.223	0.141	0.141	0.141
240 245	-		-		0.604 0.631	0.406 0.415	0.333	0.299	0.232	0.141 0.141	0.141 0.141	0.141
250			-	-	0.658	0.415	0.342	0.308	0.242	0.141	0.141	0.141
255					0.684	0.434	0.358	0.325	0.260	0.141	0.141	0.141
260					0.711	0.446	0.367	0.334	0.270	0.141	0.141	0.141
265	-	-	-	-		0.457	0.375	0.342	0.279	0.141	0.141	0.141
270	-	-	-	-	-	0.468	0.383	0.351	0.288	0.141	0.141	0.141
275	-	-	-	-	-	0,479	0.392	0.359	0.298	0.141	0.141	0.141
280	-	-	-	-	-	0.490	0.400	0.368	0.307	0.141	0.141	0.141
285	-	-	-	-	-	0.501	0.408	0.377	0.316	0.141	0.141	0.141
290		-	-	-	-	0.512	0.417	0.385	0.326	0.141	0.141	0.141
295	-	-	-	-	-	0.523	0.428	0.394	0.335	0.141	0.141	0.141
300	-	-	-	-	-	0.534	0.451	0.402	0.344	0.141	0.141	0.141
305	-	-	-	-	-	0.545	0.473	0.411	0.354	0.141	0.141	0.141
310	-	-	-	-	-	0.556	0.495	0.420	0.363	0.141	0.141	0.141
315	-	-	-	-	-	0.568	0.517	0.446	0.372	0.141	0.141	0.141
320	-	-	-	-	-	0.579	0.539	0.484	0.382	0.141	0.141	0.141
325	-	-	-	-	-	0.590	0.561	0.522	0.391	0.141	0.141	0.141
330	-	-	-	-	-	0.601	0.583	0.559	0.400	0.141	0.141	0.141
335	-	-	-	-	-	0.612	0.606	0.597	0.423	0.159	0.141	0.141
340	-		-	-	-	0.634	0.634	0.634	0.446	0.183	0.141	0.141
345	-	-	-	-	-	0.672	0.672	0.672	0.468	0.206	0.141	0.141
350		-	-	-	-	0.710	0.710	0.710	0.491	0.230	0.141	0.141
355	-	-	-	-	-		-	-	0.514	0.253	0.141	0.141
360 365	-	-		-	-	-	-	-	0.537 0.559	0.277 0.423	0.141 0.141	0.141
370	-		1		1	-		1	0.582	0.423	0.141	0.141
3/0									0.302	0.309	0.141	0.141

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 13 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

Section				Tal	ole12: I/H-C	olumn Section	ons 75 Minu	tes				
Factor up to m ⁻¹				Thic	kness (mm) Required fo	or a Design	Temperatur	e of			
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C
30	-	-	0.300	0.264	0.202	0.141	0.141	0.141	0.141	0.141	0.141	0.141
35	-	-	0.371	0.300	0.224	0.141	0.141	0.141	0.141	0.141	0.141	0.141
40	-	-	0.442	0.336	0.247	0.144	0.141	0.141	0.141	0.141	0.141	0.141
45 50	-	-	0.472	0.371	0.269	0.157	0.141	0.141	0.141	0.141	0.141	0.141
55	-	-	0.502 0.532	0.407 0.429	0.291 0.314	0.171 0.184	0.141 0.141	0.141 0.141	0.141	0.141 0.141	0.141 0.141	0.141
60	-	-	0.562	0.440	0.336	0.197	0.141	0.141	0.141	0.141	0.141	0.141
65	-	-	0.592	0.451	0.358	0.210	0.146	0.141	0.141	0.141	0.141	0.141
70	-	-	0.623	0.462	0.381	0.223	0.155	0.141	0.141	0.141	0.141	0.141
75	-	-	0.653	0.473	0.403	0.237	0.164	0.148	0.141	0.141	0.141	0.141
80	-	-	0.683	0.484	0.424	0.250	0.173	0.157	0.141	0.141	0.141	0.141
85	-	-	-	0.495	0.434	0.263	0.183	0.166	0.141	0.141	0.141	0.141
90 95	-	-	-	0.506 0.516	0.445 0.455	0.276 0.290	0.192 0.201	0.174 0.183	0.149 0.157	0.141 0.141	0.141 0.141	0.141
100	-		-	0.527	0.455	0.303	0.210	0.103	0.157	0.141	0.141	0.141
105	-	-	-	0.538	0.476	0.303	0.210	0.192	0.175	0.141	0.141	0.141
110	-	-	-	0.549	0.486	0.329	0.228	0.210	0.183	0.141	0.141	0.141
115	-	-	-	0.560	0.496	0.342	0.237	0.219	0.192	0.141	0.141	0.141
120	-	-	-	0.571	0.507	0.356	0.246	0.228	0.200	0.147	0.141	0.141
125	-		-	0.582	0.517	0.369	0.255	0.237	0.209	0.155	0.141	0.141
130	-	-	-	0.593	0.527	0.382	0.265	0.246	0.217	0.164	0.141	0.141
135 140	-	-	-	0.604 0.615	0.537 0.548	0.395 0.409	0.274 0.283	0.254 0.263	0.226 0.235	0.172 0.180	0.141 0.141	0.141 0.141
145	-	-	-	0.626	0.558	0.409	0.292	0.203	0.233	0.188	0.141	0.141
150	-	-	-	0.637	0.568	0.422	0.301	0.272	0.252	0.196	0.141	0.141
155	-	-	-	0.648	0.579	0.453	0.310	0.290	0.260	0.204	0.141	0.141
160	-	-	-	0.659	0.589	0.468	0.319	0.299	0.269	0.212	0.141	0.141
165	-	-	-	0.670	0.599	0.484	0.328	0.308	0.277	0.221	0.141	0.141
170	-	-	-	0.680	0.609	0.499	0.337	0.317	0.286	0.229	0.148	0.141
175	-	-	-	0.691	0.620	0.515	0.347	0.326	0.295	0.237	0.156	0.141
180 185	-	-	-	0.702	0.630 0.640	0.530 0.546	0.356	0.334	0.303	0.245 0.253	0.164 0.172	0.141
190			-	-	0.651	0.546	0.365	0.343	0.312	0.253	0.172	0.141
195	-	-	-	-	0.661	0.577	0.383	0.361	0.329	0.269	0.189	0.141
200	-	-	-	-	0.671	0.592	0.392	0.370	0.337	0.277	0.197	0.141
205	-	-	-	-	0.682	0.608	0.401	0.379	0.346	0.286	0.205	0.141
210	-	-	-	-	0.692	0.624	0.410	0.388	0.355	0.294	0.213	0.141
215	-	-	-	-	0.702	0.639	0.419	0.397	0.363	0.302	0.221	0.141
220	-	-	-	-	-	0.655	0.438	0.406 0.414	0.372	0.310	0.230	0.141
230	-		-	-	-	0.670 0.686	0.462	0.414	0.380	0.318 0.326	0.238	0.141
235	- :		-	-	-	0.701	0.510	0.442	0.309	0.326	0.254	0.141
240	-	-	-	-	-		0.535	0.459	0.406	0.342	0.262	0.141
245	-	-	-	-	-	-	0.559	0.477	0.415	0.351	0,270	0.141
250	-	-	-	-	-	-	0.583	0.495	0.423	0.359	0.279	0.141
255			-		-		0.607	0.513	0.435	0.367	0.287	0.141
260	-	-	-	-	-	-	0.631	0.531	0.447	0.375	0.295	0.141
265	-	-	-	-	-	-	0.656	0.549	0.459	0.383	0.303	0.141
270 275	-	-	-	-	-	-	0.680 0.704	0.567	0.471 0.483	0.391	0.311	0.142 0.154
280	-	-	-	-	-	-	- 0.704	0.584	0.483	0.399	0.320	0.154
285	-	-	-	-	-	-		0.620	0.506	0.416	0.336	0.178
290	-	-	-	-	-	-	-	0.638	0.518	0.425	0.344	0.191
295	-	-	-	-	-	-	-	0.656	0.530	0.445	0.352	0.203
300	-		-	-	-	-	-	0.674	0.542	0.465	0.360	0.215
305		-	-	-	-	-	-	0.692	0.554	0.486	0.369	0.228
310	-	-	-	-	-	-	-	0.709	0.566	0.506	0.377	0.240
315 320	-		-	-	-	-		-	0.578 0.590	0.526 0.546	0.385 0.393	0.252
325		-	-	-		-	-		0.602	0.566	0.393	0.264
330		-	-		-			-	0.614	0.587	0.401	0.277
335	-	-	-		-		-	-	0.625	0.607	0.423	0.301
340	-	-	-	-	-	-	-	-	0.627	0.627	0.436	0.423
345	-	-	-	-	-	-	-	-	0.647	0.647	0.545	0.545
350	-	-	-	-	-	-	-	-	0.667	0.667	0.667	0.667
355		-	-		-		-	-	0.688	0.688	0.688	0.688
360	-	-	-	-	-	-	-	-	0.708	0.708	0.708	0.708
365	-	-	-	-	-	-	-	-	-	-	-	-
370	-	-	-		-	-	-	-		-	-	

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 14 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-

CERTIFICATE OF APPROVAL No CF 5631

SteelMaster 600WF

-					,ic13.1/11 C	olumn Section	JII3 JO 1-1111U									
Section Factor up to m ⁻¹		Thickness (mm) Required for a Design Temperature of														
	300°C	350°C	400°C	450°C	500°C	550°C	600°C	620°C	650°C	700°C	750°C	800°C				
30	-	-	0.488	0.330	0.295	0.237	0.141	0.141	0.141	0.141	0.141	0.141				
35			0.569	0.390	0.333	0.263	0.147	0.141	0.141	0.141	0.141	0.141				
40 45	-		0.650	0.450 0.478	0.371	0.289 0.315	0.167 0.188	0.152 0.167	0.141 0.148	0.141 0.141	0.141 0.141	0.141				
50	-		-	0.478	0.409	0.315	0.188	0.167	0.148	0.141	0.141	0.141				
55	-	-	-	0.534	0.441	0.367	0.228	0.102	0.156	0.141	0.141	0.141				
60	-	-	-	0.562	0.452	0.393	0.249	0.212	0.176	0.141	0.141	0.141				
65	-	-	-	0.590	0.463	0.419	0.269	0.227	0.185	0.141	0.141	0.141				
70	-		-	0.619	0.474	0.432	0.290	0.243	0.194	0.145	0.141	0.141				
75	-	-	-	0.647	0.485	0.442	0.310	0.258	0.203	0.154	0.141	0.141				
80	-	-	-	0.675	0.496	0.452	0.330	0.273	0.212	0.163	0.141	0.141				
85 90			-	0.703	0.507 0.518	0.462 0.473	0.351 0.371	0.288	0.221 0.230	0.172 0.181	0.141 0.142	0.141				
95					0.528	0.483	0.371	0.319	0.239	0.101	0.151	0.141				
100	-	-	-	-	0.539	0.493	0.412	0.334	0.248	0.199	0.159	0.141				
105	-	-	-	-	0.550	0.504	0.428	0.349	0.257	0.208	0.168	0.141				
110	-	-	-	-	0.561	0.514	0.440	0.364	0.266	0.217	0.176	0.141				
115	-	-	-	-	0.572	0.524	0.452	0.379	0.275	0.226	0.184	0.142				
120	-	-	-	-	0.583	0.534	0.464	0.395	0.284	0.235	0.193	0.150				
125	-	-		-	0.594	0.545	0.475	0.410	0.294	0.244	0.201	0.158				
130 135	-		-	-	0.605 0.616	0.555 0.565	0.487 0.499	0.425 0.440	0.303 0.312	0.253 0.262	0.210 0.218	0.166 0.174				
140	-		-	-	0.627	0.565	0.499	0.454	0.312	0.262	0.218	0.174				
145	-	-	-	-	0.638	0.586	0.522	0.469	0.330	0.280	0.235	0.190				
150	-	-	-	-	0.649	0.596	0.534	0.484	0.339	0.289	0.243	0.198				
155	-		-	-	0.660	0.606	0.546	0.499	0.348	0.298	0.252	0.206				
160	-		-	-	0.671	0.617	0.558	0.514	0.357	0.307	0.260	0.214				
165	-	-	-	-	0.682	0.627	0.570	0.529	0.366	0.317	0.269	0.222				
170			-	-	0.693	0.637	0.581	0.543	0.375	0.326	0.277	0.230				
175				-	0.704	0.647	0.593	0.558	0.384	0.335	0.286	0.238				
180 185				-	-	0.658 0.668	0.605 0.617	0.573 0.588	0.393 0.402	0.344	0.294 0.302	0.245				
190	-		-	-	-	0.678	0.628	0.603	0.411	0.362	0.302	0.261				
195	-	-	-	-	-	0.688	0.640	0.617	0.420	0.371	0.319	0.269				
200	-	-	-	-	-	0.699	0.652	0.632	0.458	0.380	0.328	0.277				
205	-	-	-	-	-	0.709	0.664	0.647	0.507	0.389	0.336	0.285				
210	-	-	-	-	-	-	0.675	0.662	0.555	0.398	0.345	0.293				
215	-	-	-	-	-	-	0.687	0.677	0.604	0.407	0.353	0.301				
220 225	-		-	-	-	-	0.699	0.691 0.706	0.652 0.701	0.416 0.427	0.361	0.309				
230				-	-	-	0.709	0.706	0.701	0.445	0.370 0.378	0.317				
235			-	-	-	-	-	-	-	0.443	0.376	0.333				
240	-	-	-	-	-	-	-	-	-	0.482	0.395	0.341				
245	-	-	-	-	-	-	-	-	-	0.500	0.404	0.349				
250	-	-	-	-	-	-	-	-	-	0.519	0.412	0.357				
255	-	-	-	-	-	-	-	-	-	0.537	0.420	0.364				
260	-	-	-	-	-	-	-	-	-	0.556	0.432	0.372				
265	-	-	-	-	-	-	-	-	-	0.574	0.445	0.380				
270 275	-		-	-	-	-		-	-	0.592 0.611	0.457 0.470	0.388				
280	-			-	-	-	-	-	-	0.629	0.470	0.404				
285	-		-	-	-	-	-	-	-	0.648	0.495	0.412				
290	-	-	-	-	-	-	-	-		0.666	0.508	0.420				
295	-	-	-	-	-	-	-	-	-	0.684	0.521	0.436				
300	-	-	-	-	-	-	-	-	-	0.703	0.533	0.457				
305		-				-				-	0.546	0.479				
310	-	-	-	-	-	-	-	-	-	-	0.559	0.500				
315	-	-	-	-	-	-	-	-	-	-	0.572	0.521				
320 325	-		-	<u> </u>	-	-	-		-		0.584 0.597	0.542				
325				-	-	-	- :	-	-	-	0.597	0.585				
335	-				-	-		-	-	-	0.622	0.606				
340	-	-	-	-	-	-	-	-	-		0.635	0.627				
345	-			-	-	-	-		-	-	0.649	0.649				
350	-	-	-	-	-	-	-	-	-	-	0.670	0.670				
355	-	-	-	-	-	-	-	-	-	-	0.691	0.691				
360		-	-	-	-	-	-	-	-	-	-	-				
365	-	-	-	-	-	-	-	-	-	-	-	-				

Thickness is intumescent only. Results also apply to I/H-section beams exposed on all four sides limited to a maximum protection thickness of 0.715mm.

Page 15 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol Agg-



SteelMaster 600WF

	Table14: Circular and Rectangular Hollow Columns : Fire resistance period: 15 Minutes														
Section Factor up to m ⁻¹				Thickness	s (mm) Requ	uired for a D	esign Temp	erature of							
	300°C	350°C	400°C	450°C	500°C	520°C	550°C	600°C	650°C	700°C	750°C				
50	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
55	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
60	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
65	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
70	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
75	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
80	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
85	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
90	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
95	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
100	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
105	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
110	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
115	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
120	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
125	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
130	0.250	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
135	0.266	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
140	0.283	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
145	0.299	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
150	0.315	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
155	0.332	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
160	0.348	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
165	0.364	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
170	0.381	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
175	0.397	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
180	0.413	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
185	0.430	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
190	0.446	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
195	0.462	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
200	0.478	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
205	0.495	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
210	0.511	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
215	0.528	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
220	0.552	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
225	0.576	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				
230	0.601	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249				

Thickness is intumescent only. Maximum DFT thickness for Rectangular Hollow section is limited to 0.968mm.

Page 16 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-



SteelMaster 600WF

		Table15:	Circular and	d Rectangul	ar Hollow Co	olumns : Fire	e resistance	period: 30	Minutes					
Section Factor up to m ⁻¹	Thickness (mm) Required for a Design Temperature of													
	300°C	350°C	400°C	450°C	500°C	520°C	550°C	600°C	650°C	700°C	750°C			
50	0.489	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
55	0.526	0.314	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
60	0.549	0.328	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
65	0.571	0.342	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
70	0.593	0.357	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
75	0.616	0.371	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
80	0.638	0.385	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
85	0.661	0.399	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
90	0.683	0.414	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
95	0.705	0.428	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
100	0.728	0.442	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
105	0.750	0.457	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
110	0.772	0.471	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
115	0.795	0.485	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
120	0.817	0.500	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
125	0.839	0.514	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
130	0.862	0.529	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
135	0.884	0.557	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
140	0.952	0.585	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
145	1.019	0.612	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
150	1.087	0.640	0.257	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
155	1.154	0.668	0.283	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
160	1.190	0.695	0.309	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
165	1.244	0.723	0.335	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
170	1.299	0.750	0.360	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
175	-	0.778	0.386	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
180		0.806	0.412	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
185	-	0.833	0.438	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
190	-	0.861	0.464	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
195	-	0.891	0.490	0.251	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
200	-	0.937	0.515	0.274	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
205	-	0.982	0.546	0.296	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
210	-	1.027	0.580	0.319	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
215	-	1.072	0.614	0.341	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
220	-	1.117	0.648	0.363	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
225	-	1.163	0.682	0.386	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
230	-	1.208	0.716	0.408	0.249	0.249	0.249	0.249	0.249	0.249	0.249			

Thickness is intumescent only. Maximum DFT thickness for Rectangular Hollow section is limited to 0.968mm.

Page 17 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-



SteelMaster 600WF

		Table16:	Circular an	d Rectangul	ar Hollow Co	olumns : Fire	e resistance	period: 45	Minutes					
Section Factor up to m ⁻¹	Thickness (mm) Required for a Design Temperature of													
	300°C	350°C	400°C	450°C	500°C	520°C	550°C	600°C	650°C	700°C	750°C			
50	0.910	0.555	0.403	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
55	0.950	0.594	0.426	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
60	0.990	0.633	0.449	0.249	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
65	1.030	0.672	0.472	0.265	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
70	1.069	0.711	0.495	0.283	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
75	1.109	0.750	0.518	0.301	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
80	1.149	0.789	0.545	0.319	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
85	1.189	0.828	0.574	0.336	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
90	1.228	0.867	0.602	0.354	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
95	1.268	0.903	0.631	0.372	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
100	1.308	0.936	0.660	0.390	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
105	-	0.969	0.688	0.407	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
110	-	1.002	0.717	0.425	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
115	-	1.035	0.746	0.443	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
120	-	1.068	0.775	0.461	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
125	-	1.101	0.803	0.479	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
130	-	1.133	0.832	0.496	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
135	-	1.166	0.861	0.514	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
140	-	1.199	0.890	0.537	0.249	0.249	0.249	0.249	0.249	0.249	0.249			
145	-	1.232	0.924	0.571	0.266	0.249	0.249	0.249	0.249	0.249	0.249			
150	-	1.265	0.957	0.605	0.298	0.249	0.249	0.249	0.249	0.249	0.249			
155	-	1.298	0.990	0.639	0.331	0.269	0.249	0.249	0.249	0.249	0.249			
160	-	-	1.024	0.673	0.364	0.292	0.249	0.249	0.249	0.249	0.249			
165	-	-	1.057	0.708	0.396	0.315	0.249	0.249	0.249	0.249	0.249			
170	-	-	1.090	0.742	0.429	0.339	0.249	0.249	0.249	0.249	0.249			
175	-	-	1.124	0.776	0.462	0.362	0.261	0.249	0.249	0.249	0.249			
180	-	-	1.157	0.810	0.494	0.385	0.285	0.249	0.249	0.249	0.249			
185	-	-	1.190	0.844	0.527	0.408	0.308	0.249	0.249	0.249	0.249			
190	-	-	1.224	0.878	0.561	0.431	0.331	0.249	0.249	0.249	0.249			
195	-	-	1.257	0.919	0.595	0.454	0.354	0.249	0.249	0.249	0.249			
200	-	-	1.290	0.962	0.628	0.477	0.377	0.249	0.249	0.249	0.249			
205	-	-	-	1.004	0.662	0.500	0.400	0.249	0.249	0.249	0.249			
210	-	-	-	1.046	0.696	0.523	0.423	0.249	0.249	0.249	0.249			
215	-	-	-	1.088	0.730	0.563	0.447	0.249	0.249	0.249	0.249			
220	-	-	-	1.130	0.764	0.606	0.470	0.263	0.249	0.249	0.249			
225	-	-	-	1.173	0.798	0.648	0.493	0.290	0.249	0.249	0.249			
230	-	_	_	1.215	0.832	0.691	0.516	0.317	0.249	0.249	0.249			

Thickness is intumescent only. Maximum DFT thickness for Rectangular Hollow section is limited to 0.968mm.

Page 18 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-



SteelMaster 600WF

		Table17	: Circular an	d Rectangul	ar Hollow Co	olumns : Fire	e resistance	period: 60	Minutes						
Section Factor up to m ⁻¹		Thickness (mm) Required for a Design Temperature of													
	300°C	350°C	400°C	450°C	500°C	520°C	550°C	600°C	650°C	700°C	750°C				
50	-	0.918	0.692	0.492	0.376	0.352	0.249	0.249	0.249	0.249	0.249				
55	-	0.962	0.745	0.524	0.398	0.368	0.266	0.249	0.249	0.249	0.249				
60	-	1.006	0.797	0.556	0.419	0.385	0.283	0.249	0.249	0.249	0.249				
65	-	1.050	0.850	0.588	0.441	0.402	0.300	0.249	0.249	0.249	0.249				
70	-	1.094	0.894	0.620	0.463	0.419	0.317	0.249	0.249	0.249	0.249				
75	-	1.138	0.923	0.651	0.485	0.436	0.333	0.249	0.249	0.249	0.249				
80	-	1.182	0.952	0.683	0.506	0.453	0.350	0.249	0.249	0.249	0.249				
85	-	1.227	0.981	0.715	0.528	0.470	0.367	0.249	0.249	0.249	0.249				
90	-	1.271	1.009	0.747	0.558	0.487	0.384	0.249	0.249	0.249	0.249				
95	-	-	1.038	0.779	0.588	0.503	0.400	0.249	0.249	0.249	0.249				
100	-	-	1.067	0.811	0.617	0.520	0.417	0.249	0.249	0.249	0.249				
105	-	-	1.096	0.843	0.647	0.545	0.434	0.249	0.249	0.249	0.249				
110	-	-	1.125	0.875	0.677	0.576	0.450	0.249	0.249	0.249	0.249				
115	-	-	1.154	0.909	0.706	0.606	0.467	0.249	0.249	0.249	0.249				
120	-	-	1.183	0.946	0.736	0.636	0.484	0.249	0.249	0.249	0.249				
125	-	-	1.211	0.982	0.765	0.667	0.501	0.249	0.249	0.249	0.249				
130	-	-	1.240	1.018	0.795	0.697	0.517	0.249	0.249	0.249	0.249				
135	-	-	1.269	1.054	0.825	0.727	0.541	0.263	0.249	0.249	0.249				
140	-	-	1.298	1.090	0.854	0.758	0.572	0.301	0.249	0.249	0.249				
145	-	-	-	1.126	0.884	0.788	0.604	0.339	0.249	0.249	0.249				
150	-	-	-	1.162	0.922	0.818	0.636	0.377	0.249	0.249	0.249				
155	-	-	-	1.199	0.960	0.849	0.667	0.415	0.249	0.249	0.249				
160	-	-	-	1.235	0.998	0.879	0.699	0.453	0.249	0.249	0.249				
165	-	-	-	1.271	1.036	0.917	0.731	0.491	0.269	0.249	0.249				
170	-	-	-	1.307	1.074	0.957	0.762	0.528	0.292	0.249	0.249				
175	-	-	-	-	1.112	0.998	0.794	0.558	0.314	0.249	0.249				
180	-	-	-	-	1.150	1.038	0.825	0.587	0.337	0.249	0.249				
185	-	-	-	-	1.188	1.078	0.857	0.617	0.360	0.249	0.249				
190	-	-	-	-	1.226	1.118	0.892	0.646	0.382	0.249	0.249				
195	-	-	-	-	1.264	1.158	0.949	0.676	0.405	0.249	0.249				
200	-	-	-	-	1.302	1.198	1.005	0.705	0.428	0.249	0.249				
205	-	-	-	-	-	1.239	1.062	0.735	0.450	0.249	0.249				
210	-	-	-	-	-	1.279	1.118	0.764	0.473	0.249	0.249				
215	-	-	-	-	-	-	1.175	0.794	0.496	0.249	0.249				
220	-	-	-	-	-	-	1.231	0.823	0.519	0.284	0.249				
225	-	-	-	-	-	-	1.288	0.852	0.555	0.320	0.249				
230	_	-	-	-	-	-	-	0.882	0.599	0.355	0.249				

Thickness is intumescent only. Maximum DFT thickness for Rectangular Hollow section is limited to 0.968mm.

Page 19 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-



SteelMaster 600WF

				Table 18: Ci	rcular Hollov	v Columns:	75 Minutes								
Section Factor up to m ⁻¹		Thickness (mm) Required for a Design Temperature of													
	300°C	350°C	400°C	450°C	500°C	520°C	550°C	600°C	650°C	700°C	750°C				
50	-	-	0.968	0.813	0.579	0.520	0.456	0.374	0.249	0.249	0.249				
55	-	-	1.012	0.879	0.631	0.561	0.488	0.396	0.267	0.249	0.249				
60	-	-	1.057	0.916	0.684	0.602	0.520	0.419	0.288	0.249	0.249				
65	-	-	1.101	0.950	0.737	0.643	0.551	0.442	0.308	0.249	0.249				
70	-	-	1.146	0.984	0.789	0.683	0.581	0.465	0.328	0.249	0.249				
75	-	-	1.191	1.018	0.842	0.724	0.611	0.488	0.348	0.249	0.249				
80	-	-	1.235	1.052	0.890	0.765	0.641	0.510	0.368	0.249	0.249				
85	-	-	1.280	1.086	0.918	0.806	0.671	0.534	0.388	0.249	0.249				
90	-	-	-	1.120	0.946	0.847	0.701	0.561	0.409	0.249	0.249				
95	-	-	-	1.154	0.974	0.887	0.731	0.588	0.429	0.249	0.249				
100	-	-	-	1.188	1.002	0.919	0.761	0.615	0.449	0.249	0.249				
105	-	-	-	1.222	1.031	0.952	0.791	0.642	0.469	0.249	0.249				
110	-	-	-	1.256	1.059	0.985	0.821	0.669	0.489	0.249	0.249				
115	-	-	-	1.290	1.087	1.017	0.851	0.696	0.509	0.249	0.249				
120	-	-	-	-	1.115	1.050	0.881	0.723	0.530	0.249	0.249				
125	-	-	-	-	1.144	1.082	0.924	0.750	0.553	0.249	0.249				
130	-	-	-	-	1.172	1.115	0.969	0.777	0.577	0.249	0.249				
135	-	-	-	-	1.200	1.147	1.014	0.804	0.600	0.283	0.249				
140	-	-	-	-	1.228	1.180	1.059	0.831	0.623	0.330	0.249				
145	-	-	-	-	1.256	1.213	1.103	0.858	0.647	0.377	0.249				
150	-	-	-	-	1.285	1.245	1.148	0.885	0.670	0.425	0.249				
155	-	-	-	-	-	1.278	1.193	0.936	0.693	0.472	0.249				
160	-	-	-	-	-	1.310	1.238	0.987	0.717	0.519	0.249				
165	-	-	-	-	-	-	1.282	1.037	0.740	0.548	0.249				
170	-	-	-	-	-	-	-	1.088	0.763	0.575	0.251				
175	-	-	-	-	-	-	-	1.138	0.786	0.601	0.276				
180	-	-	-	-	-	-	-	1.189	0.810	0.627	0.302				
185	-	-	-	-	-	-	-	1.239	0.833	0.653	0.328				
190	-	-	-	-	-	-	-	1.290	0.856	0.679	0.354				
195	-	-	-	-	-	-	-	-	0.880	0.706	0.379				
200	-	-	-	-	-	-	-	-	0.971	0.732	0.405				
205	-	-	-	-	-	-	-	-	1.078	0.758	0.431				
210	-	-	-	-	-	-	-	-	1.185	0.784	0.457				
215	-	-	-	-	-	-	-	-	1.285	0.810	0.483				
220	-	-	-	-	-	-	-	-	-	0.837	0.508				
225	-	-	-	-	-	-	-	-	-	0.863	0.540				
230	-	_	_	-	_	_	_	_	_	0.936	0.586				

Thickness is intumescent only. Results are only applicable to Circular Hollow Sections columns.

Page 20 of 20 Signed AH/007, E/140, AH/022, AB/006, R/014, G/009

Pol agg-