
Product Overview

D01S is a high-rigidity, inorganic-filler dental model resin purpose-built for orthodontic and restorative workflows. Its plaster-like matte finish mimics traditional dental stone, giving technicians a familiar surface texture they trust — while delivering the dimensional accuracy that digital dentistry demands.

Key Specifications

Parameter	Value	Parameter	Value
Appearance / Color	Seashell (Matte)	Shore Hardness	92D
Viscosity (25° C)	1,100 mPa · s	Tensile Strength	43 MPa
Flexural Strength	65.9 MPa	Flexural Modulus	2,660 MPa
Elongation at Break	5%	Notched Impact	18.4 J/m
Water Absorption	0.51%	Liquid / Solid Density	1.159 / 1.225 g/cm ³

Why D01S for Dental Models

- Industry-low water absorption (0.51%) — Most dental resins absorb 0.8–1.5% moisture. D01S models hold dimension from morning print through afternoon thermoforming, even in humid environments.
- 92D Shore hardness — Second-hardest in the entire RESIONE product line. Models withstand repeated thermoforming pressure and rough handling without deformation.
- Inorganic filler, plaster-like finish — Dental technicians immediately recognize the matte surface texture. No learning curve. No trust barrier.
- 8/10 dimensional stability — Consistent shrinkage control across batches. A model printed Monday fits the same aligner as one printed Friday.

Import Pricing (FOB Shenzhen)

The pricing below is for direct import from our factory in Dongguan, China. Compared to buying through a local distributor, direct import typically saves 30–50% per kilogram, depending on volume.

D01S Volume Pricing

Tier	Quantity	Unit Price (USD/kg)	Packaging	Lead Time
Sample / Trial	1–3 kg	\$75.00	1 kg bottle	3–5 days
Small Batch	4–20 kg	\$48.00	1 kg bottle	5–7 days
Standard	20–96 kg	\$35.00	1 kg / 5 kg	7–10 days
Wholesale (F-Level)	96 kg +	\$27.00	5 kg jerry can	10–14 days

Shipping Cost Estimate

Destination	Air Freight (5–7 days)	Sea Freight (25–35 days)	Courier (3–5 days)
Middle East / South Asia	~\$6–8 / kg	~\$1.5–2 / kg	~\$12–15 / kg
Europe	~\$5–7 / kg	~\$1–2 / kg	~\$10–14 / kg
North America	~\$5–8 / kg	~\$1.5–2.5 / kg	~\$10–13 / kg
Southeast Asia	~\$3–5 / kg	~\$0.8–1.5 / kg	~\$8–10 / kg

Estimates only. Actual shipping cost depends on exact destination, weight, and carrier. We can quote door-to-door DDP for qualified buyers.

How to Read This vs. Local Distributor Pricing

If your local distributor charges you ~\$55–65/kg for Anycubic (typical markup), here is the math on a 100 kg annual consumption:

	Price/kg	Annual Cost (100 kg)	Savings
Local Distributor (Anycubic)	~\$60.00	~\$6,000	—
D01S Direct Import (FOB)	\$27.00	\$2,700	\$3,300 / year
D01S + Sea Freight (~\$2/kg)	~\$29.00	~\$2,900	\$3,100 / year

Bottom line: Direct import pays for itself on the first order. The savings alone cover shipping, customs, and still leave you 35–45% below distributor pricing.

D01S vs. General-Purpose Resins

Why a purpose-built dental model resin matters

Dimension	D01S (Dental-Specific)	General-Purpose Resin (e.g. Anycubic)
Water Absorption	0.51% — industry-low	0.8–1.5% — absorbs moisture, model drifts
Surface Finish	Plaster-like matte (inorganic filler)	Glossy/ semi-gloss
Hardness	92D — stands up to the 500g ring	75–85D — softer, deforms under pressure
Dimensional Stability	8/10 — consistent batch-to-batch	Varies — general-purpose formulation
Target Use	Dental models, aligner thermoforming	General printing, figurines, prototyping
Batch Consistency	Controlled shrinkage, tight tolerance	Wider tolerance range

How to Start

1. Trial Order Start with 1–3 kg. Run it on your existing models side-by-side with your current resin. No commitment beyond the trial.
2. Validate Print the same dental model file. Thermoform on both. Check fit. Measure dimensions after 24 hours. The difference will be visible.
3. Scale Once validated, we can discuss volume pricing (F-Level starts at 96 kg) and establish regular shipment schedules.

What We Need From You for a Formal Quote

- ☐ Destination port / delivery address
- ☐ Estimated monthly or annual volume
- ☐ Preferred shipping method (air / sea / courier DDP)

Payment & Terms

Item	Standard Terms
Payment	T/T 50% deposit, 50% before shipment (flexible for established relationships)
MOQ	1 kg for trial; 4 kg for wholesale pricing
Incoterms	FOB Shenzhen (default); CIF / DDP available on request
Packaging	1 kg UV-resistant bottle; 5 kg jerry can for bulk orders
Shelf Life	12 months (store in cool, dark place; 15–30° C)
Certification	MSDS available; ISO 9001 factory

Important note: D01S is for lab-side / technician use (indirect dental models). It is not certified for intraoral application. If you need biocompatible resins for surgical guides or temporary crowns,

ask us about our ISO 10993-certified product line.

Ready to try D01S?

Contact Person	Jenson Huang
Title	International Sales Engineer
Company	RESIONE / Dongguan Godsaid Technology Co., Ltd.
Email	jenson@godsaid3d.com
Phone / WhatsApp	+86 13798847261
Website	www.resione.top
Factory Address	Dongguan, Guangdong, China

I am happy to prepare a formal proforma invoice once you share your shipping details and target volume. No pressure — just let me know what works for you.

Jenson