

Reverse Monte Carlo (RMC), Hybrid Reverse Monte Carlo (HRMC), and Empirical Potential Structure Refinement (EPSR) for Modeling Calcium Silicate Glass Structures

A Scientific Report on Theory, Methodology, and Structural Interpretation

Prepared by: Iliya_Farokhi

Supervisor: Dr_Amirhossein_Moghania

Date: 2026-05-07

This report summarizes the physical basis, mathematical formulation, computational workflow, and scientific interpretation of RMC-based structural modeling approaches for calcium silicate glasses. Special emphasis is placed on radial distribution functions, network connectivity, pair constraints, and the comparative strengths of RMC, HRMC, and EPSR.

1. Introduction

Calcium silicate glasses are important inorganic materials used in biomaterials, sealing systems, glass-ceramics, and high-temperature functional applications. Their structural complexity arises from the disordered arrangement of SiO_4 tetrahedra, network-modifying Ca ions, and oxygen species distributed as bridging oxygen (BO) and non-bridging oxygen (NBO).

Because glass lacks long-range periodicity, conventional crystallographic methods are insufficient for determining its full atomic arrangement. Instead, total scattering experiments, radial distribution functions, and atomistic modeling methods are combined to infer realistic three-dimensional structures.

Among these methods, Reverse Monte Carlo (RMC) has become a widely used approach for generating atomistic models that reproduce experimental scattering data. However, standard RMC may yield physically unrealistic configurations unless additional chemical or energetic constraints are introduced. This limitation motivated the development of Hybrid Reverse Monte Carlo (HRMC) and Empirical Potential Structure Refinement (EPSR).




Figure 1. Schematic representation of a calcium silicate glass network illustrating SiO_4 tetrahedra, modifying Ca ions, and oxygen connectivity.

2. Structural Features of Calcium Silicate Glass

2.1 Network Formers and Network Modifiers

In calcium silicate glass, silicon acts as the principal network former, typically occupying tetrahedral coordination with oxygen. Calcium acts primarily as a network modifier. The addition of CaO disrupts Si-O-Si bridges and generates non-bridging oxygens, thereby depolymerizing the silicate network.

2.2 Bridging and Non-Bridging Oxygens

Bridging oxygens connect two silicon atoms and contribute to network connectivity. Non-bridging oxygens are bonded to only one silicon atom and are charge-balanced by calcium cations. The BO/NBO ratio strongly influences viscosity, density, transport properties, and chemical durability.




Figure 2. Schematic distinction between bridging oxygen (BO) and non-bridging oxygen (NBO) environments in silicate glass.

2.3 Pair Correlations

The local structure of calcium silicate glass is commonly interpreted using partial pair correlations such as Si-O, O-O, Si-Si, Ca-O, and Ca-Si. These correlations define the first-shell coordination geometry and medium-range order in the disordered network.

3. Radial Distribution Function and Scattering Basis

The radial distribution function $g(r)$ describes the probability of finding an atom at a distance r from a reference atom relative to an ideal gas of the same number density. It is a central quantity in the structural analysis of amorphous materials.

$$g(r) = (1 / (4\pi r^2 \rho)) * (dN(r) / dr)$$

Here, ρ is the atomic number density and $dN(r)$ is the number of atoms in the spherical shell between r and $r + dr$.

The total scattering structure factor $S(Q)$ measured by neutron or X-ray diffraction is related to real-space pair correlations through Fourier transformation.

$$G(r) = 4\pi r \rho * (g(r) - 1)$$

$$S(Q) = 1 + 4\pi \rho * \int_0^\infty [r^2 (g(r) - 1) \sin(Qr) / (Qr) dr]$$




Figure 3. Example radial distribution or pair distribution function used to interpret short-range order in calcium silicate glass.

Peaks in $g(r)$ or $G(r)$ correspond to preferred interatomic distances. For silicate glasses, the first sharp peak is often associated with Si-O nearest-neighbor bonding, while subsequent features reflect O-O, Si-Si, and Ca-O environments.

4. Reverse Monte Carlo (RMC) Method

Reverse Monte Carlo is a data-driven structural refinement technique in which atoms are moved randomly inside a simulation box until the calculated structural observables agree with experiment. In contrast to conventional Monte Carlo with an explicit interaction potential, standard RMC primarily minimizes the mismatch between model predictions and experimental data.

4.1 Objective Function

A common least-squares form of the misfit function is:

$$\chi^2 = \sum_i [(D_{\text{exp}}(i) - D_{\text{calc}}(i))^2 / \sigma_i^2]$$

where $D_{\text{exp}}(i)$ is the experimental value, $D_{\text{calc}}(i)$ is the simulated value, and σ_i represents the uncertainty or weighting factor.

4.2 Acceptance Logic

A trial move that improves the fit is accepted. A move that worsens the fit may be rejected depending on the implementation, but in standard RMC the guiding principle is reduction of structural discrepancy with respect to experiment.

4.3 Typical Constraints

To avoid nonphysical structures, RMC simulations often include additional constraints such as minimum approach distances, coordination limits, bond-angle restrictions, and composition conservation.

Constraint Type	Purpose	Example in Ca-Silicate Glass
-----------------	---------	------------------------------

Cutoff distance	Avoid atomic overlap	Si-O > 1.4 Å, Ca-O > 2.0 Å
Coordination constraint	Preserve chemistry	Si approximately 4-fold
Bond angle range	Maintain tetrahedral geometry	O-Si-O around 109.5 deg
Composition constraint	Respect stoichiometry	Fixed Ca/Si/O ratio

5. Hybrid Reverse Monte Carlo (HRMC)

Hybrid Reverse Monte Carlo extends standard RMC by combining agreement with experimental data and an explicit energetic penalty derived from an interatomic potential. As a result, HRMC seeks structures that are not only consistent with scattering measurements but also energetically more realistic.

$$\Phi = \chi^2 + \lambda * E_{\text{potential}}$$

In this expression, Φ is the total objective function, χ^2 measures agreement with experiment, $E_{\text{potential}}$ is the configurational energy from an assumed force field or potential model, and λ is a weighting parameter controlling the balance between data fitting and physical realism.

HRMC is especially useful in oxide glasses because unconstrained RMC can occasionally generate unrealistic bond-angle distributions or coordination defects. The energy term suppresses such artifacts.

6. Empirical Potential Structure Refinement (EPSR)

Empirical Potential Structure Refinement begins with a reference interaction potential and iteratively modifies it to improve agreement with experimental scattering data. EPSR thus combines the strengths of physically motivated atomistic modeling and data refinement.

Instead of fitting only coordinates directly, EPSR updates an empirical correction to the potential so that the generated ensemble reproduces measured structure factors and pair distribution functions.

$$U_{\text{total}}(r) = U_{\text{reference}}(r) + U_{\text{empirical}}(r)$$

This approach is particularly advantageous when a reasonable initial force field exists but needs refinement to capture the true short-range and medium-range ordering observed experimentally.




Figure 4. Conceptual comparison of RMC, HRMC, and EPSR strategies for structural refinement of disordered materials.

7. Comparison of RMC, HRMC, and EPSR

Method	Main Driver	Strength	Limitation
RMC	Fit to experiment	Flexible and data-driven	May produce nonphysical structures
HRMC	Experiment + energy	More realistic local chemistry	Requires suitable potential
EPSR	Reference potential + empirical refinement	Balances physics and fit	More model dependent

The appropriate method depends on the available experimental data, the quality of the interaction model, and the scientific objective. If the goal is rapid structural fitting to diffraction data, RMC may be sufficient. If local chemistry and physically meaningful coordination environments are essential, HRMC or EPSR often provide superior structural realism.

8. Application to Calcium Silicate Glass

When applied to calcium silicate glasses, these methods provide insight into coordination environments, modifier distribution, Qn species populations, and medium-range connectivity. A refined atomistic model can be used to interpret partial RDFs, bond-angle distributions, ring statistics, and transport-related descriptors.

Important structural questions include the average Ca-O coordination number, the distribution of Si-O bond lengths, the relative abundance of BO and NBO species, and the degree of silicate network depolymerization as a function of CaO content.




Figure 5. Example atomistic structural model of calcium silicate glass obtained through scattering-based refinement.




Figure 6. Alternative visualization of calcium silicate glass topology emphasizing disrupted network connectivity and modifier-rich environments.

9. Typical Computational Workflow

Step	Description
1	Prepare composition, density, and initial atomic configuration
2	Import experimental S(Q), F(Q), or G(r) data

3	Define cutoff distances and chemical constraints
4	Run RMC, HRMC, or EPSR refinement
5	Monitor fit quality, coordination numbers, and structural stability
6	Analyze final model using RDF, BAD, Qn, and topology metrics

The final refined structure is not a single unique solution, but rather one acceptable configuration or ensemble consistent with the chosen data and constraints. Therefore, interpretation should always consider uncertainty, model dependence, and the possibility of multiple structurally plausible solutions.

10. Conclusion

Reverse Monte Carlo and its advanced variants provide a powerful framework for the structural modeling of calcium silicate glasses. RMC offers direct fitting to scattering data, HRMC introduces energetic realism, and EPSR refines interatomic interactions to improve consistency with experiment.

For complex oxide glasses, physically meaningful interpretation requires not only agreement with diffraction measurements but also appropriate chemical constraints and validation against complementary observables. When applied carefully, these methods reveal the relationship between atomic-scale disorder and macroscopic glass properties.

11. Selected References

1. McGreevy, R. L. Reverse Monte Carlo modelling. *Journal of Physics: Condensed Matter*, 13, R877-R913.
2. Gereben, O., Pusztai, L. Reverse Monte Carlo studies of disordered systems. *Physica Scripta*, 2012.
3. Tucker, M. G., Keen, D. A., Dove, M. T., Goodwin, A. L., Hui, Q. RMCProfile: reverse Monte Carlo for polycrystalline materials. *Journal of Physics: Condensed Matter*, 19, 335218.
4. Soper, A. K. Empirical Potential Structure Refinement of fluid structure. *Chemical Physics*, 202, 295-306.
5. Akinsunmade, A., Adebayo, G., and co-workers. Structural modelling approaches for oxide glasses using diffraction-guided simulations.
6. Cormier, L., Cuello, G. J., and collaborators. Neutron diffraction and structural modelling of silicate and aluminosilicate glasses.