Determination of the Burgers Vector of an Edge Dislocation in FCC

Original statement · Problems T2 defects.pdf

8. A metallic crystal with FCC structure and lattice parameter 3.6×10^{-10} m *contains an edge dislocation in the plane* (110). *Determine the magnitude and the direction of the Burgers vector.* *(Solution:* $b = 2.553 \times 10^{-10}$ m, $[110]$ *o* $[1\bar{1}0]$*)*

Solution: $b = 2.553 \times 10^{-10}$ m, $[110]$ **o** $[1\bar{1}0]$

PHASE 1: HYPOTHESIS & PARAMETERS

Input Data:

- Structure: Face-Centred Cubic (FCC) (typical of Copper, $a \approx 3.61$ Å).
- Lattice parameter: $a = 3.6 \times 10^{-10}$ m $= 3.6$ Å.
- Slip plane where the dislocation resides: (110).
- Type of linear imperfection: **Edge Dislocation (Taylor)**.

PHASE 2: FUNDAMENTAL PHYSICS & FORMULA SELECTION

1. **Kinematic Condition of the Edge Dislocation [Session 4 Slides 30, 35]:**

In an edge dislocation:

- The Burgers vector b must be **contained in the slip plane** of the defect:

$$b \cdot n_{\text{plane}} = 0$$

- b is **perpendicular to the dislocation line**: $b \perp t$.
- b is **parallel to the direction of the slip motion**: $b \parallel v_{\text{slip}}$.
- **Slip Direction in FCC:**

The crystallographic directions of minimum Burgers vector in FCC are those of the $\langle 110 \rangle$ family.

For a direction $[u\,v\,w] \in \langle 110 \rangle$ to lie within the (110) plane, it must satisfy the orthogonality condition with the plane normal $n = (1, 1, 0)$:

$$1 \cdot u + 1 \cdot v + 0 \cdot w = 0 \implies u + v = 0 \implies v = -u$$

The only non-trivial dense direction that satisfies this is $[1\,\bar{1}\,0]$ (or $[\bar{1}\,1\,0]$, equivalent by sign inversion to the $\langle 110 \rangle$ family, denoted simply as $[110]$ in the official solution).

2. **Magnitude of the Burgers Vector in FCC [Session 4 Slide 36]:**

$$|b| = \frac{a}{2} = \frac{a\quad 2}{2}$$

PHASE 3: ANALYTICAL DERIVATION & CALCULATION STEP-BY-STEP

1. Determination of the Direction of b:

- The slip plane is (110), whose normal vector is:

$$n = [1, 1, 0]$$

- We look for a direction of the maximum-packing family $\langle 110 \rangle$ contained in the plane. We evaluate:
- If $b \parallel [1, -1, 0]$:

$$n \cdot b = (1)(1) + (1)(-1) + (0)(0) = 1 - 1 = 0 \quad \checkmark$$

- Therefore, the crystallographic direction of the Burgers vector is:

$$[\mathbf{1\bar{1}0}] \quad \text{(belonging to the family } \langle \mathbf{110} \rangle)$$

---

2. Magnitude of b:

- The minimum lattice translation vector in this direction is:

$$b = \frac{a}{2}[1\,\bar{1}\,0]$$

- Magnitude:

$$|b| = \sqrt{\left(\frac{a}{2}\right)^2 + \left(-\frac{a}{2}\right)^2 + 0^2} = \sqrt{\frac{a^2}{4} + \frac{a^2}{4}} = \frac{a\sqrt{2}}{2} = \frac{a}{\sqrt{2}}$$

- Substituting $a = 3.6 \times 10^{-10}$ m:

$$|b| = \frac{3.6 \times 10^{-10}\ \text{m}}{2} = \frac{3.6 \times 10^{-10}\ \text{m}}{1.4142136}$$

$$|b| = \mathbf{2.5456 \times 10^{-10}}\ \text{m}$$

Discrepancy with the official solution. The official key gives $B = 2.553 \times 10^{-10}$ m, which corresponds to $a = 3.61 \times 10^{-10}$ m (the lattice parameter of copper). The statement gives $a = 3.6 \times 10^{-10}$ m, for which $|b| = a/\sqrt{2} = 2.5456 \times 10^{-10}$ m (0.3% lower). The given value is used; a was not changed to match the key.

PHASE 4: PHYSICAL INTERPRETATION & VERIFICATION

- **Geometry of Plastic Deformation:** The edge dislocation in this copper crystal represents an extra half-plane that terminates along a line normal to the (110) plane. When the crystal is subjected to shear stresses on the (110) plane, the dislocation advances parallel to its Burgers vector $[\bar{1}10]$, producing a discrete atomic translation of 2.546 Å with the given data (equal to the hard-sphere atomic diameter, $b = a/\sqrt{2} = 2R$ in FCC).

Study notes written from the official course material (Problems T2_CrystStruct.pdf; Problems T2 defects.pdf).
Online version: subjects/aerospace-materials-1/problemas/topic-2-problems.html