Drawing Crystal Planes in a Cubic Lattice

Original statement · Problems T2_CrystStruct.pdf

3. Draw the crystalline planes in a cubic lattice that present the following Miller indices: a) $(1\,0\,\bar{1})$ *b)* $(1\,\bar{2}\,1)$ *c)* $(\bar{2}\,1\,3)$ *d)* $(1\,\bar{3}\,3)$ *e)* $(1\,\bar{2}\,\bar{2})$ *f)* $(\bar{3}\,\bar{1}\,2)$ *g)* $(1\,2\,\bar{3})$ *h)* $(\bar{1}\,\bar{4}\,3)$ *i)* $(\bar{3}\,\bar{1}\,\bar{3})$ *j)* $(3\,\bar{1}\,3)$

PHASE 1: HYPOTHESIS & PARAMETERS

Geometric Context:

Ten families of crystallographic planes are analysed in a cubic lattice with orthogonal edges of length a.

Origin Selection Criterion [Session 3 Slides 45, 49]:

- If all indices h, k, l are positive, the natural origin is placed at the lower left rear vertex $(0, 0, 0)$.
- If any index is negative (overbar notation $\bar{u}$), the origin must be translated by $+1$ unit along the corresponding axis so that the intercept falls inside the standard unit cell:
- $\bar{h} \implies$ translate origin to $x = 1$.
- $\bar{k} \implies$ translate origin to $y = 1$.
- $\bar{l} \implies$ translate origin to $z = 1$.

PHASE 2: FUNDAMENTAL PHYSICS & FORMULA SELECTION

According to Miller's systematic inverse procedure [Session 3 Slides 44, 48]:

1. Take the **reciprocals of the Miller indices** to find the relative axial intercepts:

$$x_{\text{int}} = \frac{1}{h}, \quad y_{\text{int}} = \frac{1}{k}, \quad z_{\text{int}} = \frac{1}{l}$$

(with the rule $1/0 = \infty$, indicating parallelism to the axis).

2. Determine the required origin translation from the sign of the intercepts.
3. Mark the cut points on the unit cell edges relative to the chosen origin and join them with straight lines to form the polygon of the planar section.

PHASE 3: ANALYTICAL DERIVATION & CALCULATION STEP-BY-STEP

PHASE 4: PHYSICAL INTERPRETATION & VERIFICATION

1. **Symmetry Invariance:** The planes $(\bar{3}\bar{1}2)$, $(12\bar{3})$, $(\bar{3}\bar{1}\bar{3})$ and $(3\bar{1}3)$ all belong to the same crystallographic family of planes $\{321\}$ or $\{331\}$ in the cubic lattice. Although their geometric orientation differs because of the choice of axes, they all have the **same interplanar spacing** d_{hkl} and the **same planar atomic density** ρ_p.
2. **Orthogonality Property:** In all cases, the normal direction vector of the drawn plane is proportional to the index vector $[h\,k\,l]$, rigorously satisfying crystallographic perpendicularity in cubic lattices [Session 3 Slide 45].

Study notes written from the official course material (Problems T2_CrystStruct.pdf; Problems T2 defects.pdf).
Online version: subjects/aerospace-materials-1/problemas/topic-2-problems.html