



Aluminum Composite Panel

Panel Thickness	Standard	Unit	2mm	3mm	4mm	6mm
Thickness of Aluminium	DIN 1784	mm	0.3	0.3	0.3	0.3
Aluminum thickness deviation	DIN 1784	mm	±0.01	±0.01	±0.01	±0.01
Weight		Kg/m ²	2.92	3.85	4.76	6.75
Tolerance in length	DIN 16927 / ISO 11833-1	mm	- 0 / +2	- 0 / +2	-0/+2	-0/+2
Tolerance in width	DIN 16927 / ISO 11833-1	mm	- 0 / +1.0	- 0 / +1.0	- 0 / +1.0	- 0 / +1.0
Tolerance in thickness	DIN 16927 / ISO 11833-1	mm	± 0.15	± 0.10	± 0.10	± 0.15
Horizontal flatness	DIN ISO 1101	mm	5	3	3	3
Longitudinal roughness	DIN ISO 1101	mm	6	5	5	5
Technical Properties						
Section Modulus W	DIN 53293	cm ³ /m	1.32	1.55	1.85	2.96
Rigidity (Poisson's ratio μ = 0.3) E.J	DIN 53293	kNm²/m	0.97	0.16	0.34	0.86
Alloy	EN 573-3	ENAW	3003			
Temper of Cover Sheets	EN 515		H16/H24			
Modulus of Elasticity	EN 1999 1-1	N/mm ²	70,000			
Tensile Strength of Aluminium	EN 485-2	N/mm ²	R _m ≥ 175			
0.2% Proof Stress	EN 485-2	N/mm ²	R _{p0.2} ≥ 120			
Elongation	EN 485-2	%	A ₅₀ ≥ 3			
Linear Thermal Expansion	EN 1999 1-1	mm/m°C	2.4 at 100°C Temp difference			
Core						
Polyethylene, Typ LD-PE		g/cm ³	0.935			
Surface			Coil Coating			
Lacquering			Fluorocarbon based (PE)			
Thickness of coating		μm	≥19	≥19	≥19	≥19
Gloss (initial value)	ECCA T2	%	20 - 100			
Pencil Hardness	ECCA T4		2H			
Acoustical Properties						
Sound Absorption Factor ά _s	ISO 354		0.05			
Sound Transmission Loss R _W	ISO 717-1	DB	23	25	26	28
Loss Factor d	EN ISO 6721		0.0062	0.0072	0.0087	0.0138
Thermal Properties						
Thermal Resistance R	DIN 52612	m ² K/W	0.0036	0.0069	0.0103	0.0172
Heat Transition Coefficient U	DIN 4108	W/m ² K	5.98	5.65	5.54	5.34
Temperature Range		°C	-50+80			

PIVOT DECORATIVE MATERIALS CO.,LTD.

ADD:Pivot Industrial Park, Huashi, Jiangyin, Jiangsu, China

Tel:0086-510-86218220 E-mail:info@pivotacp.com Web:www.pivotacp.com Fax:0086-510-86218185 Post:214421 www.ibond.cn