Spirulina 3D Printing Paste Recipe

Ingredients:


- **120 ml Spirulina Powder** (Half a level cup)
- **30 ml Potato Starch** (2 level tablespoons)
- **30 ml Extra-fine Semolina** (2 level tablespoons)
- **7.5 ml Methylcellulose** (Half a level tablespoon)
- **120 ml Water** (Half a level cup)

How to measure a level cup:

When measuring, fill each cup or spoon


to the top and level it off using a flat utensil.

Do not compact the powders.



Procedure:

1. Measure all the dry ingredients one by one and add them to a mixing bowl:



2. Use a spatula to mix all the dry ingredients together until they are evenly combined.



3. Add 120 ml of water and mix until you have a thick, smooth paste with no dry powder left.



4. The paste is now ready to be loaded into the 3D printer cartridge.