STAINLESS STEEL PRODUCTS

fully resistant	:	A less than .00035 inches
satisfactorily resistant	:	B .00035- .0035 inches
fairly resistant	:	C .0035 - .010 inches
slightly resistant	:	D.010--.035 inches
not resistant	:	E over .035 inches

substance and condition	temp F	304	316
Lactic acid			
5%	70°	A	A
5%	150°	B	A
10%	boiling	D	B
10%	150°	C	B
lard	70°	A	A
lead	molten	B	B
linseed oil	70°	A	A
Magnesium chloride			
1% & 5% still	70°	A1	A
	hot	C1	B1
magnesium sulphate	cold, hot	A	A
malic acid	cold, hot	B	A
mayonnaise	70°	A1	A
mercuric chloride			
dilute solutions		E1	D1
mercury		A	A
methanol			
(methyl alcohol)		A	A
milk, fresh or sour	hot, cold	A	A
mixed acids			
53% H_2SO_4	cold	A	A
45% HNO_3	cold	A	A
mustard	70°	A1	A1
Naphtha	70°	A	A
naphtha - crude	70°	A	A
nickel chloride			
solution	70°	A1	A1
nickel sulphate	hot, cold	A	A
nitric acid			
5% solution	70°	A	A
20% solution	70°	A	A
50% solution	70°	A	A
50% solution	boiling	A	A
65% solution	boiling	B	B
concentrated	70°	A	A
concentrated	boiling	D	D
Oils, crude	hot, cold	A3	A3
oils, vegetable, mineral	hot, cold	A3	A
oleic, acid	70°	A1	A
oxclic acid			
5%	hot, cold	A	A
10%	70°	A	A
10%	boiling	D	C
Paraffin	hot, cold	A	A
petroleum ether		A	A
phenol		A	A
phosphoric acid			
1 %	70°	A4	A4
5% still	70°	A	A
5% agitated	70°	A	A
5% aerated	70°	A	A
10% still	70°	C	A
10% agitated	70°	C	B
10% aerated	70°	C	B
picric acid	70°	A	A
potassium bichromate	70°	A	A
potassium bromide	70°	B1	A1
potassium carbonate			
1% still	70°	A	A
1% agitated	70°	A	A
1 % aerated	70°	A	A
potassium carbonate	hot	A	A
potassium chlorate		A	A
potassium chloride			
1% still	70°	A1	A1
1% agitated	70°	A	A
1% aerated	70°	A	A

substance and condition	temp F	304	316
5% still	70°	A1	A1
5% agitated	70°	A	A
5% aerated	70°	A	A
	boiling	A	A
potassium ferricyanide			
5%	70°	A	A
potassium ferrocyanide			
5%	70°	A	A
potassium hydroxide			
5% still	70°	A	A
5% agitated	70°	A	A
5% aerated	70°	A	A
27%	boiling	A	A
50%	boiling	B	A
potassium nitrate			
1% still	70°	A	A
1% agitated	70°	A	A
1% aerated	70°	A	A
5% aerated	70°	A	A
5% still & agitated	70°	A	A
potassium nitrate	hot	A	A
potassium oxalate		A	A
potassium permanganate			
5%	70°	A	A
potassium sulphate			
1% still	70°	A	A
1% agitated	70°	A	A
1% aerated	70°	A	A
5% still	70°	A	A
5% agitated	70°	A	A
5% aerated	70°	A	A
	hot	A	A
potassium sulphide			
(salt)		A	A
pyrogallic acid		A	A
Rosin	molten	A	A
Sea water		A1	A1
silver bromide		B1	A1
silver chloride		E	E
silver nitrate		A	A
soap	70°	A	A
sodium acetate-moist		A1	A
sodium bicarbonate			
all concentrations	70°	A	A
5% still	150°	A	A
sodium bisulphate			
solution	70°	A	A
saturated solution	70°	E	
2g + 1gH_2SO_4			
per liter	68°		A
	212°		B
sodium carbonate			
5%	70°	A	A
5%	150°	A	A
sodium chloride			
5% still	70°	A1	A
5% still	150°	A1	A
20% aerated	70°	A1	A
saturated	70°	A1	A
saturated	boiling	B1	A
sodium fluoride			
5% solution		B1	A1
sodium hyroxide		A	A
sodium hypochlorite			
5% still		B1	Al
sodium hyposulphite	70°	A3	A
sodium nitrate	fused	C	B

substance and condition	temp F	304	316
sodium sulphate			
5% still	70°	A	A
all concentrations	70°	A	A
sodium sulphide			
saturated		B1	A
sodium sulphite			
5%	70°	A	A
10%	150°	A	A
sodium thiosulphate			
saturated solution	70°	A	A3
acid fixing bath (hypo)	70°		A
25% solution	70°		A3
	boiling		A3
stearic acid		A	A
sugar juice		A	A
sulphur chloride		E	D
sulphur dioxide			
gas-moist	70°	B	A
gas	575°	A	A
sulphur-dry	molten	A	A
wet		B1	A1
sulphuric acid			
5%	70°	C	B
5%	boiling	E	C
10%	70°	C	B
10%	boiling	E	D
50%	70°	D	C
50%	boiling	E	D
concentrated	70°	A	A
concentrated	boiling	D	D
concentrated	300°	E	E
fuming	70°	C	B
sulphurous acid			
saturated	70°	C	B
saturated 60 lb.			
pressure	250°	C	B
saturated 70/125 lb.			
pressure	310°	C	B
150 lb. pressure	375°	C	B
sulphurous spray	70°	D1	D1
Tannic acid	70°	A	A
	150°	B	A
tin	molten	C	C
trichloracetic acid	70°	E	E
trichlorethylene	70°	A1	
Varnish	70°	A	A
	hot	A	A
Vegetable juices		A	A
vinegar fumes		B	A
vinegar-still	70°	A	A
agitated		A	A
aerated	70°	A	A
Zinc	molten	E	E
zinc chloride			
5% still	70°	A1	A1
	boiling	B1	B1
zinc sulphate			
5%	70°	A	A
saturated	70°	A	A
25%	boiling	A	A

3. May attack when sulphuric acid is present.
4. May attack when hydrochloric acid is present.