


HOT FORMED HOLLOW SECTIONS



SQUARE

Section size D x B	Thickness t	Unit weight M	Section area A	Moment of inertia I	Radius of gyration r	Elastic modulus Z	Plastic modulus S	Torsional J	Constants C	Superficial area per m	Approx. length per tonne
mm	mm	kg/m	cm ²	cm ⁴	cm	cm ³	cm ³	cm ⁴	cm ³	m ²	m
90 x 90	3.6	9.72	12.4	154	3.52	34.1	40.0	237	49.7	0.352	103
	5.0	13.3	16.9	202	3.46	45.0	53.6	315	64.9	0.349	75.2
	6.0	15.7	20.0	234	3.42	51.9	62.7	367	74.4	0.347	63.7
	6.3	16.4	20.9	242	3.41	53.9	65.3	381	77.1	0.346	61.0
	8.0*	20.4	25.9	288	3.33	64.0	79.2	459	90.7	0.343	49.0
100 x 100	4.0	12.0	15.3	234	3.91	46.8	54.9	361	68.2	0.391	83.4
	5.0	14.8	18.9	283	3.87	56.6	67.1	439	81.9	0.389	67.6
	6.0	17.6	22.4	328	3.83	65.6	78.6	512	94.4	0.387	56.8
	6.3	18.4	23.4	341	3.81	68.2	82.0	533	97.9	0.386	54.4
	8.0	22.9	29.1	408	3.74	81.5	99.9	646	116	0.383	43.7
	10.0	27.9	35.5	474	3.65	94.9	119	761	134	0.379	35.9
120 x 120	5.0	18.0	22.9	503	4.69	83.8	98.4	775	122	0.469	55.6
	6.0	21.3	27.2	586	4.64	97.7	116	910	141	0.467	46.9
	6.3	22.3	28.5	610	4.63	102	121	949	147	0.466	44.9
	8.0	27.9	35.5	738	4.56	123	149	1,159	176	0.463	35.9
	10.0	34.2	43.5	870	4.47	145	178	1,381	206	0.459	29.3
	12.5*†	41.6	53.0	1,009	4.36	168	212	1,624	237	0.453	24.0
140 x 140	5.0*	21.1	26.9	814	5.50	116	136	1,251	170	0.549	47.4
	5.6*	23.5	30.0	899	5.48	128	151	1,385	187	0.548	42.6
	6.0	25.1	32.0	954	5.46	136	160	1,473	198	0.547	39.8
	6.3*	26.3	33.5	994	5.45	142	168	1,538	206	0.546	38.0
	7.1*	29.4	37.5	1,099	5.41	157	186	1,706	227	0.545	34.0
	8.0*	32.9	41.9	1,212	5.38	173	207	1,889	249	0.543	30.4
	10.0*	40.4	51.5	1,441	5.29	206	250	2,269	294	0.539	24.8
	12.5*	49.5	63.0	1,691	5.18	242	299	2,695	342	0.533	20.2
150 x 150	5.0	22.7	28.9	1,009	5.91	135	157	1,548	197	0.589	44.1
	6.0	27.0	34.4	1,185	5.87	158	185	1,826	230	0.587	37.0
	6.3	28.3	36.0	1,236	5.86	165	194	1,907	240	0.586	35.4
	8.0	35.4	45.1	1,510	5.78	201	240	2,348	291	0.583	28.3
	10.0	43.6	55.5	1,803	5.70	240	290	2,829	345	0.579	23.0
	12.5	53.4	68.0	2,125	5.59	283	348	3,372	403	0.573	18.8
	16.0	66.4	84.5	2,500	5.44	333	421	4,029	468	0.566	15.1

Notes:

Sizes printed black on grey background are by the Continuous Weld Process. Sizes printed in bold type are by the Hot Finished Seamless Process.

* Size not included in BS 4848 Part 2

† 43C only

Length per tonne rounded up