

EXPLANATORY NOTES

COMPARISON OF EN10025 & BS4360

EN 10025: 1993								BS 4360: 1986					
					Impact Energy (J °C) Nominal Thickness							Impact Energy (J °C) Nominal Thickness	
Grade	Former Grade	Tensile Strength	Min Yield Strength at 16mm N/mm ²	Max Thk for Specified Yield N/mm ²	Temp °C	<150mm -1	>150mm <250mm -1	Grade	Tensile Strength >3mm N/mm ²	Min Yield Strength at 16mm N/mm ²	Max thk Specified Yield N/mm ² (2)	Temp °C	<100mm -3
S185 (4)	Fe 310-0(4)	290/510	185	25	-	-	-	-	-	-	-	-	-
S235 (5)	Fe 360A (5)	340/470	235	250	-	-	-	40A	340/500	235	150	-	-
S235JR (4)	Fe 360B (4)	340/470	235	25	20	27	-	-	-	-	-	-	-
(4)	Fe 360(FU) (4)	340/470	235	25	+20 (6)	27	-	-	-	-	-	-	-
S235JRG2	Fe 360B (FN)	340/470	235	250	+20 (6)	27	23	40B	340/500	235	150	+20 (6)	27
S235JO	Fe 360C	340/470	235	250	0	27	23	40C	340/500	235	150	0	27
S235J2G3	Fe 360D1	340/470	235	250	-20	27	23	40D	340/500	235	150	-20	27
S235J2G4	Fe 360D2	340/470	235	250	-20	27	23	40D	340/500	235	150	-20	27
S275 (5)	Fe 430A (5)	410/560	275	250	-	-	-	43A	430/580	275	150	-	-
S275JR	Fe 430B	410/560	275	250	+20 (6)	27	23	43B	430/580	275	150	+20 (6)	27
S275JO	Fe 430C	410/560	275	250	0	27	23	43C	430/580	275	150	0	27
S275J2G3	Fe 430D1	410/560	275	250	-20	27	23	43D	430/580	275	150	-20	27
S275J2G4	Fe 430D2	410/560	275	250	-20	27	23	43D	430/580	275	150	-20	27
S355 (5)	Fe 510A	490/630	355	250	-	-	-	50A	490/640	355	150	-	-
S355JR	Fe 510B	490/630	355	250	+20 (6)	27	23	50B	490/640	355	150	+20 (6)	27
S355JO	Fe 510C	490/630	355	250	0	27	23	50C	490/640	355	150	0	27
S355J2G3	Fe 510D1	490/630	355	250	-20	27	23	50D	490/640	355	150	-20	27
S355J2G4	Fe 510D2	490/630	355	250	-20	27	23	50D	490/640	355	150	-20	27
S355K2G3	Fe 510DD1	490/630	355	250	-20	40	33	50DD	490/640	355	150	-30	27
S355K2G4	Fe 510DD2	490/630	355	250	-20	40	33	50DD	490/640	355	150	-30	27
E295	Fe 490-2	470/610	295	250	-	-	-	-	-	-	-	-	-
E335	Fe 590-2	570/710	335	250	-	-	-	-	-	-	-	-	-
E360	Fe 690-2	670/830	350	250	-	-	-	-	-	-	-	-	-

- (1) For sections up to and including 100mm only
- (2) For wide flats and Sections up to and including 63mm and 100mm respectively
- (3) For wide flats up to and including 50mm and sections no limit is stated
- (4) Only available up to and including 25mm thick
- (5) The Steel grades S235 (Fe 360A), S275 (Fe 430A), and S355 (Fe 510A) appear only in the English language version (BS EN 10025) as non conflicting additions and do not appear in European versions
- (6) Verification of the specified impact value is only carried out when agreed at time of enquiry and order