

PIPES

TECHNICAL SPECIFICATION REFERENCE -STEEL TUBES AND LIPPED CHANNEL

Classification	Standard Specification		Application	Chemical Requirements (%)					Physical Requirements (%)			
				C	Mn	Si	P	S	Others	Tensile Strength	Yield Strength	Elongation
				max. %	max. %	max. %	max. %	max. %	%	N/mm ²	N/mm ²	%
Circular Hollow Section	BS1387	L	Carbon Steel Tubes for Ordinary Uses, Water Pipes and Structural Purposes	0.20	1.20	--	0.045	0.045	--	320 - 460	195 min.	20 min.
		M										
		H										
	JIS G 3444 /Mfg Standard	STK 290	Carbon Steel Tubes for Structural Purposes (Scaffolding)	--	--	--	0.05	0.05	--	290 min.	--	25 min.
		STK 400		0.25	--	--	0.04	0.04	--	400 min.	235 min.	18 min.
		STK 500		0.30	0.30 - 1.00	0.35	0.04	0.04	--	500 min.	355 min.	10 min.
	JIS G 3445 /Mfg Standard	STKM11A	Carbon Steel Tubes for Machine Structural Purposes	0.12	0.60 max.	0.35	0.04	0.04	--	290 min.	--	30 min.
	JIS G 3452 /Mfg Standard	SGP	Carbon Steel Tubes for Ordinary Uses, Water Pipes and Structural Purposes	--	--	--	0.04	0.04	--	290 min.	--	25 min.
Square and Rectangular Hollow Section	ASTM A500/ Mfg Standard	A	Carbon Steel Tubes for Structural Purposes and Machine Structural Purposes	0.30	--	--	0.05	0.063	Cu (max) = 0.18	310 min.	269 min.	25 min.
		B		0.30	--	--	0.05	0.063	Cu (max) = 0.18	400 min.	317 min.	23 min.
Circular Hollow Section	Mfg Standard	AA	Carbon Steel Tubes for Ordinary Uses	0.20	1.20	--	0.045	0.045	--	250 min.	190 min.	20 min.
Light Gauge Lipped Channel	Mfg Standard		For Civil Engineering	0.25	--	--	0.05	0.05	--	295 min.	--	25 min.
Conduit Pipe	BS 31/ Mfg Standard		For Electrical Wiring	--	--	--	--	--	--	273 - 365	--	15 min.
Window Pipe	Mfg Standard		For Window Usage	--	--	--	--	--	--	--	--	--