

CARBON STEEL PIPES FOR GENERAL STRUCTURAL PURPOSES

LIGHT (AA) (MANUFACTURER STANDARD)

Nominal Size		Outside Diameter		Nominal Wall Thickness		Calculated Weight		
		Minimum	Maximum			Plain Ends		
in	mm	mm	mm	in	mm	kg/m	kg/ft	lb/ft
½	15	21.0	21.4	0.063	1.6	0.739	0.225	0.496
¾	20	26.4	26.9	0.063	1.6	0.982	0.229	0.659
1	25	33.2	33.8	0.069	1.8	1.364	0.416	0.916
1¼	32	41.9	42.3	0.069	1.8	1.739	0.530	1.167
1½	40	47.8	48.4	0.069	1.8	1.994	0.608	1.339
2	50	59.6	60.2	0.069	1.8	2.503	0.763	1.680
2½	65	75.2	76.0	0.072	1.9	3.368	1.026	2.261
3	80	87.9	88.7	0.080	2.1	4.330	1.320	2.907
3½	90	101.1	102.0	0.080	2.1	5.150	1.570	3.460
4	100	112.2	113.2	0.085	2.2	5.917	1.803	3.972
5	125	138.7	140.6	0.150	4.0	12.364	3.768	8.308
6	150	164.1	166.1	0.150	4.0	15.069	4.593	10.117

Wall Thickness Tolerance = -10%

CARBON STEEL CEMENT LINING PIPES (MANUFACTURER STANDARD)

Outside Diameter	Minimum Nominal Wall Thickness	Outside Diameter		Calculated Weight
		Maximum	Minimum	
mm	mm	mm	mm	kg/m
177.3	3.7	179.1	175.5	17.51
	4.1	179.1	175.5	19.22
232.2	4.1	234.5	229.9	25.32