

PIPES

CARBON STEEL PIPES FOR SCAFFOLDING

JIS G 3444/88 (MANUFACTURER STANDARD))

Nominal Size	Standard Specification	Outside Diameter		Wall Thickness	Weight	Reference			
		Min	Max			Cross Sectional Area	Geometrical Moment of Inertia	Modulus of Section	Radius of Gyration of Area
		mm	mm			cm ²	cm ⁴	cm ³	cm
21.7 O/D	STK 290	21.45	21.95	1.20	0.607	0.773	0.407	0.375	0.726
				1.50	0.747	0.952	0.488	0.45	0.716
				1.60	0.793	1.010	0.513	0.473	0.713
				2.00	0.972	1.238	0.607	0.56	0.700
42.7 O/D	STK 400	42.45	42.95	2.30	2.29	2.919	5.97	2.80	1.43
				2.50	2.49	3.157	6.40	3.00	1.42
				2.80	2.76	3.510	7.02	3.29	1.41
48.6 O/D	STK 500	48.35	48.85	2.30	2.63	3.345	8.99	3.70	1.64
				2.50	2.84	3.621	9.65	3.97	1.63
				2.80	3.16	4.029	10.60	4.36	1.62
				3.20	3.58	4.564	11.80	4.86	1.61

Notes:

- 1) When Wall Thickness < 3.0 mm, tolerance = ± 0.3 mm
- 2) When $3.0 \text{ mm} \leq \text{wall thickness} < 12 \text{ mm}$, tolerance = $\pm 10\%$

YICK HOE