

CARBON STEEL PIPES FOR ORDINARY PIPING

JIS G 3452-1968 (SGP)

Nominal Size		Outside Diameter		Thickness		Unit weight (plain end)		Test Pressure	
A	B	mm	in	mm	in	lb/ft	kg/m	kg/cm ²	Psi
6	1/8	10.5	0.413	2.0	0.079	0.282	0.419	25	360
8	¼	13.8	0.543	2.3	0.090	0.438	0.652	25	360
10	3/8	17.3	0.681	2.3	0.090	0.572	0.851	25	360
15	½	21.7	0.854	2.8	0.110	0.88	1.31	25	360
20	¾	27.2	1.071	2.8	0.110	1.13	1.68	25	360
25	1	34.0	1.338	3.2	0.126	1.63	2.43	25	360
32	1¼	42.7	1.681	3.5	0.138	2.27	3.38	25	360
40	1½	48.6	1.913	3.5	0.138	2.61	3.89	25	360
50	2	60.5	2.382	3.8	0.150	3.57	5.31	25	360
65	2½	76.3	3.004	4.2	0.165	5.02	7.47	25	360
80	3	89.1	3.508	4.2	0.165	5.91	8.79	25	360
90	3½	101.6	4.000	4.2	0.165	6.79	10.1	25	360
100	4	114.3	4.500	4.5	0.177	8.2	12.2	25	360
125	5	139.8	5.504	4.5	0.177	10.1	15.0	25	360
150	6	165.2	6.504	5.0	0.197	13.3	19.8	25	360
175	7	190.7	7.508	5.3	0.209	16.3	24.2	25	360
200	8	216.3	8.516	5.8	0.228	20.2	30.1	25	360
225	9	241.8	9.520	6.2	0.244	24.2	36.0	25	360
250	10	267.4	10.528	6.6	0.260	28.5	42.4	25	360
300	12	318.5	12.539	6.9	0.272	35.6	53.0	25	360
350	14	355.6	14.00	7.9	0.311	45.5	67.7	25	360
400	16	406.4	16.00	7.9	0.311	52.1	77.6	25	360
450	18	457.2	18.00	7.9	0.311	58.7	87.5	25	360
500	20	508.0	20.00	7.9	0.311	65.4	97.4	25	360