

PIPES

CARBON STEEL PIPES FOR GENERAL STRUCTURAL PURPOSES

JIS G 3444-1988-STK 290

JIS G 3444-1988-STK 500

JIS G 3444-1988-STK 400

JIS G 3444-1988-STK 540

Outside Diameter	Wall Thickness	Calculated Weight	Cross-Sectional Area	Geometrical Moment of Inertia	Modulus of Section	Radius of Gyration of Area
mm	mm	kg/mm	cm ²	cm ⁴	cm ³	cm
21.7	2.0	0.972	1.238	0.607	0.56	0.70
27.2	2.0	1.24	1.583	1.26	0.93	0.89
	2.3	1.41	1.799	1.41	1.03	0.88
34.0	2.3	1.80	2.291	2.89	1.70	1.12
42.7	2.3	2.29	2.919	5.97	2.80	1.43
	2.5	2.49	3.157	6.40	3.00	1.42
	2.8	2.76	3.510	7.02	3.29	1.41
48.6	2.3	2.63	3.345	8.99	3.70	1.64
	2.5	2.84	3.621	9.65	3.97	1.63
	2.8	3.16	4.029	10.6	4.36	1.62
	3.2	3.58	4.564	11.8	4.86	1.61
60.5	2.3	3.30	4.205	17.8	5.90	2.06
	3.2	4.52	5.760	23.7	7.84	2.03
	4.0	5.57	7.100	28.5	9.41	2.00
76.3	2.8	5.08	6.465	43.7	11.5	2.60
	3.2	5.77	7.349	49.2	12.9	2.59
	4.0	7.13	9.085	59.5	15.6	2.56
89.1	2.8	5.96	7.591	70.7	15.9	3.05
	3.2	6.78	8.636	79.8	17.9	3.04
	4.0	8.39	10.69	97.0	21.8	3.01
101.6	3.2	7.76	9.892	120	23.6	3.48
	4.0	9.63	12.26	146	28.8	3.45
	5.0	11.90	15.17	177	34.9	3.42
114.3	3.2	8.77	11.17	172	30.2	3.93
	3.6	9.83	12.52	192	33.6	3.92
	4.5	12.20	15.52	234	41.0	3.89
	5.6	15.00	19.12	283	49.6	3.85
139.8	3.6	12.10	15.40	357	51.1	4.82
	4.0	13.40	17.07	394	56.3	4.80
	4.5	15.00	19.13	438	62.7	4.79
	6.0	19.80	25.22	566	80.9	4.74
165.2	4.5	17.80	22.72	734	88.9	5.68
	5.0	19.80	25.16	808	97.8	5.67
	6.0	23.60	30.01	952	115	5.63
	7.0	27.30	34.79	1,090	132	5.60
190.7	4.5	20.70	26.32	1,140	120	6.59
	5.0	22.90	29.17	1,260	132	6.57
	6.0	27.30	34.82	1,490	156	6.53
	7.0	31.70	40.40	1,710	179	6.50
216.3	4.5	23.50	29.94	1,680	155	7.49
	6.0	31.10	39.64	2,190	203	7.44
	7.0	36.10	46.03	2,520	233	7.40

Applicable Tolerances:

Thickness	Under 3 mm ± 0.3mm
	3 mm and over to 8 mm ± 10%
Outside Diameter	Under 50 mm ± 0.25 mm
	50 mm or over ± 0.5%