

TECHNICAL SPECIFICATION REFERENCE - STEEL PLATES, SHEETS

Excerpts from JIS G 3131, JIS G 3101, JIS G 3302 & JIS G 3141 Specifications

Classification	Specification	Grade	Chemical Composition					Tensile Test					Bend Test ^{*2}	
			C max. %	Mn max. %	Si max. %	P max. %	S max. %	Tensile Strength N/mm ²	Yield Strength N/mm ²	Elongation			Bending Angle	Bending Radius
										Test PC	Thickness	%		
Hot Rolled Steel Plates and Sheets & Chequered Plates	JIS G 3131	SPHC	0.15	0.60	--	0.05	0.05	270 min.	--	No.5	1.2mm & over, up to 1.6 mm	27 min.	180°	Flat on itself 0.5t
											1.6mm & over, up to 3.2 mm	29 min.		
											3.2mm & over	31 min.		
	JIS G 3101	SS330	--	--	--	0.05	0.05	330 - 430	205 min.	No.5	5 mm & under	26 min.	180°	0.5t
										No.1A	over 5mm- 16mm	21 min.		
	JIS G 3101	SS400	--	--	--	0.05	0.05	400 - 510	245 min.	No.5	5 mm & under	21 min.	180°	1.5t
										No.1A	over 5mm- 16mm	17 min.		
Galvanised Steel Sheets	JIS G 3302	SGCC	--	--	--	--	--	270 min.	205 min.	--	Up to 1.6 mm	--	180°	t ^{*1} t ^{*1} 2t ^{*1}
											1.6 mm & over, up to 3.0 mm			
											3.0 mm & over			
	JIS G 3302	SGHC	--	--	--	--	--	270 min.	205 min.	--	Up to 1.6 mm	--	180°	t ^{*1} t ^{*1} 2t ^{*1}
											1.6 mm & over, Up to 3.0 mm			
											3.0 mm & over			
Cold Rolled Steel Sheets	JIS G 3141	SPCC	0.12	0.50	--	0.04	0.045	270 min.	--	No. 5	0.6 mm & over, up to 1.0 mm	36 min.	180°	Flat on itself
											1.0 mm & over, up to 1.6 mm	37 min.		
											1.6mm & over, up to 2.5 mm	38 min.		
											2.5 mm & over	39 min.		

Notes:

*1 - Up to grade Z27 maximum

*2 - Bend Test test piece No. 3

t - Thickness