

STAINLESS STEEL SHEETS & PLATES

SPECIFICATIONS: MECHANICAL PROPERTIES OF STAINLESS STEEL SHEETS

Type of Structure	Type of Composition	Corresponding Designation			Mechanical Properties							
					Tensile Test			Hardness Test		Bend Test 180° Radius (t, min)		
		Tensile Strength min.		Yield Strength min.	Elongation %, min.							
JIS	AISI	DIN	kg/mm²	psi	kg/mm²	psi	JIS No.13 Specimen	Rockwell B Scale max.	Vickers Hardness max.			
Austenite	17Cr-5Ni-7Mn	SUS 201	201	--	65	93,000	25	35,800	40	100	253	--
	18Cr-6Ni-10Mn	SUS 202	202	--	60	85,500	25	35,800	40	95	218	--
	17Cr-7Ni	SUS 301	301	4310	53	75,800	21	30,000	40	90	200	--
	18Cr-8Ni-high C	SUS 302	302	4300	53	75,800	21	30,000	40	90	200	--
	18Cr-8Ni	SUS 304	304	4301	53	75,800	21	30,000	40	90	200	--
	18Cr-8Ni -extra -low C	SUS 304L	304L	4306	49	69,500	18	25,500	40	90	200	--
	18Cr-12Ni	SUS 305	305	3955	49	69,500	18	25,500	40	90	200	--
	23Cr-12Ni	SUS 309S	309S	4845	53	75,800	21	30,000	40	90	200	--
	25Cr-20Ni	SUS 310S	310S	--	53	75,800	21	30,000	40	90	200	--
	18Cr-12Ni-2.5Mo	SUS 316	316	4401	53	75,800	21	30,000	40	90	200	--
	18Cr-12Ni-7.5 Mo-extra-low C	SUS 316L	316L	4404	49	69,500	18	25,500	40	90	200	--
	18Cr-12Ni-2Mo -2Cu	SUS 316J1		4505	53	75,800	21	30,000	40	90	200	--
	18Cr-13Ni-3.5Mo	SUS 317	317	4402	53	75,800	21	30,000	40	90	200	--
	18Cr-13Ni-3.5 Mo-extra- low C	SUS 317L	317L	--	49	69,500	18	25,800	40	90	200	--
	18Cr-8Ni-Ti	SUS 321	321	4541	53	75,800	21	30,000	40	90	200	--
18Cr-9Ni-Nb	SUS 347	347	4550	53	75,800	21	30,000	40	90	200	--	
Ferrite	13Cr-Al	SUS 405	405	4002	42	60,000	18	25,500	20	88	200	t < 8.05 t
	16Cr	SUS 429	429	4009	46	65,800	21	30,000	22	88	200	1.0 t
	18Cr	SUS 430	430	4016	46	65,800	21	30,000	22	88	200	1.0 t
	18Cr-Mo	SUS 434	434	4113	46	65,800	21	30,000	22	88	200	1.0 t
Martensite	13Cr-low Si	SUS 403	403	4024	45	64,000	21	30,000	20	88	200	1.0 t
	13Cr	SUS 410	410	4000	45	64,000	21	30,000	20	88	200	1.0 t
	13Cr-high C	SUS 420J2	420	4021	55	78,500	23	32,750	18	93	210	--
	18Cr-high C	SUS 440A	440A	--	60	85,500	25	35,800	15	97	230	--
Precipitation Hardened	17Cr-7Ni-1Al	SUS 631	631	--	105	148,000	39	55,500	20	92	200	--