

STAINLESS STEEL SHEETS & PLATES

MAIN USES

JIS Designation	AISI Designation	Characteristics and Main Uses
SUS 410	410	The most common grade of economical 13 Cr steels. In the annealed condition, this grade may be drawn or formed. Used for machine structures, home appliances, etc.
SUS 403	403	Suited for steam turbine blades, jet engines, compressor blades and other applications involving high stresses.
SUS 405	405	Possesses corrosion resistance equivalent to that of 13 Cr steel. Used in applications involving welding. Machine structures, food-processing machinery, chemical equipment, etc.
SUS 420 J2	420	High carbon content results in high abrasion resistance. Greater hardness may be obtained by heat treatment. Used for cutlery, machine parts, etc.
SUS 434	434	Designed to resist atmospheric corrosion especially for use as automotive trim. Used for wheel covers, hub caps, grilles, mouldings, etc.
SUS 430	430	The most common and widely used of the ferritic grades. This steel may be drawn or formed and has high corrosion resistance. Used for office and kitchen equipment, buildings, automobiles, etc.
SUS 301	301	This grade can be cold worked to very high strength levels. Corrosion resistance is somewhat inferior to SUS 304. Used for rolling stock, automobiles, home appliances, etc.
SUS 302	302	More resistant to corrosion than SUS 301. Suited for oil, chemical, paper and food-processing machinery, dairy installations, buildings, kitchen equipment and utensils, etc.
SUS 304	304	Slightly more resistant to general corrosion than SUS 302. Suited for the same range of applications as SUS 302.
SUS 304L	304L	A special SUS 304 grade for use where carbide precipitation after welding is undesirable. Used for chemical and petrochemical equipment, nuclear reactor equipment, oil-refining equipment, etc.
SUS 321	321	Suited for use in a 500° to 850°C temperature range in which carbides tend to precipitate and in applications where stress relieving (or annealing) is not feasible. Used in the chemical industry, etc.
SUS 316	316	High resistant to such reducing acids as sulphuric, sulphurous, acetic and hydrochloric acids. Also, high creep strength at elevated temperatures. Used in applications in the paper, textile, and chemical industries.
SUS 316L	316L	A special SUS 316 grade intended for use where carbide precipitation after welding is undesirable.
SUS 347	347	Suited for the same applications as SUS 321. Widely used for the construction of manufacturing equipment involving welding.