

STAINLESS STEEL SHEETS & PLATES

FINISHES

Finish Designation	Finishing Method and Degree of Finish
No. 1	Hot-rolled, annealed and descaled. Generally used in industrial applications, where heat or corrosion resistance is required but surface smoothness is not particularly important.
No. 2D	Dull, smooth finish produced by cold rolling, annealing and pickling. Steel is soft and has a silver white surface, suited for deep drawing as well as general uses.
No. 2B	Bright, smooth cold-rolled finish obtained by skinpass rolling of No. 2D. Specified for general use.
No. 3	Intermediate polished finish obtained with rather coarse abrasives (#100 to #120 mesh). A higher luster can be attained by further polishing after fabrication.
No. 4	A standard polished finish produced with finer abrasives (#150 to #180 mesh). Widely specified for restaurant and kitchen equipment and dairy processing equipment.
#240	Polish finish of about #240. Used when finer finish than No. 4 finish is desired such as equipment for restaurants and household kitchens.
#320	Polishing finish of about #320.
#400	High luster finish produced by polishing No. 2B first with #400 buffing iron and then with buffing cloth. Suited for general use.
H.L.	Special polished finish having continuous lines produced with abrasives of an appropriate grain size. Mainly used in architectural applications.
BA	Highly reflective finish produced by cold rolling, bright annealing and-temper rolling. Used where a lustrous surface is specially required.

Note:

Upon request, strip surface protection is provided such as bonding of vinyl sheets or vinyl coating.

YICK HOE