

STAINLESS STEEL ANGLES & FLATS

Stainless Steel Angles and Flats are produced by hot-rolling.

After fully annealed, they are subjected to special chemical treatment for descaling, which gives the products the following advantages:

1. Clean and silvery coloured surface.
2. Smooth and tight skinned surface by this descaling process, which enables to achieve fine surface finish by polishing.
3. Excellent corrosion resistance and bending quality by full annealing.

Hot rolled stainless steel angles and flats are superior to cold formed products with regard to minimum internal stress, better corrosion resistance and lower cost.

For applications where the corrosion resistance after welding is essential, Extra Low Carbon Stainless Steel Angles and Flats (Ex. AISI 304 L, 316 L) is particularly recommended.

CHEMICAL COMPOSITION AISI, ASTM A276-78

Type	C max.	Mn max.	P max.	S max.	Si max.	Cr	Ni	Mo	Ti
302	0.15	2.0	0.045	0.03	1.0	17.0 - 19.0	8.0 - 10.0	--	
304	0.08	2.0	0.045	0.03	1.0	18.0 - 20.0	8.0 - 10.5	--	
304L	0.03	2.0	0.045	0.03	1.0	18.0 - 20.0	8.0 - 12.0	--	
316	0.08	2.0	0.045	0.03	1.0	16.0 - 18.0	10.0 - 14.0	2.0 - 3.0	
316L	0.03	2.0	0.045	0.03	1.0	16.0 - 18.0	10.0 - 14.0	2.0 - 3.0	
321	0.08	2.0	0.045	0.03	1.0	17.0 - 19.0	9.0 - 12.0	--	5 x C min.
430	0.12	1.0	0.040	0.03	1.0	16.0 - 18.0	--	--	