

STAINLESS STEEL BARS

ROUND BARS

Type Number	UNS Number	Equivalent to			Chemical Composition, %								Other Elements
		JIS	BS	DIN	C	Mn	P	S	Si	Cr	Ni	Mo	
201	(S20100)	SUS201	--	--	0.15	5.50 ~ 7.50	0.06	0.03	1.00	16.00 ~ 18.00	3.50 ~ 5.50	--	N 0.25
202	(S20200)	SUS202	284S16	--	0.15	7.50 ~ 10.00	0.06	0.03	1.00	17.00 ~ 19.00	4.00 ~ 6.00	--	N 0.25
205	(S20500)	--	--	--	0.12 ~ 0.25	14.00 ~ 15.50	0.06	0.03	1.00	16.50 ~ 18.00	1.00 ~ 1.75	--	N 0.32 / 0.40
301	(S30100)	SUS301	301S21	4310	0.15	2.00	0.045	0.03	1.00	16.00 ~ 18.00	6.00 ~ 8.00	--	
302	(S30200)	SUS302	302S25	4300	0.15	2.00	0.045	0.03	1.00	17.00 ~ 19.00	8.00 ~ 10.00	--	
302B	(S30215)	SUS302B	--	--	0.15	2.00	0.045	0.03	2.00 ~ 3.00*	17.00 ~ 19.00	8.00 ~ 10.00	--	
303	(S30300)	SUS303	303S21	4305	0.15	2.00	0.20	0.15	1.00	17.00 ~ 19.00	8.00 ~ 10.00	0.60	
303Se	(S30323)	SUS303Se	303S41	--	0.15	2.00	0.20	0.06	1.00	17.00 ~ 19.00	8.00 ~ 10.00	--	Se 0.15 min.
304	(S30400)	SUS304	304S15	4301	0.08	2.00	0.045	0.03	1.00	18.00 ~ 20.00	8.00 ~ 10.50	--	
304L	(S30403)	SUS304L	304S12	4306	0.03	2.00	0.045	0.03	1.00	18.00 ~ 20.00	8.00 ~ 12.00	--	
	(S30430)	--	--	--	0.08	2.00	0.045	0.03	1.00	17.00 ~ 19.00	8.00 ~ 10.00	--	Cu 3.00/4.00
304N	(S30451)	SUS304N1	--	--	0.08	2.00	0.045	0.03	1.00	18.00 ~ 20.00	8.00 ~ 10.00	--	N 0.10/0.16
305	(S30500)	SUS305	305S19	--	0.12	2.00	0.045	0.03	1.00	17.00 ~ 19.00	10.50 ~ 13.00	--	
308	(S30800)	SUS308	305S19	--	0.08	2.00	0.045	0.03	1.00	19.00 ~ 21.00	10.00 ~ 12.00	--	
309	(S30900)	SUH309	309S24	--	0.20	2.00	0.045	0.03	1.00	22.00 ~ 24.00	12.00 ~ 15.00	--	
309S	(S30908)	SUS309S	309S24	--	0.08	2.00	0.045	0.03	1.00	22.00 ~ 24.00	12.00 ~ 15.00	--	
310	(S31000)	SUH310	310S24	--	0.25	2.00	0.045	0.03	1.50	24.00 ~ 26.00	19.00 ~ 22.00	--	
310S	(S31008)	SUS310S	310S24	4845	0.08	2.00	0.045	0.03	1.50	24.00 ~ 26.00	19.00 ~ 22.00	--	
314	(S31400)	--	--	--	0.25	2.00	0.045	0.03	1.50 ~ 3.00	23.00 ~ 26.00	19.00 ~ 22.00	--	
316	(S31600)	SUS316	316S16	4401	0.08	2.00	0.045	0.03	1.00	16.00 ~ 18.00	10.00 ~ 14.00	2.00 ~ 3.00	
316F	(S31620)	--	--	--	0.08	2.00	0.20	0.10	1.00	16.00 ~ 18.00	10.00 ~ 14.00	1.75 ~ 2.50	
316L	(S31603)	SUS316L	316S16	4402	0.03	2.00	0.045	0.03	1.00	16.00 ~ 18.00	10.00 ~ 14.00	2.00 ~ 3.00	

Note:

- * May be added at the manufacturer's discretion.
- Products excluded from the above table are also available upon request.