

STAINLESS STEEL BARS

ROUND BARS

Type Number	UNS Number	Equivalent to			Chemical Composition, %								Other Elements
		JIS	BS	DIN	C	Mn	P	S	Si	Cr	Ni	Mo	
430F	(S43020)	SUS430F	--	4104	0.12	1.25	0.06	0.15	1.00	16.00 ~ 18.00	--	0.60*	
430FSe	(S43023)	--	--	--	0.12	1.25	0.06	0.06	1.00	16.00 ~ 18.00	--	--	Se 0.15 max.
431	(S43100)	SUS431	431S29	4037	0.20	1.00	0.04	0.03	1.00	15.00 ~ 17.00	1.25 ~ 2.50	--	
434	(S43400)	SUS434	434S19	4113	0.12	1.00	0.04	0.03	1.00	16.00 ~ 18.00		0.75 ~ 1.25	
436	(S43600)	--	--	--	0.12	1.00	0.04	0.03	1.00	16.00 ~ 18.00		0.75 ~ 1.25	Cb + Ta 5 x C min.
440A	(S44002)	SUS440A	--	--	0.60~ 0.75	1.00	0.04	0.03	1.00	16.00 ~ 18.00		0.75	
440B	(S44003)	SUS440B	--	--	0.75~ 0.95	1.00	0.04	0.03	1.00	16.00 ~ 18.00		0.75	
440C	(S44004)	SUS440C	--	--	0.95~ 1.20	1.00	0.04	0.03	1.00	16.00 ~ 18.00		0.75	
442	(S44200)	--	--	--	0.20	1.00	0.04	0.03	1.00	18.00 ~ 23.00			
446	(S44600)	SUH446	--	--	0.20	1.50	0.04	0.03	1.00	23.00 ~ 27.00			N0.25
501	(S50100)	--	--	--	0.10	1.00	0.04	0.03	1.00	4.00 ~ 6.00		0.40 ~ 0.65	
502	(S50200)	--	--	--	0.10	1.00	0.04	0.03	1.00	4.00 ~ 6.00		0.40 ~ 0.65	
	(S13800)	--	--	--	0.05	0.10	0.01	0.008	0.10	12.25 ~ 13.25	7.50 ~ 8.50	2.00 ~ 2.50	Al 0.09/1.35 N 0.01
	(S15500)	--	--	--	0.07	1.00	0.04	0.03	1.00	14.00 ~ 15.00	3.50 ~ 5.50	--	Cu 3.00/5.00 Cb + Ta 0.15/0.45
	(S17400)	SUS630	--	--	0.07	1.00	0.04	0.03	1.00	15.50 ~ 17.50	3.00 ~ 5.00	--	Cu 3.00/5.00 Cb + Ta 0.15/0.45
	(S17700)	SUS631	--	--	0.09	1.00	0.04	0.04	1.00	16.00 ~ 18.00	6.50 ~ 7.75	--	Al 0.75/1.50
	(K66286)	SUH660	--	--	0.08	2.00	0.04	0.03	1.00	13.50 ~ 16.00	24.00 ~ 17.00	1.00 ~ 1.50	Ti 1.90/2.35, Al 0.35 V 0.1/0.5, B 0.001/0.01

Note:

- * May be added at the manufacturer's discretion.
- Products excluded from the above table are also available upon request.