

STAINLESS STEEL WELDED TUBINGS

ROUND TUBING

TABLE OF UNIT WEIGHT

Outside diameter		Type	Wall Thickness (mm)																			
			0.5		0.6		0.7		0.8		1.0		1.2		1.5		2.0		2.5		3.0	
			kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'	kg/m	kg/20'
1/2	12.7	AISI 304	0.152	0.927	0.181	1.10	0.209	1.27	0.237	1.44	0.291	1.77	0.344	2.10	0.418	2.55						
		AISI 430	0.148	0.902	0.176	1.07	0.203	1.24	0.203	1.40	0.283	1.73	0.334	2.04	0.406	2.47						
5/8	15.9	AISI 304	0.192	1.17	0.229	1.40	0.265	1.62	0.301	1.83	0.371	2.26	0.439	2.68	0.538	3.28						
		AISI 430	0.186	1.13	0.222	1.35	0.257	1.57	0.292	1.78	0.36	2.19	0.427	2.60	0.522	3.18						
	16	AISI 304	0.193	1.18	0.23	1.40	0.267	1.63	0.303	1.85	0.374	2.28	0.442	2.69	0.542	3.30						
		AISI 430	0.187	1.14	0.224	1.37	0.259	1.58	0.294	1.79	0.363	2.21	0.43	2.62	0.562	3.21						
3/4	19.1	AISI 304	0.232	1.41	0.277	1.69	0.321	1.96	0.365	2.23	0.451	2.75	0.533	3.26	0.658	4.01						
		AISI 430	0.225	1.37	0.269	1.64	0.321	1.90	0.354	2.16	0.438	2.67	0.52	3.17	0.639	3.90						
7/8	22.2	AISI 304			0.323	1.97	0.375	2.29	0.426	2.60	0.528	3.22	0.628	3.83	0.773	4.71	1.01	6.16				
		AISI 430			0.314	1.91	0.364	2.33	0.414	2.52	0.513	3.13	0.61	3.72	0.751	4.58	0.977	5.96				
	25	AISI 304			0.365	2.23	0.429	2.62	0.482	2.94	0.598	3.65	0.711	4.33	0.878	5.35	1.15	7.01				
		AISI 430			0.354	2.16	0.411	2.51	0.468	2.85	0.581	3.54	0.691	4.21	0.853	5.20	1.11	6.77				
1	25.4	AISI 304			0.371	2.26	0.431	2.63	0.49	2.99	0.608	3.71	0.723	4.41	0.893	5.44	1.17	7.13				
		AISI 430			0.36	2.19	0.417	2.54	0.476	2.90	0.59	3.60	0.702	4.28	0.867	5.29	1.13	6.89				
1 1/8	28.6	AISI 304			0.418	2.55	0.486	2.96	0.554	3.38	0.687	4.19	0.819	4.99	1.01	6.16	1.32	8.05				
		AISI 430			0.406	2.47	0.472	2.88	0.538	3.28	0.668	4.07	0.795	4.85	0.983	5.99	1.29	7.86				
1 1/4	31.8	AISI 304					0.542	3.30	0.618	3.77	0.767	4.68	0.915	5.58	1.13	6.89	1.48	9.02	1.82	11.1	2.15	13.1
		AISI 430					0.527	3.21	0.60	3.66	0.745	4.54	0.888	5.41	1.10	6.71	1.44	8.78	1.77	10.8	2.09	12.7
	32	AISI 304					0.546	3.33	0.622	3.79	0.772	4.71	0.921	5.61	1.14	6.95	1.49	9.08	1.84	11.2	2.17	13.2
		AISI 430					0.53	3.23	0.604	3.68	0.75	4.57	0.894	5.45	1.11	6.77	1.45	8.84	1.78	10.9	2.10	19.8
1 1/2	38.1	AISI 304					0.652	3.97	0.743	4.53	0.924	5.63	1.10	6.71	1.37	8.35	1.80	11.0	2.22	13.5	2.62	16.0
		AISI 430					0.633	3.86	0.722	4.40	0.897	5.47	1.07	6.52	1.33	8.11	1.75	10.7	2.15	13.1	2.55	15.3
1 5/8	41.3	AISI 304							0.807	4.92	1.00	6.10	1.20	7.32	1.49	9.08	1.96	11.9	2.42	14.8	2.86	17.4
		AISI 430							0.784	4.78	0.974	5.94	1.16	7.07	1.44	8.78	1.90	11.6	2.35	14.3	2.78	16.9
1 3/4	44.5	AISI 304							0.871	5.31	1.08	6.58	1.29	7.86	1.61	9.81	2.12	12.9	2.62	16.0	3.10	18.9
		AISI 430							0.846	5.16	1.05	6.40	1.26	7.68	1.56	9.51	2.06	12.6	2.54	15.5	3.01	18.3
	45	AISI 304							0.881	5.37	1.10	6.71	1.31	7.99	1.63	9.94	2.14	13.0	2.65	16.2	3.14	19.1
		AISI 430							0.855	5.21	1.06	6.46	1.27	7.74	1.58	9.63	2.08	12.7	2.57	15.7	3.05	18.6
1.9	48.3	AISI 304							0.947	5.77	1.18	7.19	1.41	8.60	1.75	10.7	2.31	14.1	2.85	17.4	3.39	20.7
		AISI 430							0.92	5.61	1.14	6.95	1.37	8.35	1.70	10.4	2.24	13.7	2.77	16.9	3.29	20.1
	50	AISI 304									1.22	7.44	1.46	8.90	1.81	11.0	2.39	14.6	2.96	18.0	3.51	21.4
		AISI 430									1.19	7.25	1.42	8.66	1.76	10.7	2.32	14.1	2.87	17.5	3.41	20.8
2	50.8	AISI 304									1.24	7.56	1.48	9.02	1.84	11.2	2.43	14.8	3.01	18.3	3.57	21.8
		AISI 430									1.20	7.32	1.44	8.78	1.79	10.9	2.36	14.4	2.92	17.8	3.47	21.2
	60.8	AISI 304											1.77	10.8	2.20	13.4	2.91	17.7	3.61	22.0	4.30	26.2
		AISI 430											1.72	10.5	2.14	13.0	2.83	17.3	3.51	21.4	4.17	25.4
2 1/2	63.5	AISI 304											1.86	11.3	2.32	14.1	3.06	18.7	3.80	23.2	4.52	27.6
		AISI 430											1.81	11.0	2.25	13.7	2.98	18.2	3.69	22.5	4.39	26.8
3	76.2	AISI 304											2.24	13.7	2.79	17.0	3.70	22.6	4.59	28.0	5.47	33.3
		AISI 430											2.18	13.3	2.71	16.5	3.59	21.9	4.46	27.2	5.31	32.4