

STAINLESS STEEL PIPES

Symbol		Chemical Composition (%)								
JIS	ASTM	C	Si	Mn	P	S	Ni	Cr	Mo	Others
SUS 304TP SUS 304TB		≤0.08	≤1.00	≤2.00	≤0.04	≤0.03	8.00~ 11.00	18.00~ 20.00	--	
	TP 304	≤0.08	≤0.75	≤2.00	≤0.04	≤0.03	8.00~ 11.00	18.00~ 20.00	--	
SUS 304LTP SUS 304LTB		≤0.03	≤1.00	≤2.00	≤0.04	≤0.03	9.00~ 13.00	18.00~ 20.00	--	
	TP 304L	≤0.035*	≤0.75	≤2.00	≤0.04	≤0.03	8.00~ 13.00	18.00 ~ 20.00	--	
SUS 321TP SUS 321TB		≤0.08	≤1.00	≤2.00	≤0.04	≤0.03	9.00~ 13.00	17.00~ 19.00	--	Ti 5 x C% min.
	TP 321	≤0.08	≤0.75	≤2.00	≤0.04	≤0.03	9.00~ 13.00	17.00~ 19.00	--	Ti 5 x C% ~ 0.60
SUS 316TP SUS 316TB		≤0.08	≤1.00	≤2.00	≤0.04	≤0.03	10.00~ 14.00	16.00~ 18.00	2.00~ 3.00	
	TP 316	≤0.08	≤0.75	≤2.00	≤0.04	≤0.03	11.00~ 14.00	16.00~ 18.00	2.00~ 3.00	
SUS 316LTP SUS 316LTB		≤0.03	≤1.00	≤2.00	≤0.04	≤0.03	12.00~ 16.00	16.00~ 18.00	2.00~ 3.00	
	TP 316L	≤0.035*	≤0.75	≤2.00	≤0.04	≤0.03	10.00~ 15.00	16.00~ 18.00	2.00~ 3.00	
SUS 309STP SUS 309STB		≤0.15	≤1.00	≤2.00	≤0.04	≤0.03	12.00~ 15.00	22.00~ 24.00	--	
	TP 309	≤0.15	≤0.75	≤2.00	≤0.04	≤0.03	12.00~ 15.00	22.00~ 24.00	--	
SUS 310STP SUS 310STB		≤0.15	≤1.50	≤2.00	≤0.04	≤0.03	19.00~ 22.00	24.00~ 26.00	--	
	TP 310	≤0.15	≤0.75	≤2.00	≤0.04	≤0.03	19.00~ 22.00	24.00~ 26.00	--	
SUS 321HTP SUS 321HTB		0.04 ~ 0.10	≤0.75	≤2.00	≤0.03	≤0.03	9.00~ 13.00	17.00~ 20.00	--	Ti 4 x C% ~ 0.60
	TP 321H	0.04 ~ 0.10	≤0.75	≤2.00	≤0.04	≤0.03	9.00~ 13.00	17.00~ 20.00	--	Ti 4 x C% ~ 0.60

Note:

- The above chemical composition shall be applied even when product analysis is requested by the purchasers. However, the carbon content of SUS 340LTP/LTB and SUS 316 LTP/LTB shall be 0.035% or less.
- Those with an asterisk (*) having either a small diameter (i.e., outside diameter less than 0.5 in or 12.70 mm) or a thin wall (i.e., average wall thickness less than 0.049 in or 12.40 mm) or minimum wall thickness (less than 0.044 in or 1.12 mm) and requiring several drawings, shall have carbon content of 0.04% or less.