

PRE-HARDEN & TEMPERED ALLOY STEEL

ALLOY STEEL KS D3708 D3709, JIS G4102 G4103

KS JIS	AISI	Chemical Composition %							Mechanical Properties						
		C	Si	Mn	P	S	Ni	Cr	Mo	YP kg/mm ²	TS kg/mm ²	EL %	RA %	Impact charpy	Hardness HB
SNC415		.12/.18	.15/.35	.35/.65	≤.030	≤.030	2.00/2.50	.20/.50	-	-	≤80	≥17	≥45	≥9	235/341
SNC815		.12/.18	.15/.35	.35/.65	≤.030	≤.030	3.00/3.50	.70/1.00	-	-	≤100	≥12	≥45	≥8	285/388
SNC631		.27/.35	.15/.35	.35/.65	≤.030	≤.030	2.50/3.00	.60/1.00	-	≥70	≥85	≥18	≥50	≥12	248/302
SNC236		.32/.40	.15/.35	.35/.65	≤.030	≤.030	2.50/3.00	.60/1.00	-	≥70	≥85	≥18	≥50	≥12	248/302
	3135	.33/.38	.20/.35	.60/.80	≤.040	≤.040	1.10/1.40	.55/.75	-						
SNC836		.32/.40	.15/.35	.35/.65	≤.030	≤.030	3.00/3.50	.60/1.00	-	≥80	≥95	≥19	≥49	≥8	269/321
SNCM415		.12/.18	.15/.35	.40/.70	≤.030	≤.030	1.60/2.00	.40/.65	.15/.30	-	≥90	≥16	≥45	≥7	255/341
SNCM815	.12/.18	.15/.35	.30/.60	≤.030	≤.030	4.00/4.52	.70/1.00	.15/.30	-	≥110	≥12	≥40	≥7	311/375	
SNCM616		.13/.20	.15/.35	.80/1.20	≤.030	≤.030	2.80/3.20	1.40/1.80	.40/.60	-	≥120	≥14	≥40	≥8	341/415
SNCM220		.17/.23	.15/.35	.60/.90	≤.030	≤.030	.40/.70	.40/.60	.15/.30	-	≥85	≥17	≥40	≥6	248/341
SNCM420		.17/.23	.13/.35	.40/.70	≤.030	≤.030	1.60/2.00	.40/.65	.15/.30	-	≥100	≥15	≥40	≥7	293/375
	4320	.17/.22	.15/.30	.45/.65	≤.035	≤.040	1.65/2.00	.40/.60	.20/.30						
SNCM625		.20/.30	.15/.35	.35/.60	≤.030	≤.030	3.00/3.50	1.00/1.50	.15/.30	≥85	≥95	≥18	≥50	≥8	269/321
SNCM630		.25/.35	.15/.35	.35/.60	≤.030	≤.030	2.50/3.50	2.50/3.50	.50/.70	≥90	≥110	≥15	≥45	≥8	302/352
SNCM431		.27/.35	.15/.35	.60/.90	≤.030	≤.030	1.60/2.00	.60/1.00	.15/.30	≥70	≥85	≥20	≥55	≥10	248/302
	4337	.35/.40	.20/.35	.60/.90	≤.040	≤.040	1.65/2.00	.70/.90	.20/.30						
SNCM439		.36/.43	.15/.35	.60/.90	≤.030	≤.030	1.60/2.00	.60/1.00	.15/.30	≥90	≥100	≥16	≥45	≥7	293/352
	4340	.38/.43	.15/.30	.60/.80	≤.035	≤.030	1.65/2.00	.70/.90	.20/.30						
SNCM240		.38/.43	.15/.35	.70/1.00	≤.030	≤.030	.40/.70	.40/.65	.15/.30	≥80	≥90	≥17	≥50	≥7	255/311

YICK HOE