

COLD FINISHED STEEL BAR

FREE CUTTING STEEL KS D3567, JIS G4804

KS JIS	AISI	Chemical Composition %						Mechanical Properties					
		C	Si	Mn	P	S	Pb	YP	TS	EL	RA	Impact	Hardness
								kg/mm ²	kg/mm ²	%	%	charpy	HB
SUM11		.08/.13	-	.30/.60	≤.04	.08/.13	-						
	1109	.08/.13	-	.60/.90	≤.04	.08/.13	-						
SUM12		.08/.13	-	.60/.90	≤.04	.08/.13	-						
SUM32		.12/.20	-	.60/1.10	≤.04	.10/.20	-						
SUM31		.14/.20	-	1.00/1.30	≤.04	.08/.13	-						
	1117	.14/.20	-	1.00/1.30	≤.04	.08/.13	-	28.4	43.7	32.8	58	69	121
SUM41		.32/.39	-	1.35/1.65	≤.04	.08/.13	-						
	1137	.32/.39	-	1.35/1.65	≤.04	.08/.13	-	35.1	59.5	26.8	53.9	36.8	174
SUM42		.37/.45	-	1.35/1.65	≤.04	.08/.13	-						
	1141	.37/.45	-	1.35/1.65	≤.04	.08/.13	-						
SUM43		.37/.45	-	1.35/1.65	≤.04	.24/.33	-						
	1144	.40/.48	-	1.35/1.65	≤.04	.24/.33	-	35.2	59.5	24.8	47.3	48	167
SUM23		≤.09	-	.75/1.05	.04/.09	.26/.35	-						
SUM21		≤.13	-	.70/1.00	.07/.12	.16/.23	-						
	1213	≤.13	-	.70/1.00	.07/.12	.24/.33	-						
SUM22		≤.13	-	.70/1.00	.07/.12	.24/.33	-						

YICK HOE