

STEEL PILES

Larssen and Frodingham profiles of sheet piling are well known to civil engineers throughout the world.

Their usefulness and reliability in all types of earth and water retaining structures has been proven on countless occasions over many years. However, with the benefit of experience and research, the range and efficiency of the sections has continually been improved.

The following information contains full details of a major development - the new range of Larssen profiles recently developed.

The new range provides sections which are markedly superior to those previously available in terms of strength to weight ratios, but which have also been carefully proportioned to retain the traditionally highly valued driving characteristics.

More comprehensive information on the design and installation of all sections is available in the Piling Handbook, available from the publisher of this handbook - CHYE HIN HARDWARE PTE LTD.

STEEL QUALITIES

	Ultimate stress		Minimum yield stress				Minimum elongation on 200 mm	
			Up to and including 16 mm thick		Over 16 mm up to and including 40 mm thick		Up to and including 9 mm thick	Over 9mm thick
	kg/mm ²	N/mm ²	kg/mm ²	N/mm ²	kg/mm ²	N/mm ²	%	%
BS.4360:1986 (mild steel) Grade FE 430A	43.8/59.0	430/580	28.0	275	27.0	265	16	20
BS.4360:1986 (High yield steel) Grade FE 510A	49.9/65.2	490/640	36.2	355	35.2	345	15	18
Similar to ASTM-A328	49.2 min.	482.6 min.	27.0	265	27.0	265	--	17

Notes:

COPPER BEARING STEEL - all the grades of steel are available with 0.20% up to 0.35% or over 0.35% up to 0.50% Copper content.

1N/mm² = 0.101972 kg/mm²

RECOMMENDED WORKING STRESSES FOR STEEL SHEET PILING

Class of work	BS.4360 Grade 43A ASTM A328 and CSA G40.7 (mild steel)		BS.4360 Grade 50A (high yield steel)	
	kg/mm ²	N/mm ²	kg/mm ²	N/mm ²
Permanent	14.2	140	18.3	180
Temporary	17.8	175	22.9	225

Note:

Stresses in temporary conditions occurring during construction may be varied at the discretion of the client's engineer.