

COLD FORMED HOLLOW SECTIONS

Other Tests			Dimensional Tolerances	
Flattening (min.)	Bend Test	Hydrostatic Test	On Diameter except for Non-Circular Tubes	On Wall Thickness
12	13	14	15	16
H = 2/3D H = 2/3D H = 7/8D H = 7/8D	6D at 90° 6D at 90° 8D at 90° 6D at 90°	-- -- --	Under 50 mm ± 0.25 mm 50 mm & over ± 0.50 %	Under 3mm ±0.30 mm 3mm - 12 mm ± 10% excluding
H = 1/2D H = 2/3D H = 2/3D -- H = 2/3D H = 3/4D -- H = 3/4D H = 7/8D	4D at 180° 6D at 90° 6D at 90° -- 6D at 90° 6D at 90° -- 6D at 90° 8D at 90°	--	As per Classification (No. 1, 2, 3) of Table 4	As per Classification (No. 1,2,3) of Table 5
H = 2/3D	6D at 90°	P=25 kgf/mm ²	10.5 to 48.6 mm ± 0.50mm 60.5 to 165. 2 mm ± 1%	+ not limited -12.5%
--	--	--	Up to 100 mm ± 1.5mm Over 100 mm ± 1.5% Squareness of side ± 1.5° Radii of corner Max. 3t ¹	Up to 3mm ±0.30 mm 3mm & over ± 10%

*9: P = Test Pressure

*10 t¹ = Thickness of Flat Portion