

## The numeric-verb style

This style is similar to `numeric` except that a list of multiple citations is printed in a slightly more verbose format.

### Multiple citations

[5], [8], [1], [3], [6], [7], [2], [4]  
[6c], [4c]

### Multiple citations with `\supercite`

This is just filler text.<sup>5,8,1,3,6,7,2,4</sup>  
This is just filler text.<sup>6c,4c</sup>

## References

- [1] Robert L. Augustine. *Heterogeneous catalysis for the synthetic chemist*. New York: Marcel Dekker, 1995.
- [2] Aaron Bertram and Richard Wentworth. “Gromov invariants for holomorphic maps on Riemann surfaces.” In: *J. Amer. Math. Soc.* 9.2 (1996), pp. 529–571.
- [3] Frank Albert Cotton et al. *Advanced inorganic chemistry*. 6th ed. Chichester: Wiley, 1999.
- [4] (a) Sheldon Glashow. “Partial Symmetries of Weak Interactions.” In: *Nucl. Phys.* 22 (1961), pp. 579–588; (b) Steven Weinberg. “A Model of Leptons.” In: *Phys. Rev. Lett.* 19 (1967), pp. 1264–1266; (c) Abdus Salam. “Weak and Electromagnetic Interactions.” In: *Elementary particle theory. Relativistic groups and analyticity*. Proceedings of the Eighth Nobel Symposium. (Aspenäs garden, Lerum, May 19–25, 1968). Ed. by Nils Svartholm. Stockholm: Almqvist & Wiksell, 1968, pp. 367–377.
- [5] Christopher Hammond. *The basics of crystallography and diffraction*. Oxford: International Union of Crystallography and Oxford University Press, 1997.
- [6] (a) Wolfgang A. Herrmann et al. “A carbocyclic carbene as an efficient catalyst ligand for C–C coupling reactions.” In: *Angew. Chem. Int. Ed.* 45.23 (2006), pp. 3859–3862; (b) Özge Aksın et al. “Effect of immobilization on catalytic characteristics of saturated Pd-N-heterocyclic carbenes in Mizoroki-Heck reactions.” In: *J. Organomet. Chem.* 691.13 (2006), pp. 3027–3036; (c) Myeong S. Yoon et al. “Palladium pincer complexes with reduced bond angle strain: efficient catalysts for the Heck reaction.” In: *Organometallics* 25.10 (2006), pp. 2409–2411.
- [7] Michael J. Hostetler et al. “Alkanethiolate gold cluster molecules with core diameters from 1.5 to 5.2 nm. Core and monolayer properties as a function of core size.” In: *Langmuir* 14.1 (1998), pp. 17–30.
- [8] Werner Massa. *Crystal structure determination*. 2nd ed. Berlin: Springer, 2004.