


Specimen 1 to 4



	Specimen label	Length [mm]	Thickness [mm]
1	bad	68.00	1.96
2	S2	68.40	1.94
3	S1	67.20	2.00
4	S3	68.61	1.92

	Width [mm]	Tensile stress at Tensile strength [MPa]	Tensile strain (Displacement) at Tensile strength [%]
1	35.00	3.00	147.07
2	35.00	2.75	146.21
3	34.98	2.47	148.82
4	35.00	2.71	145.76