HIGH-END SOC REBALLING TEMPERATURE PROFILE & REFLOW CURV

SMD Workshop Guide & Reflow Oven Specifications | Sheet 1 of 1

TEMPERATURE PROFILE STAGES

Standard Sn63Pb37 Solder Paste Heating Profile

Stage 1 (Preheat): 25 deg C to 120 deg C over 60 seconds (Rate: 1.5 deg C/sec)

Stage 2 (Soak): 120 deg C to 150 deg C for 90 seconds (Flux activation & solvent burnoff)

Stage 3 (Reflow Peak): 183 deg C (liquidus) ramping to 215 deg C peak for 20-30 seconds

Stage 4 (Cooling): Gradual cooling to 60 deg C at 3 deg C/sec to ensure crystal uniformity

Flux Recommendation: Genuine Amtech NC-559-ASM or Mechanic UV50 tacky flux

CONFIDENTIAL - SALEN MOBILE GURU CHIP-LEVEL HARDWARE LAB