Abstract

This process is licensed under the Libre Silicon public license; you can redistribute it and/or modify it under the terms of the Libre Silicon public license as published by the Libre Silicon alliance, either version 2 of the License, or (at your option) any later version.

This design is distributed in the hope that it will be useful, but WITHOUT ANY WARRANTY; without even the implied warranty of MERCHANTABILITY or FITNESS FOR A PARTICULAR PURPOSE. See the Libre Silicon Public License for more details.

This is the specification of the free silicon manufacturing standard for manufacturing the ls018[1]standard logic cells and related free technology nodes from the LibreSilicon project.

1 Well

	We start with a p-type silicon wafer
	We grow an oxide layer of approximately 1000 angstrom thickness (see documentation)
	We thin film deposit a layer of resist
	We expose and develop the pattern from the GDS2 layer information
	We etch the 1000 angstrom oxide layer
	Ion implantation: Implant Phosphorus (P); n-type impurity to create N-well (see documentation)
	Remove resist
	Remove oxide

2 Implant

	We grow an oxide layer of approximately 1000 angstrom thickness (see documentation)

3 Select

4 Active

5 Metal

[1] https://github.com/leviathanch/ls018