



Fig. S3 — Bond-angle distributions vs reference data



Peak ° / FWHM °

Si-O-Si ref. NMR (Mauri): 151 / 26 (Gaussian σ→FWHM)

Si-O-Si ref. CPMD: ~137 (peak)

24-atom Si-O-Si 131.5 / 33.0      O-Si-O 109.5 / 8.0

36-atom Si-O-Si 133.5 / 33.0      O-Si-O 108.5 / 11.0

48-atom Si-O-Si 129.5 / 32.0      O-Si-O 109.5 / 13.0

ref. CPMD O-Si-O: 109.5 / 9.0