	technology	energy density	specific cost	operating life
[h]		[Wh/kg]	[Wh/\$]	# cycles
	NiMH	100	3.41	500
	NiH2	45	10.50	20000
	LCO	195	2.84	750
	LMO	150	2.84	500
	NiCad	30	7.50	500
	SLA	30	7.00	500
	LiPo	150	2.50	600
	LFP	90	1.50	1500