	technology	energy density	specific cost	operating life
[h]		[Wh/kg]	[Wh/\$]	# cycles
	NiMH	100	3.4 1	500
	NiH2	45	10.50	20000
	LCO	195	2.84	750
	LMO	150	2.84	500
	NiCad	30	7.50	500
	SLA	30	7.00	500
	LiPo	150	2.50	600
	LFP	90	1.50	1500