

# Development and implementation of material subroutine for fibre reinforced plastics in a commercial FEM software

Master thesis

Winter semester 2018/19



Presented by: Arun prakash Ganapathy

Supervised by: Dr.-Ing Dominik Laveuve

Mat.Nr: 63876

E-mail: [arun-prakash.ganapathy@student.tu-freiberg.de](mailto:arun-prakash.ganapathy@student.tu-freiberg.de)

# 1 Introduction

## 1.1 Background and motivation

Composite materials are made of two or more dissimilar materials of different physical or chemical properties when combined, create a material with properties unlike the individual constituent materials. The earliest use of composite materials date back to 3400 B.C when Mesopotamians glued wood strips at different angles to create plywood. Another notable example is the bow made by Mongols during 1200 A.D, which is made from a combination of bamboo, wood, cattle tendons and silk bonded with natural resin. In the early, 1900s bakelite based composites were developed for its non-conductivity and heat resistant properties and widely used in industrial and consumer applications. Now a days advanced composite materials are widely used in structural design in various industries such as aerospace, automobile, marine, petrochemical etc., due to their superior properties over traditional engineering materials.




Figure 1: Composite materials used in a Boeing 787 'Dreamliner'

Composite material are attractive because of their high strength, stiffness, high stiffness-to-density ratio, light weight properties etc., Another important reason for using composite materials is the ability to tailor the stiffness and strength to specific design load flexibly. Despite their superior physical properties, composite materials are fragile and can be easily damaged from number of sources, both during initial processing and in operation. Since composite materials possess elastic brittle properties with negligible margin of safety through ductility as offered by metals and accumulate damage before structural collapse, the development of damage must be understood for predicting failure of such materials. For example fibre-reinforced plastics exhibit local damage such as fibre breakage, matrix cracks, fibre matrix debonds etc., under normal operating conditions which may contribute to the failure. Therefore the ability to predict the initiation and growth of damage is important for predicting the performance of the composite materials for safe and reliable use of such materials. Continuum damage mechanics (CDM) has been considered as a reliable candidate for creating numerical models which predict the onset and evolution of the damage in the composite materials.

## 2 Continuum damage mechanics

Continuum damage mechanics (CDM) is a theory for analyzing damage and fracture processes in materials from continuum mechanics point of view. Continuum damage mechanics (CDM) provides a continuum perspective for microflaws initiation, propagation, and their coalescence that eventually results in macroscopic faults and fractures. CDM uses state variables to represent the effect of damage on the stiffness and remaining life of the material that is damaging as a result of load and ageing. A Damage activation function is required to predict the initiation of damage. Damage evolution does not progress spontaneously after initiation therefore a mathematical model is required. In plasticity formulations, the damage evolution is controlled by a hardening function but this requires additional phenomenological parameters that must be found through experimentation, which is expensive and time consuming. On the other hand, micromechanics of damage formulations are able to predict both damage initiation and evolution without additional material properties.

### 2.1 Damage

Consider a body  $B$  of Fig. 2 where a crack of length  $a$  has developed due to an external load  $F$ . If we take an arbitrary point  $P(x)$  near the crack tip, a number of microscopic cavities or microcracks would be observed around the region. These cavities can be nucleated usually as a result of breakage of atomic bonds, or of some defects in atomic array. From microscopic point of view, fracture of materials is a process of nucleation of microcavities or microcracks due to the breakage of atomic bonds. From macroscopic point of view, it is a process of extension of cracks brought about by the coalescence of these microcracks. From mesoscopic point of view, which exists between microscopic and macroscopic scale, it is a process of nucleation, growth and the coalescence of microscopic cavities leads to the initiation of macroscopic crack. The development of microscopic, mesoscopic and the macroscopic processes of fracture in materials together with the resulting deterioration in their mechanical properties is called damage. Continuum damage mechanics, in particular, aims at the analysis of the damage development in mesoscopic and macroscopic fracture processes in the framework of continuum mechanics.




Figure 2: Scales of damage observation

The separation of atomic bonds is induced either by shear or tensile decohesion. However the separation of material at the microscopic level consists of four damage mechanisms namely Cleavage, Growth and Coalescence of Microvoids, Glide plane decohesion and Void Growth due to Grain-Boundary diffusion. The aspects of damage vary largely by difference in materials and loading conditions. The damage may be classified phenomenologically as follows

- Ductile Damage
- Brittle Damage
- Creep Damage
- Low Cycle Fatigue
- Very Low Cycle Fatigue
- High Cycle fatigue damage
- Very High Cycle fatigue damage
- Creep Damage

## 2.2 Representative Volume Element(RVE)

In order to discuss the effects of microscopic discontinuities in a material by means of CDM we must homogenize the mechanical effects of microstructure and represent them as a macroscopic continuous field in the material. For this purpose we take a small region of a mesoscale around the material point  $P(x)$  in a body  $B$  as shown in Fig. 2. We assume that the material with discontinuous structures in this region can be statistically homogeneous and the mechanical state of the material in this region can be represented by the statistical average of the mechanical variables in that region. This region is said to be the Representative Volume Element(RVE). For such RVE, the following two conditions must be satisfied:

- For the material in the RVE to be statistically homogeneous, the RVE should be large enough to contain a sufficient number of discontinuities
- In order to represent a non-uniform macroscopic mechanical field by means of a continuum, the size of RVE should be sufficiently small so that the variation of the macroscopic variable in it may be insignificantly small

The size of RVE depends on the microstructure of the relevant material and their typical sizes are as follows

- Metals and ceramics -  $0.1mm^3$
- Polymer and composites -  $1mm^3$
- Timber -  $10mm^3$
- Concrete -  $100mm^3$

## 2.3 Concept of Continuum damage mechanics (CDM)

The basic concept of CDM is to that microstructural defects in a material can be represented by a set of damage variables. Continuum damage mechanics first represent the damage state of a material in terms of damage variables and then describe the mechanical behaviour of the damaged material and then development of damage by use of these damage variables. Let us consider a body B of Fig. 3 and take a representative volume element(RVE) at an arbitrary point  $P(x)$  in B. If the total void area in  $dA$  is  $dA_D$ , the mechanical effect of  $dA$  will be decreased by  $dA_D$ . Then the area,

$$d\tilde{A} = dA - dA_D \quad (1)$$

may be interpreted as the area which carries the internal force and is called as *effective area*. Thus the damage variable D can be specified as

$$D = \frac{dA - d\tilde{A}}{dA} = \frac{dA_D}{dA} \quad (2)$$

where the damage variable D takes value between 0 and 1 ( $0 \leq D \leq 1$ ).  $D = 0$  representing initial undamaged state and  $D = 1$  represents fully damaged state. Suppose




Figure 3: Effective area reduction due to microcracks

a cylindrical bar of cross-sectional area  $dA$  is subject to a tensile load  $dF$  the actual load carrying area is  $d\tilde{A}$  rather than  $dA$ . According to eqn (1) and (2) the effective area  $d\tilde{A}$  is given by,

$$d\tilde{A} = (1 - D)dA \quad (3)$$

The decrease in load-carrying area increase the effect of stress  $\sigma$  induced by the external force  $dF$ . Due to eqn (3) the magnified stress  $\tilde{\sigma}$  is given by,

$$\tilde{\sigma} = \frac{dF}{d\tilde{A}} = \frac{\sigma}{1 - D} \quad (4)$$

Since the stress  $\tilde{\sigma}$  represents the effect of stress magnified by the net area reduction due to damage, it is called as effective stress. From eqn (3) and (4) we can postulate that the damaged cylindrical bar of Fig.4b with the cross-section  $dA$  subject to force  $dF$  is mechanically equivalent to the fictitious undamaged bar of Fig.4c which is subject to force  $dF$ , has the cross-section  $d\tilde{A}$  and hence stress has the stress  $\tilde{\sigma}$




Figure 4: Damage of bar under tensile load

### 2.3.1 Modelling by variation of elastic modulus

Since the development of microcracks induces the reduction in stiffness of material, the damage state can be characterized by variation in elastic modulus. Let us consider the bar (b) and (c) of Fig4 are in damaged and fictitious undamaged state respectively. Then the elastic strain  $\epsilon$  in the bar (c) caused by stress  $\tilde{\sigma}$  should be equal to the  $\epsilon$  of the bar (b) under stress  $\sigma$ ; i.e.,

$$\tilde{\sigma} = E_0 \epsilon, \quad \sigma = E(D) \epsilon \quad (5)$$

$$\epsilon = \frac{\sigma}{E(D)} = \frac{\tilde{\sigma}}{E_0} \quad (6)$$

where  $E_0$  and  $E(D)$  denote young's modulus of the material in the initial undamaged state and that in damaged state after loading, respectively. Therefore, eqn(6) defines another effective stress

$$\epsilon = \frac{E_0}{E(D)} \sigma \quad (7)$$

By combining Eqn(4) and (6) we get,

$$E(D) = (1 - D) E_0 \quad (8)$$

$$D = 1 - \frac{E(D)}{E_0} \quad (9)$$

Therefore, the damage variable  $D$  is characterized by the variation in Young's modulus  $E(D)$ . The modelling of damage by means of reduction in stiffness can be applied also the anisotropic damage of brittle materials like composite materials, concrete, rocks etc.,

## 2.4 Mechanical representation of three dimensional damage state

The deformation of a material basically depends on the direction of applied stress or strain and hence it is an anisotropic phenomenon. Therefore different theories have been developed for modelling 3-D anisotropic damage phenomenon. Some fundamental theories that describes 3-D damage state are given below

### Scalar Damage Variable

In case of random or isotropic distribution of microcracks or voids , the damage state is usually considered as isotropic. the damage state in this case may be represented by means of scalar damage variable  $D$ . When microvoids have oriented distribution the damage state is anisotropic and the scalar damage variable cannot be applied accurately. However, when void density is small the global mechanical properties can be approximated as nearly isotropic. thus isotropic damage theory based on isotropic damage variable has been often applied to 3-D problems of creep, elastic-plastic, ductile and fatigue damage

#### 2.4.1 Plural Scalar damage variables

A single scalar damage variable is often insufficient to describe the variation in mechanical properties of the damaged materials, even if the distribution of microcracks are isotropic. Plural scalar damage variables are often employed to characterize several different microscopic mechanisms of the relevant damage development.

#### 2.4.2 Vector damage variable

The damage state can be specified by the decrease in load carrying effective area due to void development. hence it is easy to postulate a vector damage variable. Kachanov (1974, 1986) tried to extend the definition of damage to anisotropic damage by noting a surface element in an arbitrary direction  $n$ , he proposed a vector damage variable  $\omega = \omega_n n$ , where  $\omega_n$  is the effective area fraction. However the damage variable  $D(n)$  discussed at the beginning representing the damage state of a plane with specific unit normal vector  $n$  should be unchanged irrespective of the change in the sense of  $n$  and hence we have the requirement,

$$D(n) = D(-n) \quad (10)$$