

Aathivinayaga Refractories



Technical Data Sheet

Product Name : Fire Cast - C

SI No	Properties	Value
1	Service Temperature °C (Max)	1450
2	Grain Size (MM) (Max)	5
3	Water Required to Mix	13 to 14
4	Method of Installation	Patching/Travelling/Vibro Casting
5	Bulk Density (gm/cc) (Min) Dried at 110°C	2.2
Cold Crushing Strength (Kg/Cm²) (Min)		
1	110°C	400
2	1100°C	300
3	1300°C	350
4	1500°C	
Permanent Linear Change (%) (Max)		
1	1100°C	1.0
2	1300°C	1.5
3	1500°C	
Chemical Analysis (%)		
1	Al ₂ O ₃	50
2	Fe ₂ O ₃	2.0
Recommended Application Areas		

Factory Address: No: 189/5 Periyakandiyankuppam, Aaladi Road, Virudhachalam Taluk, Cuddalore District, TamilNadu. Pin Code: 606001.

Mobile: +91 8667497262 / +91 9566802585

E-Mail-aathivinayaga@outlook.com & aathivinayaga2020@gmail.com