

# **Aathivinayaga Refractories**



## **Technical Data Sheet**

### **Product Name : Fire In Cast - 11**

SI No	Properties	Value
1	Service Temperature °C (Max)	1000
2	Grain Size (MM) (Max)	6
3	Water Required to Mix	
4	Method of Installation	
5	Bulk Density (gm/cc) (Min) Dried at 110°C	1.25
<b>Cold Crushing Strength (Kg/Cm<sup>2</sup>) (Min)</b>		
1	110°C	35
2	800°C	
3	1100°C	
4	1200°C	
<b>Permanent Linear Change (%) (Max)</b>		
1	800°C	1
2	1000°C	
3	1100°C	1.2
<b>Thermal Conductivity (Kcal/m/hr/°C)</b>		
1	400°C	0.35
2	600°C	0.4
3	800°C	0.5
4	1000°C	0.55
<b>Chemical Analysis (%)</b>		
1	Al <sub>2</sub> O <sub>3</sub>	35
2	Fe <sub>2</sub> O <sub>3</sub>	5
<b>Recommended Application Areas</b>		

**Factory Address:** No: 189/5 Periyakandiyankuppam, Aaladi Road, Virudhachalam Taluk, Cuddalore District, TamilNadu. Pin Code: 606001.

Mobile: +91 8667497262 / +91 9566802585

E-Mail-aathivinayaga@outlook.com & aathivinayaga2020@gmail.com