Characteristic | Unit | Value | Min | Max | Status |
Inherent Viscosity | | 0.921 | 0.9 | 0.94 | ■ Approved |
Volatiles | % | 0.057 | 0.0 | 0.3 | ■ Approved |
RVCM | ppm | 0.02 | 0.0 | 2.0 | ■ Approved |
Retained on 40 Mesh | % | 0.0 | 0.0 | 0.2 | ■ Approved |
Retained on 60 Mesh | % | 0.0 | 0.0 | 2.0 | ■ Approved |
Retained on 80 Mesh | % | 2.93 | 0.0 | 0.0 | ■ Rejected |
Retained on 100 Mesh | % | 21.09 | 0.0 | 0.0 | ■ Rejected |
Retained on 140 Mesh | % | 61.49 | 0.0 | 0.0 | ■ Rejected |
Retained on 200 Mesh | % | 13.66 | 0.0 | 25.0 | ■ Approved |
Retained on Pan | % | 0.83 | 0.0 | 6.0 | ■ Approved |
DIPP | Lal FE (3 Min) | | 47.0 | 0.0 | 50.0 | ■ Approved |
DIPP | Lal FE (3 Min) | | 47.0 | 0.54 | ■ Approved |
Contamination | | 0 | 0 | 12 | ■ Approved